

# Detailed Member Calculations

**Units: N&mm**

**Regulation: ASCE 41-17**

## Calculation No. 1

column C1, Floor 1


Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity  $V_{Rd}$

Edge: Start

Local Axis: (2)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.

Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 Existing Column  
 New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$   
 New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$   
 Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 #####  
 Note: Especially for the calculation of  $\mu_y$  for displacement ductility demand,  
 the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as  
 Deformation-Controlled Action (Table C7-1, ASCE 41-17).  
 Jacket  
 New material: Concrete Strength,  $f_c = f_{cm} = 33.00$   
 New material: Steel Strength,  $f_s = f_{sm} = 555.56$   
 Existing Column  
 New material: Concrete Strength,  $f_c = f_{cm} = 33.00$   
 New material: Steel Strength,  $f_s = f_{sm} = 555.56$   
 #####  
 Max Height,  $H_{max} = 750.00$   
 Min Height,  $H_{min} = 400.00$   
 Max Width,  $W_{max} = 750.00$   
 Min Width,  $W_{min} = 400.00$   
 Jacket Thickness,  $t_j = 100.00$   
 Cover Thickness,  $c = 25.00$   
 Element Length,  $L = 3000.00$   
 Primary Member  
 Ribbed Bars  
 Ductile Steel  
 Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
 Longitudinal Bars With Ends Lapped Starting at the End Sections  
 Inadequate Lap Length with  $l_o/l_{o,min} = l_b/l_d = 0.30$   
 FRP Wrapping Data  
 Type: Carbon  
 Dry properties (design values)  
 Thickness,  $t = 1.00$   
 Tensile Strength,  $f_{fu} = 840.00$   
 Tensile Modulus,  $E_f = 82000.00$   
 Elongation,  $e_{fu} = 0.009$   
 Number of directions,  $NoDir = 1$   
 Fiber orientations,  $bi: 0.00^\circ$   
 Number of layers,  $NL = 1$   
 Radius of rounding corners,  $R = 40.00$

-----  
 Stepwise Properties  
 -----

EDGE -A-  
 Bending Moment,  $M_a = -1.5106E+007$   
 Shear Force,  $V_a = -4865.29$   
 EDGE -B-  
 Bending Moment,  $M_b = 505194.60$   
 Shear Force,  $V_b = 4865.29$   
 BOTH EDGES  
 Axial Force,  $F = -18154.424$   
 Longitudinal Reinforcement Area Distribution (in 2 divisions)  
 -Tension:  $As_t = 0.00$   
 -Compression:  $As_c = 5353.274$   
 Longitudinal Reinforcement Area Distribution (in 3 divisions)  
 -Tension:  $As_{l,ten} = 1137.257$   
 -Compression:  $As_{l,com} = 2208.54$   
 -Middle:  $As_{l,mid} = 2007.478$   
 Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$   
 -----  
 -----

New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $VR = 1.0 * V_n = 948969.182$

$V_n$  ((10.3), ASCE 41-17) =  $k_n \cdot V_{CoI0} = 948969.182$

$V_{CoI} = 948969.182$

$k_n = 1.00$

$displacement\_ductility\_demand = 0.02149821$

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c\_jacket} \cdot Area\_jacket + f'_{c\_core} \cdot Area\_core) / Area\_section = 25.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1.5106E+007$

$V_u = 4865.29$

$d = 0.8 \cdot h = 600.00$

$N_u = 18154.424$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$

$V_{s,j1} = 251327.412$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 471238.898$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 88467.249$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$s/d = 0.56818182$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression, where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L \cdot t / N_{oDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 797164.595$

$b_w = 400.00$

displacement\_ductility\_demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END A -  
for rotation axis 3 and integ. section (a)

From analysis, chord rotation = 5.3401566E-005  
 $y = (M_y * L_s / 3) / E_{eff} = 0.002484$  ((4.29), Biskinis Phd))  
 $M_y = 3.6650E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 3104.858  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
factor = 0.30  
 $A_g = 440000.00$   
Mean concrete strength:  $f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00$   
 $N = 18154.424$   
 $E_c * I_g = E_{c,jacket} * I_{g,jacket} + E_{c,core} * I_{g,core} = 5.0901E+014$

Calculation of Yielding Moment  $M_y$

Calculation of  $\delta / y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:  
flange width,  $b = 750.00$   
web width,  $b_w = 400.00$   
flange thickness,  $t = 400.00$

$y = \text{Min}(y_{ten}, y_{com})$   
 $y_{ten} = 2.7302957E-006$   
with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 * f_y * (I_b / I_d)^{2/3}) = 311.2112$   
 $d = 707.00$   
 $y = 0.19388674$   
 $A = 0.01020577$   
 $B = 0.00451618$   
with  $p_t = 0.00214476$   
 $p_c = 0.00416509$   
 $p_v = 0.00378591$   
 $N = 18154.424$   
 $b = 750.00$   
" = 0.06082037  
 $y_{comp} = 1.6519231E-005$   
with  $f_c' (12.3, (ACI 440)) = 33.60672$   
 $f_c = 33.00$   
 $f_l = 0.61848273$   
 $b = b_{max} = 750.00$   
 $h = h_{max} = 750.00$   
 $A_g = 0.44$   
 $g = p_t + p_c + p_v = 0.01009575$   
 $rc = 40.00$   
 $A_e / A_c = 0.31291181$   
Effective FRP thickness,  $t_f = N_L * t * \text{Cos}(b_1) = 1.00$   
effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$   
 $f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19183796$   
 $A = 0.01001935$   
 $B = 0.00440616$   
with  $E_s = 200000.00$   
CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $I_b / I_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1  
At local axis: 2  
Integration Section: (a)

## Calculation No. 2

column C1, Floor 1



Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity (  $\theta$  )

Edge: Start

Local Axis: (2)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3  
(Bending local axis: 2)  
Section Type: rcjcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

-----  
At local axis: 3

EDGE -A-

Shear Force,  $V_a = -0.00017144$

EDGE -B-

Shear Force,  $V_b = 0.00017144$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{sl,t} = 0.00$

-Compression:  $A_{sl,c} = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $A_{sl,ten} = 1137.257$

-Compression:  $A_{sl,com} = 2208.54$

-Middle:  $A_{sl,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio,  $V_e/V_r = 0.49879178$

Member Controlled by Flexure ( $V_e/V_r < 1$ )

Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$

with

$M_{pr1} = \text{Max}(M_{u1+}, M_{u1-}) = 8.1540E+008$

$M_{u1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination

$M_{u1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination

$M_{pr2} = \text{Max}(M_{u2+}, M_{u2-}) = 8.1540E+008$

$M_{u2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the static loading combination

$M_{u2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the static loading combination

-----  
Calculation of Mu1+  
-----

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 8.4959181E-006$$

$$Mu = 4.9689E+008$$

-----

with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

-----

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

-----

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length

equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_s,jacket * A_{sl,ten,jacket} + f_s,core * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es1 = (E_s,jacket * A_{sl,ten,jacket} + E_s,core * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (f_s,jacket * A_{sl,com,jacket} + f_s,core * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with  $Es2 = (E_s,jacket * A_{sl,com,jacket} + E_s,core * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.0557338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu1-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008  
-----

with full section properties:

b = 400.00

d = 707.00

d' = 43.00

v = 0.00174378

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu: cu\* = shear\_factor \* Max( cu, cc) = 0.01241186

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY: cu = 0.01241186

we ((5.4c), TBDY) = ase\* sh,min\*fywe/fce+ Min( fx, fy) = 0.0496383

where f = af\*pf\*ffe/fce is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = N_L * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f,e} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length

equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length

equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

psh2 ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 =  $0.4 * esu1_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs_{jacket} * A_{sl,ten,jacket} + fs_{core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with Es1 =  $(Es_{jacket} * A_{sl,ten,jacket} + Es_{core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 =  $0.4 * esu2_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 =  $(fs_{jacket} * A_{sl,com,jacket} + fs_{core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with Es2 =  $(Es_{jacket} * A_{sl,com,jacket} + Es_{core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv =  $0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY  
For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv =  $(fs_{jacket} * A_{sl,mid,jacket} + fs_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$

with Esv =  $(Es_{jacket} * A_{sl,mid,jacket} + Es_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$

1 =  $A_{sl,ten} / (b * d) * (fs1 / fc) = 0.09206128$

2 =  $A_{sl,com} / (b * d) * (fs2 / fc) = 0.04740567$

v =  $A_{sl,mid} / (b * d) * (fsv / fc) = 0.08368017$

and confined core properties:

b = 340.00

d = 677.00

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.11310683$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.05824278$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

---

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $Mu_{2+}$   
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 8.4959181E-006$$

$$Mu = 4.9689E+008$$

-----  
with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00093001$$

$$N = 16273.607$$

$$fc = 33.00$$

$$co (5A.5, TBDY) = 0.002$$

$$\text{Final value of } cu: cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } cu = 0.01241186$$

$$w_e ((5.4c), TBDY) = ase * sh, \min * fy_{we} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff,e = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff,e = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } tf = NL * t * \text{Cos}(b1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$ase \text{ ((5.4d), TBDY)} = (ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$$

$$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$ase2 \text{ (>=ase1)} = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } c_c = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$l_o / l_{ou,min} = l_b / d = 0.30$$

$$su1 = 0.4 * e_{su1,nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $e_{su1,nominal} = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs_{jacket} \cdot Asl_{ten,jacket} + fs_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 389.0139$

with  $Es1 = (Es_{jacket} \cdot Asl_{ten,jacket} + Es_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/lb_{,min} = 0.30$

$su2 = 0.4 \cdot esu2\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs_{jacket} \cdot Asl_{com,jacket} + fs_{core} \cdot Asl_{com,core}) / Asl_{com} = 389.0139$

with  $Es2 = (Es_{jacket} \cdot Asl_{com,jacket} + Es_{core} \cdot Asl_{com,core}) / Asl_{com} = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/ld = 0.30$

$suv = 0.4 \cdot esuv\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} \cdot Asl_{mid,jacket} + fs_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 389.0139$

with  $Es_v = (Es_{jacket} \cdot Asl_{mid,jacket} + Es_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 200000.00$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.02528302$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.04909935$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$fcc$  (5A.2, TBDY) = 34.43547

$cc$  (5A.5, TBDY) = 0.00243499

$c$  = confinement factor = 1.0435

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.02869934$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.0557338$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs_{y2}$  - LHS eq.(4.5) is satisfied

--->

$su$  (4.9) = 0.1476063

$Mu = MRc$  (4.14) = 4.9689E+008

$u = su$  (4.1) = 8.4959181E-006

-----  
Calculation of ratio  $lb/ld$

-----  
Inadequate Lap Length with  $lb/ld = 0.30$   
-----  
-----  
-----

## Calculation of Mu2-

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o(5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e(5.4c, TBDY) = a_s e^* s_{h, \min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f,e} = 0.015$$

$$a_s e(5.4d, TBDY) = (a_s e_1 * A_{ext} + a_s e_2 * A_{int}) / A_{sec} = 0.45746528$$

$$a_s e_1 = \text{Max}(((A_{conf, \max 1} - A_{noConf 1}) / A_{conf, \max 1}) * (A_{conf, \min 1} / A_{conf, \max 1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf, \min 1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf, \max 1}$  by a length

equal to half the clear spacing between external hoops.

$A_{noConf 1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

$$a_s e_2 (>= a_s e_1) = \text{Max}(((A_{conf, \max 2} - A_{noConf 2}) / A_{conf, \max 2}) * (A_{conf, \min 2} / A_{conf, \max 2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su_1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_1 = (f_{s,jacket} * A_{sl,ten,jacket} + f_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es_1 = (E_{s,jacket} * A_{sl,ten,jacket} + E_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y_2 = 0.00140044$

$sh_2 = 0.0044814$

$ft_2 = 466.8167$

$fy_2 = 389.0139$

$su_2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su_2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered characteristic value  $fsy_2 = fs_2/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_2 = (f_{s,jacket} * A_{sl,com,jacket} + f_{s,core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with  $Es_2 = (E_{s,jacket} * A_{sl,com,jacket} + E_{s,core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$

$y_v = 0.00140044$

$sh_v = 0.0044814$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lo_{u,min} = lb/d = 0.30$$

$$suv = 0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv_{nominal} = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv_{nominal}$  and  $yv$ ,  $shv$ ,  $ftv$ ,  $fyv$ , it is considered  
characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1$ ,  $ft1$ ,  $fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs_{jacket} * Asl_{mid,jacket} + fs_{mid} * Asl_{mid,core}) / Asl_{mid} = 389.0139$$

$$\text{with } Esv = (Es_{jacket} * Asl_{mid,jacket} + Es_{mid} * Asl_{mid,core}) / Asl_{mid} = 200000.00$$

$$1 = Asl_{ten} / (b * d) * (fs1 / fc) = 0.09206128$$

$$2 = Asl_{com} / (b * d) * (fs2 / fc) = 0.04740567$$

$$v = Asl_{mid} / (b * d) * (fsv / fc) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl_{ten} / (b * d) * (fs1 / fc) = 0.11310683$$

$$2 = Asl_{com} / (b * d) * (fs2 / fc) = 0.05824278$$

$$v = Asl_{mid} / (b * d) * (fsv / fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---

$v < vs,y2$  - LHS eq.(4.5) is satisfied

---

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

Calculation of ratio  $lb/d$

Inadequate Lap Length with  $lb/d = 0.30$

Calculation of Shear Strength  $Vr = \text{Min}(Vr1, Vr2) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $Vr1 = 1.0898E+006$

$$Vr1 = VCol ((10.3), ASCE 41-17) = knl * VCol0$$

$$VCol0 = 1.0898E+006$$

$$knl = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $Vs = Av * fy * d / s$ ' is replaced by ' $Vs + f * Vf$ '  
where  $Vf$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $fc' = (fc'_{jacket} * Area_{jacket} + fc'_{core} * Area_{core}) / Area_{section} = 33.00$ , but  $fc'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$Mu = 1518.009$$

$$Vu = 0.00017144$$

$$d = 0.8 * h = 600.00$$

$$Nu = 16273.607$$

$$Ag = 300000.00$$

From (11.5.4.8), ACI 318-14:  $Vs = Vs_{jacket} + Vs_{core} = 901155.609$

where:

$$Vs_{jacket} = Vs_{j1} + Vs_{j2} = 802857.879$$

Vs,j1 = 523602.964 is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

Vs,j1 is multiplied by Col,j1 = 1.00

$$s/d = 0.16666667$$

Vs,j2 = 279254.914 is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

Vs,j2 is multiplied by Col,j2 = 1.00

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

Vs,c1 = 98297.73 is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

Vs,c1 is multiplied by Col,c1 = 1.00

$$s/d = 0.56818182$$

Vs,c2 = 0.00 is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

Vs,c2 is multiplied by Col,c2 = 0.00

$$s/d = 1.5625$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

wf/sf = 1 (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression,

where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

$$\text{orientation 1: } \theta = b1 + 90^\circ = 90.00$$

$$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a1)|), \text{ with:}$$

$$\text{total thickness per orientation, } t_{f1} = NL * t / \text{NoDir} = 1.00$$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe}((11-5), ACI 440) = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$b_w = 400.00$$

-----  
Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$$V_{r2} = V_{Col}((10.3), ASCE 41-17) = knl * V_{Col0}$$

$$V_{Col0} = 1.0898E+006$$

$$knl = 1 \text{ (zero step-static loading)}$$

-----  
NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$$= 1 \text{ (normal-weight concrete)}$$

Mean concrete strength:  $f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 * h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } V_s = V_{s,jacket} + V_{s,core} = 901155.609$$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{s,j2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

$wf/sf = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

$$\text{orientation 1: } \theta = b1 + 90^\circ = 90.00$$

$$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a1)|), \text{ with:}$$

$$\text{total thickness per orientation, } tf1 = NL * t / NoDir = 1.00$$

$$dfv = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$ffe((11-5), ACI 440) = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$bw = 400.00$$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 3  
-----

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 2

(Bending local axis: 3)

Section Type: rcjlc

Constant Properties  
-----

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$   
 Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 Existing Column  
 New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$   
 New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$   
 Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 #####  
 Note: Especially for the calculation of moment strengths,  
 the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14  
 Jacket  
 New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$   
 Existing Column  
 New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$   
 #####  
 Max Height,  $H_{max} = 750.00$   
 Min Height,  $H_{min} = 400.00$   
 Max Width,  $W_{max} = 750.00$   
 Min Width,  $W_{min} = 400.00$   
 Jacket Thickness,  $t_j = 100.00$   
 Cover Thickness,  $c = 25.00$   
 Mean Confinement Factor overall section = 1.0435  
 Element Length,  $L = 3000.00$   
 Primary Member  
 Ribbed Bars  
 Ductile Steel  
 Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
 Longitudinal Bars With Ends Lapped Starting at the End Sections  
 Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
 FRP Wrapping Data  
 Type: Carbon  
 Dry properties (design values)  
 Thickness,  $t = 1.00$   
 Tensile Strength,  $f_{fu} = 840.00$   
 Tensile Modulus,  $E_f = 82000.00$   
 Elongation,  $e_{fu} = 0.009$   
 Number of directions,  $N_{oDir} = 1$   
 Fiber orientations,  $b_i: 0.00^\circ$   
 Number of layers,  $N_L = 1$   
 Radius of rounding corners,  $R = 40.00$

-----  
 Stepwise Properties  
 -----

At local axis: 2  
 EDGE -A-  
 Shear Force,  $V_a = -0.0001715$   
 EDGE -B-  
 Shear Force,  $V_b = 0.0001715$   
 BOTH EDGES  
 Axial Force,  $F = -16273.607$   
 Longitudinal Reinforcement Area Distribution (in 2 divisions)  
   -Tension:  $A_{sl,t} = 0.00$   
   -Compression:  $A_{sl,c} = 5353.274$   
 Longitudinal Reinforcement Area Distribution (in 3 divisions)  
   -Tension:  $A_{sl,ten} = 1137.257$   
   -Compression:  $A_{sl,com} = 2208.54$   
   -Middle:  $A_{sl,mid} = 2007.478$

-----  
 -----  
 Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
 Member Controlled by Flexure ( $V_e/V_r < 1$ )  
 Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
 with

$$M_{pr1} = \text{Max}(M_{u1+}, M_{u1-}) = 8.1540\text{E}+008$$

$M_{u1+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination

$M_{u1-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination

$$M_{pr2} = \text{Max}(M_{u2+}, M_{u2-}) = 8.1540\text{E}+008$$

$M_{u2+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination

$M_{u2-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $M_{u1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:

$$\phi_u = 8.4959181\text{E}-006$$

$$M_u = 4.9689\text{E}+008$$

-----  
with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha_{co} (5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \phi_{cu}: \phi_{cu}^* = \text{shear\_factor} * \text{Max}(\phi_{cu}, \phi_{cc}) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \phi_{cu} = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY)} = \alpha_{se} * \text{sh}_{,\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha_f * \rho_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } \rho_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } \rho_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY)} = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1} ((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2} (5.4d) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1} ((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2} ((5.4d), \text{TBDY}) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c$  = confinement factor = 1.0435

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$l_0/l_{ou,min} = l_b/l_d = 0.30$

$su_1 = 0.4 * esu_{1,nominal} ((5.5), \text{TBDY}) = 0.032$

From table 5A.1, TBDY:  $esu_{1,nominal} = 0.08$ ,

For calculation of  $esu_{1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_1 = (f_{s,jacket} * A_{sl,ten,jacket} + f_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es_1 = (E_{s,jacket} * A_{sl,ten,jacket} + E_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y_2 = 0.00140044$

$sh_2 = 0.0044814$

$ft_2 = 466.8167$

$fy_2 = 389.0139$

$su_2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.0557338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30

-----  
Calculation of Mu1-

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008

-----  
with full section properties:

b = 400.00

d = 707.00

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$\text{we ((5.4c), TBDY) } = a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = NL * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$a_{se} ((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization

of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length

equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization

of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length

equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered

characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{sv} = (f_{s,jacket} \cdot A_{s,mid,jacket} + f_{s,mid} \cdot A_{s,mid,core}) / A_{s,mid} = 389.0139$

with  $E_{sv} = (E_{s,jacket} \cdot A_{s,mid,jacket} + E_{s,mid} \cdot A_{s,mid,core}) / A_{s,mid} = 200000.00$

1 =  $A_{s,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.09206128$

2 =  $A_{s,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.04740567$

$v = A_{s,mid} / (b \cdot d) \cdot (f_{sv} / f_c) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$f_{cc} (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

1 =  $A_{s,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.11310683$

2 =  $A_{s,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.05824278$

$v = A_{s,mid} / (b \cdot d) \cdot (f_{sv} / f_c) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

---->

$su (4.9) = 0.21669624$

$Mu = MRc (4.14) = 8.1540E+008$

$u = su (4.1) = 9.2452857E-006$

-----  
Calculation of ratio  $lb/ld$

-----  
Inadequate Lap Length with  $lb/ld = 0.30$   
-----  
-----

-----  
Calculation of  $Mu_{2+}$   
-----  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$

$Mu = 4.9689E+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$co (5A.5, TBDY) = 0.002$

Final value of  $cu$ :  $cu^* = \text{shear\_factor} \cdot \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

$w_e ((5.4c), TBDY) = a_{se} \cdot sh_{,min} \cdot fy_{we} / f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = a_f \cdot pf \cdot f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $fx = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2t_f / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $f_{fe} = 765.1636$   
-----

$fy = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff,e = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } tf = NL * t * \cos(b1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$ase \text{ ((5.4d), TBDY)} = (ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$$

$$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$ase2 \text{ (} \geq ase1 \text{)} = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$sh1 = 0.0044814$   
 $ft1 = 466.8167$   
 $fy1 = 389.0139$   
 $su1 = 0.00512$   
 using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
 and also multiplied by the shear\_factor according to 15.7.1.4, with  
 Shear\_factor = 1.00  
 $lo/lou,min = lb/ld = 0.30$   
 $su1 = 0.4*esu1\_nominal ((5.5), TBDY) = 0.032$   
 From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,  
 For calculation of  $esu1\_nominal$  and  $y1, sh1,ft1,fy1$ , it is considered  
 characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.  
 $y1, sh1,ft1,fy1$ , are also multiplied by  $Min(1,1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.  
 with  $fs1 = (fs,jacket*Asl,ten,jacket + fs,core*Asl,ten,core)/Asl,ten = 389.0139$   
 with  $Es1 = (Es,jacket*Asl,ten,jacket + Es,core*Asl,ten,core)/Asl,ten = 200000.00$   
 $y2 = 0.00140044$   
 $sh2 = 0.0044814$   
 $ft2 = 466.8167$   
 $fy2 = 389.0139$   
 $su2 = 0.00512$   
 using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
 and also multiplied by the shear\_factor according to 15.7.1.4, with  
 Shear\_factor = 1.00  
 $lo/lou,min = lb/lb,min = 0.30$   
 $su2 = 0.4*esu2\_nominal ((5.5), TBDY) = 0.032$   
 From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,  
 For calculation of  $esu2\_nominal$  and  $y2, sh2,ft2,fy2$ , it is considered  
 characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.  
 $y1, sh1,ft1,fy1$ , are also multiplied by  $Min(1,1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.  
 with  $fs2 = (fs,jacket*Asl,com,jacket + fs,core*Asl,com,core)/Asl,com = 389.0139$   
 with  $Es2 = (Es,jacket*Asl,com,jacket + Es,core*Asl,com,core)/Asl,com = 200000.00$   
 $yv = 0.00140044$   
 $shv = 0.0044814$   
 $ftv = 466.8167$   
 $fyv = 389.0139$   
 $suv = 0.00512$   
 using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
 and also multiplied by the shear\_factor according to 15.7.1.4, with  
 Shear\_factor = 1.00  
 $lo/lou,min = lb/ld = 0.30$   
 $suv = 0.4*esuv\_nominal ((5.5), TBDY) = 0.032$   
 From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,  
 considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY  
 For calculation of  $esuv\_nominal$  and  $yv, shv,ftv,fyv$ , it is considered  
 characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.  
 $y1, sh1,ft1,fy1$ , are also multiplied by  $Min(1,1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.  
 with  $fsv = (fs,jacket*Asl,mid,jacket + fs,mid*Asl,mid,core)/Asl,mid = 389.0139$   
 with  $Es_v = (Es,jacket*Asl,mid,jacket + Es,mid*Asl,mid,core)/Asl,mid = 200000.00$   
 $1 = Asl,ten/(b*d)*(fs1/fc) = 0.02528302$   
 $2 = Asl,com/(b*d)*(fs2/fc) = 0.04909935$   
 $v = Asl,mid/(b*d)*(fsv/fc) = 0.04462942$   
 and confined core properties:  
 $b = 690.00$   
 $d = 677.00$   
 $d' = 13.00$   
 $fcc (5A.2, TBDY) = 34.43547$   
 $cc (5A.5, TBDY) = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$   
 $1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$   
 $2 = Asl,com/(b*d)*(fs2/fc) = 0.0557338$   
 $v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$   
 Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)  
 --->  
 $v < vs,y2$  - LHS eq.(4.5) is satisfied  
 --->  
 $su (4.9) = 0.1476063$

$$\begin{aligned} \mu &= MRC(4.14) = 4.9689E+008 \\ u &= su(4.1) = 8.4959181E-006 \end{aligned}$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_2$

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\begin{aligned} u &= 9.2452857E-006 \\ \mu &= 8.1540E+008 \end{aligned}$$

with full section properties:

$$\begin{aligned} b &= 400.00 \\ d &= 707.00 \\ d' &= 43.00 \\ v &= 0.00174378 \\ N &= 16273.607 \\ f_c &= 33.00 \\ c_o(5A.5, TBDY) &= 0.002 \\ \text{Final value of } \mu: \mu^* &= \text{shear\_factor} * \text{Max}(\mu_c, \mu_{cc}) = 0.01241186 \\ \text{The Shear\_factor is considered equal to 1 (pure moment strength)} \\ \text{From (5.4b), TBDY: } \mu_c &= 0.01241186 \\ \mu_{we}((5.4c), TBDY) &= a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383 \\ \text{where } f &= a_f * p_f * f_{fe}/f_{ce} \text{ is accounting for FRP contribution like EC8-part3 A.4.4.3(6)} \end{aligned}$$

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = NL * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se}((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$   
 $p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$   
 $p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su_1 = 0.4 * esu_{1,nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu_{1,nominal} = 0.08$ ,

For calculation of  $esu_{1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_1 = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$

with  $Es_1 = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$

$y_2 = 0.00140044$

$sh_2 = 0.0044814$

$ft_2 = 466.8167$

$fy_2 = 389.0139$

$su_2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{s_u2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_u2,nominal} = 0.08$ ,

For calculation of  $e_{s_u2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered characteristic value  $f_{s_y2} = f_{s_2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_2} = (f_{s,jacket} * A_{s_l,com,jacket} + f_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 389.0139$$

$$\text{with } E_{s_2} = (E_{s,jacket} * A_{s_l,com,jacket} + E_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{u_v} = 0.00512$$

using (30) in Bisikinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_d = 0.30$$

$$s_{u_v} = 0.4 * e_{s_{u_v},nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_{u_v},nominal} = 0.08$ ,

considering characteristic value  $f_{s_{u_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{s_{u_v},nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered characteristic value  $f_{s_{u_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_v} = (f_{s,jacket} * A_{s_l,mid,jacket} + f_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 389.0139$$

$$\text{with } E_{s_v} = (E_{s,jacket} * A_{s_l,mid,jacket} + E_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 200000.00$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.09206128$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.04740567$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.11310683$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.05824278$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < v_{s,y_2}$  - LHS eq.(4.5) is satisfied

---->

$$s_u (4.9) = 0.21669624$$

$$M_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----  
-----

-----  
Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$   
-----

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$

$$V_{r1} = V_{Co1} ((10.3), ASCE 41-17) = k_{nl} * V_{Co10}$$

$$V_{Co10} = 1.0898E+006$$

$$k_{nl} = 1 \text{ (zero step-static loading)}$$

-----  
NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$$= 1 \text{ (normal-weight concrete)}$$

$$\text{Mean concrete strength: } f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00, \text{ but } f_c'^{0.5} \leq 8.3$$

MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.777$$

$$V_u = 0.0001715$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } V_s = V_{s,jacket} + V_{s,core} = 901155.609$$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$$V_f \text{ ((11-3)-(11.4), ACI 440)} = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \alpha + \cos \alpha$  is replaced with  $(\cot \alpha + \cot \alpha) \sin \alpha$  which is more a generalised expression,

where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, \alpha_i)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha_1 = b_1 + 90^\circ = 90.00$

$$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|), \text{ with:}$$

total thickness per orientation,  $tf_1 = NL \cdot t / \text{NoDir} = 1.00$

$$df_v = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$ffe \text{ ((11-5), ACI 440)} = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$bw = 400.00$$

-----  
Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$$V_{r2} = V_{Col} \text{ ((10.3), ASCE 41-17)} = knl \cdot V_{Col0}$$

$$V_{Col0} = 1.0898E+006$$

$$knl = 1 \text{ (zero step-static loading)}$$

-----  
NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$$= 1 \text{ (normal-weight concrete)}$$

Mean concrete strength:  $f_c' = (f_c'_{\text{jacket}} \cdot \text{Area}_{\text{jacket}} + f_c'_{\text{core}} \cdot \text{Area}_{\text{core}}) / \text{Area}_{\text{section}} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.776$

$V_u = 0.0001715$

$d = 0.8 \cdot h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s\text{jacket}} + V_{s\text{core}} = 901155.609$

where:

$V_{s\text{jacket}} = V_{s\text{j1}} + V_{s\text{j2}} = 802857.879$

$V_{s\text{j1}} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s\text{j1}}$  is multiplied by  $\text{Col,j1} = 1.00$

$s/d = 0.3125$

$V_{s\text{j2}} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s\text{j2}}$  is multiplied by  $\text{Col,j2} = 1.00$

$s/d = 0.16666667$

$V_{s\text{core}} = V_{s\text{c1}} + V_{s\text{c2}} = 98297.73$

$V_{s\text{c1}} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s\text{c1}}$  is multiplied by  $\text{Col,c1} = 0.00$

$s/d = 1.5625$

$V_{s\text{c2}} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s\text{c2}}$  is multiplied by  $\text{Col,c2} = 1.00$

$s/d = 0.56818182$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression,

where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 45^\circ + 90^\circ = 135^\circ$

$V_f = \text{Min}(|V_f(45, 1)|, |V_f(-45, 1)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L \cdot t / N_{\text{Dir}} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 2

-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

Section Type: rcjcs

### Constant Properties

Knowledge Factor,  $k = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

### Stepwise Properties

Bending Moment,  $M = -320719.391$

Shear Force,  $V_2 = -4865.29$

Shear Force,  $V_3 = 131.62$

Axial Force,  $F = -18154.424$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{sl} = 0.00$

-Compression:  $A_{sl,c} = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $A_{sl,ten} = 1137.257$

-Compression:  $A_{sl,com} = 2208.54$

-Middle:  $A_{sl,mid} = 2007.478$

Longitudinal External Reinforcement Area Distribution (in 3 divisions)

-Tension:  $A_{sl,ten,jacket} = 829.3805$

-Compression:  $A_{sl,com,jacket} = 1746.726$

-Middle:  $A_{sl,mid,jacket} = 1545.664$

Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $A_{sl,ten,core} = 307.8761$

-Compression:  $A_{sl,com,core} = 461.8141$

-Middle:  $A_{sl,mid,core} = 461.8141$

Mean Diameter of Tension Reinforcement,  $Db_L = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u_{,R} = 1.0^* u = 0.00194945$   
 $u = y + p = 0.00194945$

- Calculation of  $y$  -

$y = (M_y * L_s / 3) / E_{eff} = 0.00194945$  ((4.29), Biskinis Phd))  
 $M_y = 3.6650E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 2436.707  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
 $factor = 0.30$   
 $A_g = 440000.00$   
Mean concrete strength:  $f'_c = (f'_{c\_jacket} * Area_{jacket} + f'_{c\_core} * Area_{core}) / Area_{section} = 33.00$   
 $N = 18154.424$   
 $E_c * I_g = E_{c\_jacket} * I_{g\_jacket} + E_{c\_core} * I_{g\_core} = 5.0901E+014$

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:  
flange width,  $b = 750.00$   
web width,  $b_w = 400.00$   
flange thickness,  $t = 400.00$

$y = \text{Min}(y_{ten}, y_{com})$   
 $y_{ten} = 2.7302957E-006$   
with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 * f_y * (l_b/d)^{2/3}) = 311.2112$   
 $d = 707.00$   
 $y = 0.19388674$   
 $A = 0.01020577$   
 $B = 0.00451618$   
with  $pt = 0.00729988$   
 $pc = 0.00416509$   
 $pv = 0.00378591$   
 $N = 18154.424$   
 $b = 750.00$   
 $" = 0.06082037$   
 $y_{comp} = 1.6519231E-005$   
with  $f'_c$  (12.3, (ACI 440)) = 33.60672  
 $f_c = 33.00$   
 $fl = 0.61848273$   
 $b = b_{max} = 750.00$   
 $h = h_{max} = 750.00$   
 $A_g = 0.44$   
 $g = pt + pc + pv = 0.01009575$   
 $rc = 40.00$   
 $A_e/A_c = 0.31291181$   
Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b1) = 1.00$   
effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$   
 $f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19183796$   
 $A = 0.01001935$   
 $B = 0.00440616$   
with  $E_s = 200000.00$   
CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

- Calculation of  $\rho$  -

From table 10-8:  $\rho = 0.00$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/l_d < 1$

shear control ratio  $V_{yE}/V_{CoIE} = 0.49879178$

$d = d_{\text{external}} = 707.00$

$s = s_{\text{external}} = 0.00$

-  $t = s_1 + s_2 + 2 \cdot t_f/bw \cdot (f_{fe}/f_s) = 0.00729988$

jacket:  $s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_1 = 100.00$

core:  $s_2 = A_{v2} \cdot L_{\text{stir2}} / (s_2 \cdot A_g) = 0.00067082$

$A_{v2} = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir2}} = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_2 = 250.00$

The term  $2 \cdot t_f/bw \cdot (f_{fe}/f_s)$  is implemented to account for FRP contribution

where  $f = 2 \cdot t_f/bw$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $f_{fe}/f_s$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $f_s$  of jacket is used.

$NUD = 18154.424$

$A_g = 440000.00$

$f_{cE} = (f_{c\_jacket} \cdot \text{Area}_{\text{jacket}} + f_{c\_core} \cdot \text{Area}_{\text{core}}) / \text{section\_area} = 33.00$

$f_{yIE} = (f_{y\_ext\_Long\_Reinf} \cdot \text{Area}_{\text{ext\_Long\_Reinf}} + f_{y\_int\_Long\_Reinf} \cdot \text{Area}_{\text{int\_Long\_Reinf}}) / \text{Area}_{\text{Tot\_Long\_Rein}} = 555.56$

$f_{yIE} = (f_{y\_ext\_Trans\_Reinf} \cdot s_1 + f_{y\_int\_Trans\_Reinf} \cdot s_2) / (s_1 + s_2) = 555.56$

$\rho = \text{Area}_{\text{Tot\_Long\_Rein}} / (b \cdot d) = 0.01009575$

$b = 750.00$

$d = 707.00$

$f_{cE} = 33.00$

End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

### Calculation No. 3

column C1, Floor 1


Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: Start

Local Axis: (3)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

Section Type: rcjlcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.

Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand, the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $NoDir = 1$   
Fiber orientations,  $bi = 0.00^\circ$   
Number of layers,  $NL = 1$   
Radius of rounding corners,  $R = 40.00$

Stepwise Properties

EDGE -A-  
Bending Moment,  $M_a = -320719.391$   
Shear Force,  $V_a = 131.62$   
EDGE -B-  
Bending Moment,  $M_b = -72292.074$   
Shear Force,  $V_b = -131.62$   
BOTH EDGES  
Axial Force,  $F = -18154.424$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{st} = 0.00$   
-Compression:  $A_{sc} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{st,ten} = 1137.257$   
-Compression:  $A_{st,com} = 2208.54$   
-Middle:  $A_{st,mid} = 2007.478$   
Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $V_R = 1.0 \cdot V_n = 948969.182$   
 $V_n$  (10.3), ASCE 41-17) =  $k_n \cdot V_{CoIO} = 948969.182$   
 $V_{CoI} = 948969.182$   
 $k_n = 1.00$   
displacement\_ductility\_demand = 0.01042165

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)  
Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f_c'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)  
 $M/Vd = 4.00$   
 $M_u = 320719.391$   
 $V_u = 131.62$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 18154.424$   
 $A_g = 300000.00$   
From (11.5.4.8), ACI 318-14:  $V_s = V_{sjacket} + V_{s,core} = 811033.559$   
where:  
 $V_{sjacket} = V_{sj1} + V_{sj2} = 722566.31$   
 $V_{sj1} = 471238.898$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 500.00$   
 $s = 100.00$

V<sub>s,j1</sub> is multiplied by Col<sub>j1</sub> = 1.00

$$s/d = 0.16666667$$

V<sub>s,j2</sub> = 251327.412 is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

V<sub>s,j2</sub> is multiplied by Col<sub>j2</sub> = 1.00

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$$

V<sub>s,c1</sub> = 88467.249 is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

V<sub>s,c1</sub> is multiplied by Col<sub>c1</sub> = 1.00

$$s/d = 0.56818182$$

V<sub>s,c2</sub> = 0.00 is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

V<sub>s,c2</sub> is multiplied by Col<sub>c2</sub> = 0.00

$$s/d = 1.5625$$

V<sub>f</sub> ((11-3)-(11.4), ACI 440) = 463792.00

$$f = 0.95, \text{ for fully-wrapped sections}$$

w<sub>f</sub>/s<sub>f</sub> = 1 (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression,

where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function V<sub>f</sub>( $\theta, \alpha$ ), is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b1 + 90^\circ = 90.00$

V<sub>f</sub> = Min(|V<sub>f</sub>(45,  $\theta$ )|, |V<sub>f</sub>(-45,  $\theta$ )|), with:

total thickness per orientation, t<sub>f1</sub> = NL\*t/NoDir = 1.00

d<sub>fV</sub> = d (figure 11.2, ACI 440) = 707.00

f<sub>fe</sub> ((11-5), ACI 440) = 328.00

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440: V<sub>s</sub> + V<sub>f</sub> <= 797164.595

$$b_w = 400.00$$

-----  
displacement\_ductility\_demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END A -

for rotation axis 2 and integ. section (a)

-----  
From analysis, chord rotation  $\theta = 2.0316540E-005$

$$y = (M_y * L_s / 3) / E_{eff} = 0.00194945 \text{ ((4.29), Biskinis Phd)}$$

$$M_y = 3.6650E+008$$

$$L_s = M/V \text{ (with } L_s > 0.1 * L \text{ and } L_s < 2 * L) = 2436.707$$

From table 10.5, ASCE 41\_17: E<sub>eff</sub> = factor \* E<sub>c</sub> \* I<sub>g</sub> = 1.5270E+014

$$\text{factor} = 0.30$$

$$A_g = 440000.00$$

$$\text{Mean concrete strength: } f'_c = (f'_{c\_jacket} * \text{Area}_{jacket} + f'_{c\_core} * \text{Area}_{core}) / \text{Area}_{section} = 33.00$$

$$N = 18154.424$$

$$E_c * I_g = E_{c\_jacket} * I_{g\_jacket} + E_{c\_core} * I_{g\_core} = 5.0901E+014$$

-----  
Calculation of Yielding Moment M<sub>y</sub>

-----  
Calculation of  $\delta / y$  and M<sub>y</sub> according to Annex 7 -

-----  
Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width, b = 750.00  
web width, bw = 400.00  
flange thickness, t = 400.00

-----  
y = Min( y\_ten, y\_com)  
y\_ten = 2.7302957E-006  
with ((10.1), ASCE 41-17) fy = Min(fy, 1.25\*fy\*(lb/d)^ 2/3) = 311.2112  
d = 707.00  
y = 0.19388674  
A = 0.01020577  
B = 0.00451618  
with pt = 0.00214476  
pc = 0.00416509  
pv = 0.00378591  
N = 18154.424  
b = 750.00  
" = 0.06082037  
y\_comp = 1.6519231E-005  
with fc\* (12.3, (ACI 440)) = 33.60672  
fc = 33.00  
fl = 0.61848273  
b = bmax = 750.00  
h = hmax = 750.00  
Ag = 0.44  
g = pt + pc + pv = 0.01009575  
rc = 40.00  
Ae/Ac = 0.31291181  
Effective FRP thickness, tf = NL\*t\*cos(b1) = 1.00  
effective strain from (12.5) and (12.12), efe = 0.004  
fu = 0.009  
Ef = 82000.00  
Ec = 26999.444  
y = 0.19183796  
A = 0.01001935  
B = 0.00440616  
with Es = 200000.00  
CONFIRMATION: y = 0.192811 < t/d

-----  
Calculation of ratio lb/d

-----  
Inadequate Lap Length with lb/d = 0.30

-----  
End Of Calculation of Shear Capacity for element: column JLC1 of floor 1  
At local axis: 3  
Integration Section: (a)

**Calculation No. 4**

column C1, Floor 1


Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity ( $\theta_u$ )

Edge: Start

Local Axis: (3)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $NoDir = 1$   
Fiber orientations,  $bi: 0.00^\circ$   
Number of layers,  $NL = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 3  
EDGE -A-  
Shear Force,  $V_a = -0.00017144$   
EDGE -B-  
Shear Force,  $V_b = 0.00017144$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{l,com} = 2208.54$   
-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(Mu_{1+}, Mu_{1-}) = 8.1540E+008$   
 $Mu_{1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $Mu_{1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(Mu_{2+}, Mu_{2-}) = 8.1540E+008$   
 $Mu_{2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $Mu_{2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $Mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $M_u = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$   
 $f_c = 33.00$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N_L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} ((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} (\text{Length of stirrups along } Y) = 2060.00$$

$$A_{stir1} (\text{stirrups area}) = 78.53982$$

$$p_{sh2} (5.4d) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} (\text{Length of stirrups along } Y) = 1468.00$$

$$\text{Astir2 (stirrups area)} = 50.26548$$

$$\text{psh}_y * \text{Fywe} = \text{psh}_1 * \text{Fywe}_1 + \text{ps}_2 * \text{Fywe}_2 = 3.0194$$

$$\text{psh}_1 ((5.4d), \text{TBDY}) = \text{Lstir}_1 * \text{Astir}_1 / (\text{Asec} * \text{s}_1) = 0.00367709$$

$$\text{Lstir}_1 (\text{Length of stirrups along X}) = 2060.00$$

$$\text{Astir}_1 (\text{stirrups area}) = 78.53982$$

$$\text{psh}_2 ((5.4d), \text{TBDY}) = \text{Lstir}_2 * \text{Astir}_2 / (\text{Asec} * \text{s}_2) = 0.00067082$$

$$\text{Lstir}_2 (\text{Length of stirrups along X}) = 1468.00$$

$$\text{Astir}_2 (\text{stirrups area}) = 50.26548$$

$$\text{Asec} = 440000.00$$

$$\text{s}_1 = 100.00$$

$$\text{s}_2 = 250.00$$

$$\text{fywe}_1 = 694.45$$

$$\text{fywe}_2 = 694.45$$

$$\text{fce} = 33.00$$

$$\text{From } ((5.A.5), \text{TBDY}), \text{TBDY: } \text{cc} = 0.00243499$$

$$\text{c} = \text{confinement factor} = 1.0435$$

$$\text{y}_1 = 0.00140044$$

$$\text{sh}_1 = 0.0044814$$

$$\text{ft}_1 = 466.8167$$

$$\text{fy}_1 = 389.0139$$

$$\text{su}_1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/ld} = 0.30$$

$$\text{su}_1 = 0.4 * \text{esu}_1 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_1 \text{ nominal} = 0.08,$$

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

$$\text{y}_1, \text{sh}_1, \text{ft}_1, \text{fy}_1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_1 = (\text{fs,jacket} * \text{Asl,ten,jacket} + \text{fs,core} * \text{Asl,ten,core}) / \text{Asl,ten} = 389.0139$$

$$\text{with } \text{Es}_1 = (\text{Es,jacket} * \text{Asl,ten,jacket} + \text{Es,core} * \text{Asl,ten,core}) / \text{Asl,ten} = 200000.00$$

$$\text{y}_2 = 0.00140044$$

$$\text{sh}_2 = 0.0044814$$

$$\text{ft}_2 = 466.8167$$

$$\text{fy}_2 = 389.0139$$

$$\text{su}_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/lb,min} = 0.30$$

$$\text{su}_2 = 0.4 * \text{esu}_2 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_2 \text{ nominal} = 0.08,$$

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

$$\text{y}_2, \text{sh}_2, \text{ft}_2, \text{fy}_2, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_2 = (\text{fs,jacket} * \text{Asl,com,jacket} + \text{fs,core} * \text{Asl,com,core}) / \text{Asl,com} = 389.0139$$

$$\text{with } \text{Es}_2 = (\text{Es,jacket} * \text{Asl,com,jacket} + \text{Es,core} * \text{Asl,com,core}) / \text{Asl,com} = 200000.00$$

$$\text{y}_v = 0.00140044$$

$$\text{sh}_v = 0.0044814$$

$$\text{ft}_v = 466.8167$$

$$\text{fy}_v = 389.0139$$

$$\text{suv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/ld} = 0.30$$

$$\text{suv} = 0.4 * \text{esuv}_v \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esuv}_v \text{ nominal} = 0.08,$$

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

$$\text{y}_v, \text{sh}_v, \text{ft}_v, \text{fy}_v, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_v = (\text{fs,jacket} * \text{Asl,mid,jacket} + \text{fs,mid} * \text{Asl,mid,core}) / \text{Asl,mid} = 389.0139$$

$$\text{with } \text{Es}_v = (\text{Es,jacket} * \text{Asl,mid,jacket} + \text{Es,mid} * \text{Asl,mid,core}) / \text{Asl,mid} = 200000.00$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02528302$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.04909935$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02869934$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.0557338$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$\mu_u = M R_c (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{u1}$ -

Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$\mu_u = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

From EC8 A4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_u,f = 840.00$   
 $E_f = 82000.00$   
 $u,f = 0.015$

$ase((5.4d), \text{TBDY}) = (ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), \text{TBDY}) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_d = 0.30$$

$$s_u1 = 0.4 * e_{su1,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su1,nominal} = 0.08$ ,

For calculation of  $e_{su1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered  
characteristic value  $f_{sy1} = f_{s1}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s1} = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$$

$$\text{with } E_{s1} = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s,com,jacket} + f_{s,core} * A_{s,com,core}) / A_{s,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s,com,jacket} + E_{s,core} * A_{s,com,core}) / A_{s,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{uv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s,mid,jacket} + f_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s,mid,jacket} + E_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 200000.00$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.09206128$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.04740567$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.11310683$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.05824278$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{2+}$

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 8.4959181E-006$$

$$\mu_{2+} = 4.9689E+008$$

with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$\nu = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,\min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length

equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}})/A_{\text{conf,max2}}) * (A_{\text{conf,min2}}/A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered

characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{s2} = (f_{s,jacket} \cdot A_{s,com,jacket} + f_{s,core} \cdot A_{s,com,core})/A_{s,com} = 389.0139$

with  $E_{s2} = (E_{s,jacket} \cdot A_{s,com,jacket} + E_{s,core} \cdot A_{s,com,core})/A_{s,com} = 200000.00$

$y_v = 0.00140044$

$sh_v = 0.0044814$

$ft_v = 466.8167$

$fy_v = 389.0139$

$s_{uv} = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$s_{uv} = 0.4 \cdot e_{suv,nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered

characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{sv} = (f_{s,jacket} \cdot A_{s,mid,jacket} + f_{s,mid} \cdot A_{s,mid,core})/A_{s,mid} = 389.0139$

with  $E_{sv} = (E_{s,jacket} \cdot A_{s,mid,jacket} + E_{s,mid} \cdot A_{s,mid,core})/A_{s,mid} = 200000.00$

$1 = A_{s,ten}/(b \cdot d) \cdot (f_{s1}/f_c) = 0.02528302$

$2 = A_{s,com}/(b \cdot d) \cdot (f_{s2}/f_c) = 0.04909935$

$v = A_{s,mid}/(b \cdot d) \cdot (f_{sv}/f_c) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$f_{cc} (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = A_{s,ten}/(b \cdot d) \cdot (f_{s1}/f_c) = 0.02869934$

$2 = A_{s,com}/(b \cdot d) \cdot (f_{s2}/f_c) = 0.05573338$

$v = A_{s,mid}/(b \cdot d) \cdot (f_{sv}/f_c) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$s_u (4.9) = 0.1476063$

$\mu_u = M_{Rc} (4.14) = 4.9689E+008$

$u = s_u (4.1) = 8.4959181E-006$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----  
-----

-----  
Calculation of  $\mu_{u2}$ -  
-----  
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$u = 9.2452857E-006$

$\mu_u = 8.1540E+008$

-----  
with full section properties:

$b = 400.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00174378$

$N = 16273.607$

$f_c = 33.00$

$cc (5A.5, TBDY) = 0.002$

Final value of  $\mu_u$ :  $\mu_u^* = \text{shear\_factor} \cdot \text{Max}(c_u, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $c_u = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$R = 40.00$

Effective FRP thickness,  $t_f = N_L * t * \text{Cos}(b_1) = 1.00$

$f_u, f = 840.00$

$E_f = 82000.00$

$u, f = 0.015$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$

$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

psh<sub>y</sub>\*Fywe = psh<sub>1</sub>\*Fywe<sub>1</sub>+ps<sub>2</sub>\*Fywe<sub>2</sub> = 3.0194  
psh<sub>1</sub> ((5.4d), TBDY) = Lstir<sub>1</sub>\*Astir<sub>1</sub>/(Asec\*s<sub>1</sub>) = 0.00367709  
Lstir<sub>1</sub> (Length of stirrups along X) = 2060.00  
Astir<sub>1</sub> (stirrups area) = 78.53982  
psh<sub>2</sub> ((5.4d), TBDY) = Lstir<sub>2</sub>\*Astir<sub>2</sub>/(Asec\*s<sub>2</sub>) = 0.00067082  
Lstir<sub>2</sub> (Length of stirrups along X) = 1468.00  
Astir<sub>2</sub> (stirrups area) = 50.26548

Asec = 440000.00

s<sub>1</sub> = 100.00

s<sub>2</sub> = 250.00

fywe<sub>1</sub> = 694.45

fywe<sub>2</sub> = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y<sub>1</sub> = 0.00140044

sh<sub>1</sub> = 0.0044814

ft<sub>1</sub> = 466.8167

fy<sub>1</sub> = 389.0139

su<sub>1</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su<sub>1</sub> = 0.4\*esu<sub>1\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>1\_nominal</sub> = 0.08,

For calculation of esu<sub>1\_nominal</sub> and y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, it is considered  
characteristic value fsy<sub>1</sub> = fs<sub>1</sub>/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>1</sub> = (fs<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + fs<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 389.0139

with Es<sub>1</sub> = (Es<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + Es<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 200000.00

y<sub>2</sub> = 0.00140044

sh<sub>2</sub> = 0.0044814

ft<sub>2</sub> = 466.8167

fy<sub>2</sub> = 389.0139

su<sub>2</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su<sub>2</sub> = 0.4\*esu<sub>2\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>2\_nominal</sub> = 0.08,

For calculation of esu<sub>2\_nominal</sub> and y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, it is considered  
characteristic value fsy<sub>2</sub> = fs<sub>2</sub>/1.2, from table 5.1, TBDY.

y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>2</sub> = (fs<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + fs<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 389.0139

with Es<sub>2</sub> = (Es<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + Es<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 200000.00

y<sub>v</sub> = 0.00140044

sh<sub>v</sub> = 0.0044814

ft<sub>v</sub> = 466.8167

fy<sub>v</sub> = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv = 0.4\*esuv<sub>nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv<sub>nominal</sub> = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv<sub>nominal</sub> and y<sub>v</sub>, sh<sub>v</sub>,ft<sub>v</sub>,fy<sub>v</sub>, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fsv = (fs<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + fs<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 389.0139

with Es<sub>v</sub> = (Es<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + Es<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 200000.00

1 = Asl<sub>ten</sub>/(b\*d)\*(fs<sub>1</sub>/fc) = 0.09206128

2 = Asl<sub>com</sub>/(b\*d)\*(fs<sub>2</sub>/fc) = 0.04740567

$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.08368017$   
 and confined core properties:  
 $b = 340.00$   
 $d = 677.00$   
 $d' = 13.00$   
 $f_{cc} (5A.2, TBDY) = 34.43547$   
 $cc (5A.5, TBDY) = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$   
 $1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.11310683$   
 $2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.05824278$   
 $v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.10280977$   
 Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)

--->  
 $v < v_{s,y2}$  - LHS eq.(4.5) is satisfied  
 --->  
 $su (4.9) = 0.21669624$   
 $Mu = MRc (4.14) = 8.1540E+008$   
 $u = su (4.1) = 9.2452857E-006$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$   
 $V_{r1} = V_{Col} ((10.3), ASCE 41-17) = k_{nl} * V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)  
 Mean concrete strength:  $f'_c = (f'_{c,jacket} * Area_{jacket} + f'_{c,core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$   
 $Mu = 1518.009$   
 $Vu = 0.00017144$   
 $d = 0.8 * h = 600.00$   
 $Nu = 16273.607$   
 $Ag = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:  
 $V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col,j1 = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col,j2 = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{sc1} + V_{sc2} = 98297.73$   
 $V_{sc1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\gamma_c = 1$  (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$

$V_{sj1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{sj2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

d = 440.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c1 is multiplied by Col,c1 = 1.00  
 s/d = 0.56818182  
 Vs,c2 = 0.00 is calculated for section flange core, with:  
 d = 160.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c2 is multiplied by Col,c2 = 0.00  
 s/d = 1.5625  
 Vf ((11-3)-(11.4), ACI 440) = 463792.00  
 f = 0.95, for fully-wrapped sections  
 wf/sf = 1 (FRP strips adjacent to one another).  
 In (11.3) sin + cos is replaced with (cot + cota)sina which is more a generalised expression,  
 where is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function Vf( , ), is implemented for every different fiber orientation ai,  
 as well as for 2 crack directions, = 45° and = -45° to take into consideration the cyclic seismic loading.  
 orientation 1: 1 = b1 + 90° = 90.00  
 Vf = Min(|Vf(45, 1)|, |Vf(-45,a1)|), with:  
 total thickness per orientation, tf1 = NL\*t/NoDir = 1.00  
 dfv = d (figure 11.2, ACI 440) = 707.00  
 ffe ((11-5), ACI 440) = 328.00  
 Ef = 82000.00  
 fe = 0.004, from (11.6a), ACI 440  
 with fu = 0.009  
 From (11-11), ACI 440: Vs + Vf <= 915872.391  
 bw = 400.00

-----  
 End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At local axis: 3

-----  
 Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At Shear local axis: 2  
 (Bending local axis: 3)  
 Section Type: rcjics

Constant Properties

-----  
 Knowledge Factor, = 0.87  
 Mean strength values are used for both shear and moment calculations.  
 Consequently:  
 Jacket  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 Existing Column  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 #####  
 Note: Especially for the calculation of moment strengths,  
 the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14  
 Jacket  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 Existing Column  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 #####  
 Max Height, Hmax = 750.00

Min Height, Hmin = 400.00  
Max Width, Wmax = 750.00  
Min Width, Wmin = 400.00  
Jacket Thickness, tj = 100.00  
Cover Thickness, c = 25.00  
Mean Confinement Factor overall section = 1.0435  
Element Length, L = 3000.00  
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness, t = 1.00  
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions, NoDir = 1  
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers, NL = 1  
Radius of rounding corners, R = 40.00

-----  
Stepwise Properties  
-----

At local axis: 2  
EDGE -A-  
Shear Force,  $V_a = -0.0001715$   
EDGE -B-  
Shear Force,  $V_b = 0.0001715$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{sl,t} = 0.00$   
-Compression:  $A_{sl,c} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{sl,ten} = 1137.257$   
-Compression:  $A_{sl,com} = 2208.54$   
-Middle:  $A_{sl,mid} = 2007.478$   
-----  
-----

Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(\mu_{u1+} , \mu_{u1-}) = 8.1540E+008$   
 $\mu_{u1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $\mu_{u1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(\mu_{u2+} , \mu_{u2-}) = 8.1540E+008$   
 $\mu_{u2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $\mu_{u2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{u1+}$   
-----  
-----

Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006  
Mu = 4.9689E+008

with full section properties:

b = 750.00  
d = 707.00  
d' = 43.00  
v = 0.00093001  
N = 16273.607  
fc = 33.00  
co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $ase * sh, \min * fy_{we} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = af * pf * ff_e / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_e = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_e = 765.1636$

R = 40.00

Effective FRP thickness,  $tf = NL * t * \text{Cos}(b1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$psh_{min} * Fy_{we} = \text{Min}(psh_x * Fy_{we}, psh_y * Fy_{we}) = 3.0194$$

Expression (5.4d) for  $psh_{min} * Fy_{we}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$psh_x * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along Y)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ (5.4d)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along Y)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$psh_y * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along X)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ ((5.4d), TBDY)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along X)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$Asec = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$fy_{we1} = 694.45$$

$$fy_{we2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/ld = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu1_{nominal} = 0.08,$$

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs1 = (fs_{jacket} * Asl_{ten,jacket} + fs_{core} * Asl_{ten,core}) / Asl_{ten} = 389.0139$$

$$\text{with } Es1 = (Es_{jacket} * Asl_{ten,jacket} + Es_{core} * Asl_{ten,core}) / Asl_{ten} = 200000.00$$

$$y2 = 0.00140044$$

$$sh2 = 0.0044814$$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/lb_{min} = 0.30$$

$$su2 = 0.4 * esu2_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu2_{nominal} = 0.08,$$

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs2 = (fs_{jacket} * Asl_{com,jacket} + fs_{core} * Asl_{com,core}) / Asl_{com} = 389.0139$$

$$\text{with } Es2 = (Es_{jacket} * Asl_{com,jacket} + Es_{core} * Asl_{com,core}) / Asl_{com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$su_v = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fsjacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05573338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

v < vs,y2 - LHS eq.(4.5) is satisfied

---->

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu1-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008  
-----

with full section properties:

b = 400.00

d = 707.00

d' = 43.00

v = 0.00174378

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} \cdot \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase \cdot sh_{\min} \cdot fy_{we}/f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af \cdot pf \cdot f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$fy = 0.03708128$   
Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$   
 $af = 0.31984848$   
with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$   
 $b_{max} = 750.00$   
 $h_{max} = 750.00$   
From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_{u,f} = 840.00$   
 $E_f = 82000.00$   
 $u_{,f} = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2$  ( $\geq ase1$ ) =  $\text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$psh_{,min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

$psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$   
 $s1 = 100.00$   
 $s2 = 250.00$

fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00  
d = 677.00  
d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->  
v < vs,y2 - LHS eq.(4.5) is satisfied  
--->  
su (4.9) = 0.21669624  
Mu = MRc (4.14) = 8.1540E+008  
u = su (4.1) = 9.2452857E-006

-----  
Calculation of ratio lb/l<sub>d</sub>

-----  
Inadequate Lap Length with lb/l<sub>d</sub> = 0.30  
-----  
-----

-----  
Calculation of Mu<sub>2+</sub>  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:  
u = 8.4959181E-006  
Mu = 4.9689E+008  
-----

with full section properties:

b = 750.00  
d = 707.00  
d' = 43.00  
v = 0.00093001  
N = 16273.607  
f<sub>c</sub> = 33.00  
co (5A.5, TBDY) = 0.002

Final value of cu: cu\* = shear\_factor \* Max( cu, cc) = 0.01241186

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY: cu = 0.01241186

we ((5.4c), TBDY) = ase\* sh,min\*fywe/fce+Min( fx, fy) = 0.0496383

where f = af\*pf\*ffe/fce is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
fx = 0.03708128

Expression ((15B.6), TBDY) is modified as af = 1 - (Unconfined area)/(total area)

af = 0.31984848

with Unconfined area = ((bmax-2R)^2 + (hmax-2R)^2)/3 = 140733.333

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6), pf = 2tf/bw = 0.005

bw = 400.00

effective stress from (A.35), ff,e = 765.1636

-----  
fy = 0.03708128

Expression ((15B.6), TBDY) is modified as af = 1 - (Unconfined area)/(total area)

af = 0.31984848

with Unconfined area = ((bmax-2R)^2 + (hmax-2R)^2)/3 = 140733.333

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6), pf = 2tf/bw = 0.005

bw = 400.00

effective stress from (A.35), ff,e = 765.1636

-----  
R = 40.00

Effective FRP thickness, tf = NL\*t\*Cos(b1) = 1.00

fu,f = 840.00

Ef = 82000.00

u,f = 0.015

ase ((5.4d), TBDY) = (ase1\*Aext+ ase2\*Aint)/Asec = 0.45746528

ase1 = Max(((Aconf,max1-AnoConf1)/Aconf,max1)\*(Aconf,min1/Aconf,max1),0) = 0.45746528

The definitions of AnoConf, Aconf,min and Aconf,max are derived from generalization  
of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{min} = lb/ld = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/lb,min = 0.30$$

$$su2 = 0.4*esu2\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs,jacket*Asl,com,jacket + fs,core*Asl,com,core)/Asl,com = 389.0139$$

$$\text{with } Es2 = (Es,jacket*Asl,com,jacket + Es,core*Asl,com,core)/Asl,com = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/ld = 0.30$$

$$suv = 0.4*esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs,jacket*Asl,mid,jacket + fs,mid*Asl,mid,core)/Asl,mid = 389.0139$$

$$\text{with } Esv = (Es,jacket*Asl,mid,jacket + Es,mid*Asl,mid,core)/Asl,mid = 200000.00$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02528302$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.04909935$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.0557338$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

---->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu2-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\omega_e ((5.4c), \text{TBDY}) = \alpha s_e * \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$\alpha_s_e ((5.4d), \text{TBDY}) = (\alpha_s e_1 * A_{\text{ext}} + \alpha_s e_2 * A_{\text{int}}) / A_{\text{sec}} = 0.45746528$$

$$\alpha_s e_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_s e_2 (> \alpha_s e_1) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}}) / A_{\text{conf,max2}}) * (A_{\text{conf,min2}} / A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max2}} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{\text{conf,min2}} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max2}}$  by a length equal to half the clear spacing between internal hoops.

$A_{\text{noConf2}} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,\min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,\min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without

earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv$ ,  $shv$ ,  $ftv$ ,  $fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1$ ,  $ft1$ ,  $fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs\_jacket * Asl\_mid\_jacket + fs\_mid * Asl\_mid\_core) / Asl\_mid = 389.0139$$

$$\text{with } Esv = (Es\_jacket * Asl\_mid\_jacket + Es\_mid * Asl\_mid\_core) / Asl\_mid = 200000.00$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.09206128$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.04740567$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.11310683$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.05824278$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $Vr = \text{Min}(Vr1, Vr2) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $Vr1 = 1.0898E+006$

$$Vr1 = VCol ((10.3), ASCE 41-17) = knl * VCol0$$

$$VCol0 = 1.0898E+006$$

$$knl = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $Vs = Av * fy * d / s$ ' is replaced by ' $Vs + f * Vf$ ' where  $Vf$  is the contribution of FRPs (11.3), ACI 440).

$$= 1 \text{ (normal-weight concrete)}$$

Mean concrete strength:  $fc' = (fc'_jacket * Area\_jacket + fc'_core * Area\_core) / Area\_section = 33.00$ , but  $fc'^{0.5} <= 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$Mu = 1518.777$$

$$Vu = 0.0001715$$

$$d = 0.8 * h = 600.00$$

$$Nu = 16273.607$$

$$Ag = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } Vs = Vs\_jacket + Vs\_core = 901155.609$$

where:

$$Vs\_jacket = Vs\_j1 + Vs\_j2 = 802857.879$$

$Vs\_j1 = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$Av = 157079.633$$

$$fy = 555.56$$

$$s = 100.00$$

$Vs\_j1$  is multiplied by  $Col\_j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$V_f((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a_i)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}((11-5), ACI 440) = 328.00$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}((10.3), ASCE 41-17) = knl \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\lambda = 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot \text{Area}_{jacket} + f_c'_{core} \cdot \text{Area}_{core}) / \text{Area}_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.776$$

$$V_u = 0.0001715$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b1 + 90^\circ = 90.00$

$$V_f = \text{Min}(|V_f(45, \alpha)|, |V_f(-45, \alpha)|), \text{ with:}$$

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$b_w = 400.00$$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 2  
-----

-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

Section Type: rcjlcs

Constant Properties  
-----

Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$   
Steel Elasticity,  $E_s = 200000.00$   
Max Height,  $H_{max} = 750.00$   
Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

#### Stepwise Properties

Bending Moment,  $M = -1.5106E+007$   
Shear Force,  $V_2 = -4865.29$   
Shear Force,  $V_3 = 131.62$   
Axial Force,  $F = -18154.424$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$   
Longitudinal External Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,jacket} = 829.3805$   
-Compression:  $As_{c,com,jacket} = 1746.726$   
-Middle:  $As_{c,mid,jacket} = 1545.664$   
Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,core} = 307.8761$   
-Compression:  $As_{c,com,core} = 461.8141$   
-Middle:  $As_{c,mid,core} = 461.8141$   
Mean Diameter of Tension Reinforcement,  $Db_L = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u_R = 1.0^*$   $u = 0.002484$   
 $u = y + p = 0.002484$

- Calculation of  $y$  -

$y = (M_y * L_s / 3) / E_{eff} = 0.002484$  ((4.29), Biskinis Phd))  
 $M_y = 3.6650E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 3104.858  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
factor = 0.30  
 $A_g = 440000.00$   
Mean concrete strength:  $fc' = (fc'_{jacket} * Area_{jacket} + fc'_{core} * Area_{core}) / Area_{section} = 33.00$

$$N = 18154.424$$

$$E_c \cdot I_g = E_c \cdot I_{g\_jacket} + E_c \cdot I_{g\_core} = 5.0901E+014$$

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$$

$$y_{\text{ten}} = 2.7302957E-006$$

$$\text{with } ((10.1), \text{ASCE 41-17}) f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$$

$$d = 707.00$$

$$y = 0.19388674$$

$$A = 0.01020577$$

$$B = 0.00451618$$

$$\text{with } p_t = 0.00729988$$

$$p_c = 0.00416509$$

$$p_v = 0.00378591$$

$$N = 18154.424$$

$$b = 750.00$$

$$" = 0.06082037$$

$$y_{\text{comp}} = 1.6519231E-005$$

$$\text{with } f_c^* (12.3, \text{ACI 440}) = 33.60672$$

$$f_c = 33.00$$

$$f_l = 0.61848273$$

$$b = b_{\text{max}} = 750.00$$

$$h = h_{\text{max}} = 750.00$$

$$A_g = 0.44$$

$$g = p_t + p_c + p_v = 0.01009575$$

$$r_c = 40.00$$

$$A_e/A_c = 0.31291181$$

$$\text{Effective FRP thickness, } t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$$

$$\text{effective strain from (12.5) and (12.12), } e_{fe} = 0.004$$

$$f_u = 0.009$$

$$E_f = 82000.00$$

$$E_c = 26999.444$$

$$y = 0.19183796$$

$$A = 0.01001935$$

$$B = 0.00440616$$

$$\text{with } E_s = 200000.00$$

CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

- Calculation of  $p$  -

From table 10-8:  $p = 0.00$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/d < 1$

$$\text{shear control ratio } V_y E / C_o I_{OE} = 0.49879178$$

$$d = d_{\text{external}} = 707.00$$

$$s = s_{\text{external}} = 0.00$$

$$- t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$$

$$\text{jacket: } s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s1 = 100.00$$

$$\text{core: } s2 = Av2 \cdot L_{\text{stir}2} / (s2 \cdot Ag) = 0.00067082$$

$Av2 = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir}2} = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s2 = 250.00$$

The term  $2 \cdot t_f / b_w \cdot (f_{fe} / f_s)$  is implemented to account for FRP contribution

where  $f = 2 \cdot t_f / b_w$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $f_{fe} / f_s$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $f_s$  of jacket is used.

$$NUD = 18154.424$$

$$Ag = 440000.00$$

$$f_{cE} = (f_{c\_jacket} \cdot Area\_jacket + f_{c\_core} \cdot Area\_core) / section\_area = 33.00$$

$$f_{yIE} = (f_{y\_ext\_Long\_Reinf} \cdot Area\_ext\_Long\_Reinf + f_{y\_int\_Long\_Reinf} \cdot Area\_int\_Long\_Reinf) / Area\_Tot\_Long\_Rein = 555.56$$

$$f_{yTE} = (f_{y\_ext\_Trans\_Reinf} \cdot s1 + f_{y\_int\_Trans\_Reinf} \cdot s2) / (s1 + s2) = 555.56$$

$$pI = Area\_Tot\_Long\_Rein / (b \cdot d) = 0.01009575$$

$$b = 750.00$$

$$d = 707.00$$

$$f_{cE} = 33.00$$

End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

## Calculation No. 5

column C1, Floor 1



Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity  $VRd$

Edge: End

Local Axis: (2)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2  
Integration Section: (b)  
Section Type: rcjls

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$   
Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.  
Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand,  
the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as  
Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{ou,min} = l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

EDGE -A-

Bending Moment,  $M_a = -1.5106E+007$

Shear Force,  $V_a = -4865.29$

EDGE -B-

Bending Moment,  $M_b = 505194.60$

Shear Force,  $V_b = 4865.29$

BOTH EDGES

Axial Force,  $F = -18154.424$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{t,ten} = 1137.257$

-Compression:  $As_{c,com} = 2208.54$

-Middle:  $As_{mid} = 2007.478$

Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $VR = 1.0 \cdot V_n = 1.1008E+006$

$V_n$  ((10.3), ASCE 41-17) =  $knI \cdot V_{CoIO} = 1.1008E+006$

$V_{CoI} = 1.1008E+006$

$knI = 1.00$

displacement\_ductility\_demand = 0.06608388

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 2.00$

$M_u = 505194.60$

$V_u = 4865.29$

$d = 0.8 \cdot h = 600.00$

$N_u = 18154.424$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$

$V_{s,j1} = 251327.412$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col_{j1} = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 471238.898$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col_{j2} = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col_{c1} = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 88467.249$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col_{c2} = 1.00$

$s/d = 0.56818182$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $\theta$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / N_{\text{Dir}} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 797164.595$

$b_w = 400.00$

displacement ductility demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END B -

for rotation axis 3 and integ. section (b)

From analysis, chord rotation  $\theta = 1.5860857E-005$

$y = (M_y \cdot L_s / 3) / E_{\text{eff}} = 0.00024001$  ((4.29), Biskinis Phd)

$M_y = 3.6650E+008$

$L_s = M/V$  (with  $L_s > 0.1 \cdot L$  and  $L_s < 2 \cdot L$ ) = 300.00

From table 10.5, ASCE 41\_17:  $E_{\text{eff}} = \text{factor} \cdot E_c \cdot I_g = 1.5270E+014$

factor = 0.30

$A_g = 440000.00$

Mean concrete strength:  $f'_c = (f'_{c, \text{jacket}} \cdot A_{\text{jacket}} + f'_{c, \text{core}} \cdot A_{\text{core}}) / A_{\text{section}} = 33.00$

$N = 18154.424$

$E_c \cdot I_g = E_{c, \text{jacket}} \cdot I_{g, \text{jacket}} + E_{c, \text{core}} \cdot I_{g, \text{core}} = 5.0901E+014$

Calculation of Yielding Moment  $M_y$

Calculation of  $\delta / y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7302957E-006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (I_b / I_d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19388674$

$A = 0.01020577$

$B = 0.00451618$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 18154.424$

$b = 750.00$

$\lambda = 0.06082037$

$y_{\text{comp}} = 1.6519231E-005$

with  $f'_c$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e / A_c = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b1) = 1.00$

effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$

$f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19183796$   
 $A = 0.01001935$   
 $B = 0.00440616$   
with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $I_b/I_d$

Inadequate Lap Length with  $I_b/I_d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

## Calculation No. 6

column C1, Floor 1



Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity (  $\theta$  )

Edge: End

Local Axis: (2)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

At local axis: 3

EDGE -A-

Shear Force,  $V_a = -0.00017144$

EDGE -B-

Shear Force,  $V_b = 0.00017144$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{l,ten} = 1137.257$

-Compression:  $As_{l,com} = 2208.54$

-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$

Member Controlled by Flexure ( $V_e/V_r < 1$ )

Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$

with  
 $M_{pr1} = \text{Max}(\mu_{1+}, \mu_{1-}) = 8.1540\text{E}+008$   
 $\mu_{1+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination

$\mu_{1-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination

$M_{pr2} = \text{Max}(\mu_{2+}, \mu_{2-}) = 8.1540\text{E}+008$

$\mu_{2+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination

$\mu_{2-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$\mu = 8.4959181\text{E}-006$

$M_u = 4.9689\text{E}+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $\mu$ :  $\mu^* = \text{shear\_factor} * \text{Max}(\mu_c, \mu_{cc}) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\mu_c = 0.01241186$

$\mu_{cc}$  ((5.4c), TBDY) =  $\alpha s_e * \text{sh}_{\min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha^* p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{fe} = 765.1636$   
-----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{fe} = 765.1636$   
-----

$R = 40.00$

Effective FRP thickness,  $t_f = N L^* t \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{f} = 0.015$

$\alpha_{se}$  ((5.4d), TBDY) =  $(\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int})/A_{sec} = 0.45746528$

$\alpha_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.  
 $A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$   
 $p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$   
 $p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$   
 $s_1 = 100.00$   
 $s_2 = 250.00$   
 $f_{ywe1} = 694.45$   
 $f_{ywe2} = 694.45$   
 $f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y_1 = 0.00140044$   
 $sh_1 = 0.0044814$   
 $ft_1 = 466.8167$   
 $fy_1 = 389.0139$   
 $su_1 = 0.00512$

using (30) in Bisquinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su_1 = 0.4 * esu_{1,nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu_{1,nominal} = 0.08$ ,

For calculation of  $esu_{1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_1 = (f_{s,jacket} * A_{sl,ten,jacket} + f_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es_1 = (E_{s,jacket} * A_{sl,ten,jacket} + E_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y_2 = 0.00140044$   
 $sh_2 = 0.0044814$   
 $ft_2 = 466.8167$

$$f_y2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2$ ,  $sh_2, ft_2, f_y2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1$ ,  $sh_1, ft_1, f_y1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s1,com,jacket} + f_{s,core} * A_{s1,com,core}) / A_{s1,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s1,com,jacket} + E_{s,core} * A_{s1,com,core}) / A_{s1,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$f_{tv} = 466.8167$$

$$f_{yv} = 389.0139$$

$$s_{uv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v$ ,  $sh_v, f_{tv}, f_{yv}$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1$ ,  $sh_1, ft_1, f_y1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s1,mid,jacket} + f_{s,mid} * A_{s1,mid,core}) / A_{s1,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s1,mid,jacket} + E_{s,mid} * A_{s1,mid,core}) / A_{s1,mid} = 200000.00$$

$$1 = A_{s1,ten} / (b * d) * (f_{s1} / f_c) = 0.02528302$$

$$2 = A_{s1,com} / (b * d) * (f_{s2} / f_c) = 0.04909935$$

$$v = A_{s1,mid} / (b * d) * (f_{sv} / f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s1,ten} / (b * d) * (f_{s1} / f_c) = 0.02869934$$

$$2 = A_{s1,com} / (b * d) * (f_{s2} / f_c) = 0.05573338$$

$$v = A_{s1,mid} / (b * d) * (f_{sv} / f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$M_u = M_{Rc} (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u1}$ -  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$M_u = 8.1540E+008$$
  
-----

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, TBDY) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e * \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$\alpha_s_e \text{ ((5.4d), TBDY) } = (\alpha_s e_1 * A_{\text{ext}} + \alpha_s e_2 * A_{\text{int}}) / A_{\text{sec}} = 0.45746528$$

$$\alpha_s e_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_s e_2 (> = \alpha_s e_1) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}}) / A_{\text{conf,max2}}) * (A_{\text{conf,min2}} / A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max2}} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{\text{conf,min2}} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max2}}$  by a length equal to half the clear spacing between internal hoops.

$A_{\text{noConf2}} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,\min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,\min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00  
s1 = 100.00  
s2 = 250.00  
fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,  
considering characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY  
For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} * A_{sl, mid, jacket} + fs_{mid} * A_{sl, mid, core}) / A_{sl, mid} = 389.0139$

with  $Esv = (Es_{jacket} * A_{sl, mid, jacket} + Es_{mid} * A_{sl, mid, core}) / A_{sl, mid} = 200000.00$

$1 = A_{sl, ten} / (b * d) * (fs1 / fc) = 0.09206128$

$2 = A_{sl, com} / (b * d) * (fs2 / fc) = 0.04740567$

$v = A_{sl, mid} / (b * d) * (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$fcc$  (5A.2, TBDY) = 34.43547

$cc$  (5A.5, TBDY) = 0.00243499

$c =$  confinement factor = 1.0435

$1 = A_{sl, ten} / (b * d) * (fs1 / fc) = 0.11310683$

$2 = A_{sl, com} / (b * d) * (fs2 / fc) = 0.05824278$

$v = A_{sl, mid} / (b * d) * (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

---->

$v < vs, y2$  - LHS eq.(4.5) is satisfied

---->

$su$  (4.9) = 0.21669624

$Mu = MRc$  (4.14) = 8.1540E+008

$u = su$  (4.1) = 9.2452857E-006

-----  
Calculation of ratio  $lb/ld$

-----  
Inadequate Lap Length with  $lb/ld = 0.30$   
-----  
-----

-----  
Calculation of  $Mu_{2+}$   
-----  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$

$Mu = 4.9689E+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$fc = 33.00$

$co$  (5A.5, TBDY) = 0.002

Final value of  $cu$ :  $cu^* = shear\_factor * Max(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

where  $we$  ((5.4c), TBDY) =  $ase * sh_{min} * fy_{we} / f_{ce} + Min(fx, fy) = 0.0496383$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $fx = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (Unconfined\ area) / (total\ area)$

$af = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_e = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = NL * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s_1 = 100.00$$

$$s_2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

From ((5.A.5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$su1 = 0.4 * esu1\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered  
characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs,jacket * Asl,ten,jacket + fs,core * Asl,ten,core) / Asl,ten = 389.0139$

with  $Es1 = (Es,jacket * Asl,ten,jacket + Es,core * Asl,ten,core) / Asl,ten = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/lb,min = 0.30$

$su2 = 0.4 * esu2\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered  
characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs,jacket * Asl,com,jacket + fs,core * Asl,com,core) / Asl,com = 389.0139$

with  $Es2 = (Es,jacket * Asl,com,jacket + Es,core * Asl,com,core) / Asl,com = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs,jacket * Asl,mid,jacket + fs,mid * Asl,mid,core) / Asl,mid = 389.0139$

with  $Es_v = (Es,jacket * Asl,mid,jacket + Es,mid * Asl,mid,core) / Asl,mid = 200000.00$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02528302$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.04909935$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$fcc (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02869934$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.0557338$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u(4.9) = 0.1476063$$

$$M_u = M_{Rc}(4.14) = 4.9689E+008$$

$$u = s_u(4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u2}$   
-----  
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$M_u = 8.1540E+008$$

-----  
with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha(5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \phi_u: \phi_u^* = \text{shear\_factor} * \text{Max}(\phi_u, \phi_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \phi_u = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e \cdot \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$\text{ase ((5.4d), TBDY) } = (\text{ase}_1 * A_{\text{ext}} + \text{ase}_2 * A_{\text{int}}) / A_{\text{sec}} = 0.45746528$$

$$\text{ase}_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max1 = 353600.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

Aconf,min1 = 293525.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max1 by a length equal to half the clear spacing between external hoops.

AnoConf1 = 158733.333 is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
ase2 ( $\geq$  ase1) =  $\text{Max}(((Aconf,max2 - AnoConf2)/Aconf,max2) * (Aconf,min2/Aconf,max2), 0) = 0.45746528$

The definitions of AnoConf, Aconf,min and Aconf,max are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max2 = 171264.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

Aconf,min2 = 54741.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max2 by a length equal to half the clear spacing between internal hoops.

AnoConf2 = 106242.667 is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
psh,min\*Fywe =  $\text{Min}(psh,x*Fywe, psh,y*Fywe) = 3.0194$

Expression (5.4d) for psh,min\*Fywe has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
psh\_x\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194

psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along Y) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 (5.4d) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along Y) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
psh\_y\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194

psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along X) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 ((5.4d), TBDY) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along X) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 =  $0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1, ft1, fy1, it is considered characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1, ft1, fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs\_jacket * Asl\_ten\_jacket + fs\_core * Asl\_ten\_core) / Asl\_ten = 389.0139$

with Es1 =  $(Es\_jacket * Asl\_ten\_jacket + Es\_core * Asl\_ten\_core) / Asl\_ten = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{s_u2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_u2,nominal} = 0.08$ ,

For calculation of  $e_{s_u2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{s_y2} = f_{s_2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_2} = (f_{s,jacket} * A_{s_l,com,jacket} + f_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 389.0139$$

$$\text{with } E_{s_2} = (E_{s,jacket} * A_{s_l,com,jacket} + E_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{u_v} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_d = 0.30$$

$$s_{u_v} = 0.4 * e_{s_{u_v},nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_{u_v},nominal} = 0.08$ ,

considering characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{s_{u_v},nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_v} = (f_{s,jacket} * A_{s_l,mid,jacket} + f_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 389.0139$$

$$\text{with } E_{s_v} = (E_{s,jacket} * A_{s_l,mid,jacket} + E_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 200000.00$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.09206128$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.04740567$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.11310683$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.05824278$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->

$v < v_{s,y_2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$

$$V_{r1} = V_{Co1} ((10.3), ASCE 41-17) = k_{nl} * V_{Co10}$$

$$V_{Co10} = 1.0898E+006$$

$$k_{nl} = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$   
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)  
 Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)  
 $M/Vd = 4.00$   
 $\mu_u = 1518.009$   
 $V_u = 0.00017144$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 16273.607$   
 $A_g = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{sjacket} + V_{s,core} = 901155.609$   
 where:  
 $V_{sjacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col_{j1} = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col_{j2} = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$   
 $V_{s,c1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c1}$  is multiplied by  $Col_{c1} = 1.00$   
 $s/d = 0.56818182$   
 $V_{s,c2} = 0.00$  is calculated for section flange core, with:  
 $d = 160.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c2}$  is multiplied by  $Col_{c2} = 0.00$   
 $s/d = 1.5625$   
 $V_f$  ((11-3)-(11.4), ACI 440) = 463792.00  
 $f = 0.95$ , for fully-wrapped sections  
 $w_f/s_f = 1$  (FRP strips adjacent to one another).  
 In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \cot \alpha) \sin \alpha$  which is more a generalised expression,  
 where  $\theta$  is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ ,  
 as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.  
 orientation 1:  $\theta = b_1 + 90^\circ = 90.00$   
 $V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:  
 total thickness per orientation,  $t_{f1} = NL \cdot t / NoDir = 1.00$   
 $d_{fv} = d$  (figure 11.2, ACI 440) = 707.00  
 $f_{fe}$  ((11-5), ACI 440) = 328.00  
 $E_f = 82000.00$   
 $f_e = 0.004$ , from (11.6a), ACI 440  
 with  $f_u = 0.009$   
 From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $b_w = 400.00$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$   
 $V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '

where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.009$

$V_u = 0.00017144$

$d = 0.8 \cdot h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 523602.964$  is calculated for section web jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.16666667$

$V_{s,j2} = 279254.914$  is calculated for section flange jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.3125$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$s/d = 0.56818182$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$s/d = 1.5625$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \csc) \sin \alpha$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, \theta)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 45^\circ + 90^\circ = 135^\circ$

$V_f = \text{Min}(|V_f(45, 135)|, |V_f(-45, 135)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / NoDir = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 3

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 2

(Bending local axis: 3)

Section Type: rcjcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

Stepwise Properties

At local axis: 2

EDGE -A-

Shear Force,  $V_a = -0.0001715$

EDGE -B-

Shear Force,  $V_b = 0.0001715$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $As_{lc} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{l,ten} = 1137.257$   
-Compression:  $As_{l,com} = 2208.54$   
-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with

$M_{pr1} = \text{Max}(Mu_{1+} , Mu_{1-}) = 8.1540E+008$   
 $Mu_{1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination  
 $Mu_{1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(Mu_{2+} , Mu_{2-}) = 8.1540E+008$   
 $Mu_{2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination  
 $Mu_{2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $Mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $Mu = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$

$f_c = 33.00$

$\phi_c$  (5A.5, TBDY) = 0.002

Final value of  $\phi_u$ :  $\phi_u^* = \text{shear\_factor} * \text{Max}(\phi_u, \phi_c) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\phi_u = 0.01241186$

$\phi_{we}$  ((5.4c), TBDY) =  $\phi_u * \text{sh}_{min} * f_{ywe}/f_{ce} + \text{Min}(\phi_x, \phi_y) = 0.0496383$

where  $\phi = \phi_f * \phi_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $\phi_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\phi_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\phi_f = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $\phi_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

-----  
 $\phi_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\phi_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\phi_f = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $\phi_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

R = 40.00

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_f = 0.015$

$ase((5.4d), TBDY) = (ase_1 \cdot A_{ext} + ase_2 \cdot A_{int}) / A_{sec} = 0.45746528$

$ase_1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) \cdot (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) \cdot (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} \cdot F_{ywe} = \text{Min}(p_{sh,x} \cdot F_{ywe}, p_{sh,y} \cdot F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} \cdot F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} \cdot F_{ywe} = p_{sh1} \cdot F_{ywe1} + p_{sh2} \cdot F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), TBDY) = L_{stir1} \cdot A_{stir1} / (A_{sec} \cdot s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} \cdot A_{stir2} / (A_{sec} \cdot s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} \cdot F_{ywe} = p_{sh1} \cdot F_{ywe1} + p_{sh2} \cdot F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), TBDY) = L_{stir1} \cdot A_{stir1} / (A_{sec} \cdot s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), TBDY) = L_{stir2} \cdot A_{stir2} / (A_{sec} \cdot s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c$  = confinement factor = 1.0435

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o / l_{ou,min} = l_b / d = 0.30$

$$su_1 = 0.4 * esu_{1\_nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu_{1\_nominal} = 0.08$ ,

For calculation of  $esu_{1\_nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs_1 = (fs_{jacket} * A_{sl,ten,jacket} + fs_{core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$$

$$\text{with } Es_1 = (Es_{jacket} * A_{sl,ten,jacket} + Es_{core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$su_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou, \text{min} = lb/lb, \text{min} = 0.30$$

$$su_2 = 0.4 * esu_{2\_nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu_{2\_nominal} = 0.08$ ,

For calculation of  $esu_{2\_nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered characteristic value  $fsy_2 = fs_2/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs_2 = (fs_{jacket} * A_{sl,com,jacket} + fs_{core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$$

$$\text{with } Es_2 = (Es_{jacket} * A_{sl,com,jacket} + Es_{core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou, \text{min} = lb/ld = 0.30$$

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsy_v = fsv/1.2$ , from table 5.1, TBDY  
For calculation of  $esuv\_nominal$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered characteristic value  $fsy_v = fsv/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs_{jacket} * A_{sl,mid,jacket} + fs_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$$

$$\text{with } Es_v = (Es_{jacket} * A_{sl,mid,jacket} + Es_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$$

$$1 = A_{sl,ten} / (b * d) * (fs_1 / fc) = 0.02528302$$

$$2 = A_{sl,com} / (b * d) * (fs_2 / fc) = 0.04909935$$

$$v = A_{sl,mid} / (b * d) * (fsv / fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten} / (b * d) * (fs_1 / fc) = 0.02869934$$

$$2 = A_{sl,com} / (b * d) * (fs_2 / fc) = 0.0557338$$

$$v = A_{sl,mid} / (b * d) * (fsv / fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Mu1-

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_s,jacket * A_{sl,ten,jacket} + f_s,core * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es1 = (E_s,jacket * A_{sl,ten,jacket} + E_s,core * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (f_s,jacket * A_{sl,com,jacket} + f_s,core * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with  $Es2 = (E_s,jacket * A_{sl,com,jacket} + E_s,core * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

su (4.9) = 0.21669624

Mu = MRc (4.14) = 8.1540E+008

u = su (4.1) = 9.2452857E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu2+  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006

Mu = 4.9689E+008  
-----

with full section properties:

b = 750.00

d = 707.00

d' = 43.00

v = 0.00093001

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu: cu\* = shear\_factor \* Max( cu, cc) = 0.01241186

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY: cu = 0.01241186

we ((5.4c), TBDY) = ase\* sh,min\*fywe/fce+ Min( fx, fy) = 0.0496383

where f = af\*pf\*ffe/fce is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = N_L * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length

equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (\geq a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length

equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

psh2 ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 =  $0.4 * esu1_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs_{jacket} * A_{sl,ten,jacket} + fs_{core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with Es1 =  $(Es_{jacket} * A_{sl,ten,jacket} + Es_{core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 =  $0.4 * esu2_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 =  $(fs_{jacket} * A_{sl,com,jacket} + fs_{core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with Es2 =  $(Es_{jacket} * A_{sl,com,jacket} + Es_{core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv =  $0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY  
For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv =  $(fs_{jacket} * A_{sl,mid,jacket} + fs_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$

with Esv =  $(Es_{jacket} * A_{sl,mid,jacket} + Es_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$

1 =  $A_{sl,ten} / (b * d) * (fs1 / fc) = 0.02528302$

2 =  $A_{sl,com} / (b * d) * (fs2 / fc) = 0.04909935$

v =  $A_{sl,mid} / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

b = 690.00

d = 677.00

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = \text{Asl,ten}/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = \text{Asl,com}/(b*d)*(fs2/fc) = 0.0557338$$

$$v = \text{Asl,mid}/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $Mu_2$ -

Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$fc = 33.00$$

$$co (5A.5, TBDY) = 0.002$$

$$\text{Final value of } cu: cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } cu = 0.01241186$$

$$w_e ((5.4c), TBDY) = ase * sh_{min} * fy_w / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff_e = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff_e = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } tf = NL * t * \text{Cos}(b1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$ase \text{ ((5.4d), TBDY)} = (ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$$

$$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$ase2 \text{ (>=ase1)} = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } c_c = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$l_o / l_{ou,min} = l_b / d = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $es1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs_{jacket} \cdot Asl_{ten,jacket} + fs_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 389.0139$

with  $Es1 = (Es_{jacket} \cdot Asl_{ten,jacket} + Es_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$lo/lo_{min} = lb/lb_{min} = 0.30$

$su2 = 0.4 \cdot esu2_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs_{jacket} \cdot Asl_{com,jacket} + fs_{core} \cdot Asl_{com,core}) / Asl_{com} = 389.0139$

with  $Es2 = (Es_{jacket} \cdot Asl_{com,jacket} + Es_{core} \cdot Asl_{com,core}) / Asl_{com} = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$lo/lo_{min} = lb/ld = 0.30$

$suv = 0.4 \cdot esuv_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esuv_{nominal} = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv_{nominal}$  and  $yv, shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} \cdot Asl_{mid,jacket} + fs_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 389.0139$

with  $Es_v = (Es_{jacket} \cdot Asl_{mid,jacket} + Es_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 200000.00$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.09206128$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.04740567$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$fcc (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c =$  confinement factor  $= 1.0435$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.11310683$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.05824278$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs_{y2}$  - LHS eq.(4.5) is satisfied

--->

$su (4.9) = 0.21669624$

$Mu = MRc (4.14) = 8.1540E+008$

$u = su (4.1) = 9.2452857E-006$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898\text{E}+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898\text{E}+006$

$V_{r1} = V_{Co1} \text{ ((10.3), ASCE 41-17)} = k_{nl} * V_{Co10}$

$V_{Co10} = 1.0898\text{E}+006$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ '

where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{\text{jacket}} * \text{Area}_{\text{jacket}} + f_c'_{\text{core}} * \text{Area}_{\text{core}}) / \text{Area}_{\text{section}} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.777$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,\text{jacket}} + V_{s,\text{core}} = 901155.609$

where:

$V_{s,\text{jacket}} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $\text{Col},j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $\text{Col},j2 = 1.00$

$s/d = 0.16666667$

$V_{s,\text{core}} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $\text{Col},c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $\text{Col},c2 = 1.00$

$s/d = 0.56818182$

$V_f \text{ ((11-3)-(11.4), ACI 440)} = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression,

where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 1 = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \alpha)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L * t / N_{oDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $bw = 400.00$

Calculation of Shear Strength at edge 2,  $V_r2 = 1.0898E+006$   
 $V_r2 = V_{Col} ((10.3), ASCE 41-17) = knl * V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)  
Mean concrete strength:  $f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)

$M / Vd = 4.00$

$\mu_u = 1518.776$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$s/d = 0.56818182$

$V_f ((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f / s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression,  
where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a)$ , is implemented for every different fiber orientation  $a_i$ ,  
as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} ((11-5), ACI 440) = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

-----  
-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
At local axis: 2

-----  
-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

Section Type: rcjcs

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
-----  
Stepwise Properties

Bending Moment,  $M = -72292.074$

Shear Force,  $V_2 = 4865.29$

Shear Force,  $V_3 = -131.62$

Axial Force,  $F = -18154.424$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $A_{sc} = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten = 1137.257$

-Compression:  $Asl,com = 2208.54$

-Middle:  $Asl,mid = 2007.478$

Longitudinal External Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,jacket = 829.3805$

-Compression:  $Asl,com,jacket = 1746.726$

-Middle:  $Asl,mid,jacket = 1545.664$

Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,core = 307.8761$

-Compression:  $Asl,com,core = 461.8141$

-Middle:  $Asl,mid,core = 461.8141$

Mean Diameter of Tension Reinforcement,  $DbL = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u,R = 1.0^*$   $u = 0.00043942$

$u = y + p = 0.00043942$

- Calculation of  $y$  -

$y = (My*Ls/3)/Eleff = 0.00043942$  ((4.29),Biskinis Phd))

$My = 3.6650E+008$

$Ls = M/V$  (with  $Ls > 0.1*L$  and  $Ls < 2*L$ ) = 549.2484

From table 10.5, ASCE 41\_17:  $Eleff = factor*Ec*Ig = 1.5270E+014$

factor = 0.30

$Ag = 440000.00$

Mean concrete strength:  $fc' = (fc'_jacket*Area_jacket + fc'_core*Area_core)/Area_section = 33.00$

$N = 18154.424$

$Ec*Ig = Ec_jacket*Ig_jacket + Ec_core*Ig_core = 5.0901E+014$

Calculation of Yielding Moment  $My$

Calculation of  $y$  and  $My$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $bw = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{ten}, y_{com})$

$y_{ten} = 2.7302957E-006$

with ((10.1), ASCE 41-17)  $fy = \text{Min}(fy, 1.25*fy*(b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19388674$

$A = 0.01020577$

$B = 0.00451618$

with  $pt = 0.00729988$

$pc = 0.00416509$

$pv = 0.00378591$

$N = 18154.424$

$b = 750.00$

" = 0.06082037

$y_{comp} = 1.6519231E-005$

with  $fc^*$  (12.3, (ACI 440)) = 33.60672

$fc = 33.00$

$fl = 0.61848273$

$b = b_{max} = 750.00$

$h = h_{max} = 750.00$

$Ag = 0.44$

$g = pt + pc + pv = 0.01009575$

$rc = 40.00$

$Ae/Ac = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b_1) = 1.00$   
effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$   
 $f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19183796$   
 $A = 0.01001935$   
 $B = 0.00440616$   
with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.192811 < t/d$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$

-----  
- Calculation of  $\rho$  -

-----  
From table 10-8:  $\rho = 0.00$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/l_d < 1$

shear control ratio  $V_y E / V_{CoI} E = 0.49879178$

$d = d_{external} = 707.00$

$s = s_{external} = 0.00$

-  $t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$

jacket:  $s_1 = A_{v1} \cdot L_{stir1} / (s_1 \cdot A_g) = 0.00367709$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{stir1} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_1 = 100.00$

core:  $s_2 = A_{v2} \cdot L_{stir2} / (s_2 \cdot A_g) = 0.00067082$

$A_{v2} = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$L_{stir2} = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_2 = 250.00$

The term  $2 \cdot t_f / b_w \cdot (f_{fe} / f_s)$  is implemented to account for FRP contribution

where  $f = 2 \cdot t_f / b_w$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $f_{fe} / f_s$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $f_s$  of jacket is used.

$N_{UD} = 18154.424$

$A_g = 440000.00$

$f_{cE} = (f_{c,jacket} \cdot Area_{jacket} + f_{c,core} \cdot Area_{core}) / section\_area = 33.00$

$f_{yIE} = (f_{y,ext\_Long\_Reinf} \cdot Area_{ext\_Long\_Reinf} + f_{y,int\_Long\_Reinf} \cdot Area_{int\_Long\_Reinf}) / Area_{Tot\_Long\_Rein} =$

555.56

$f_{ytE} = (f_{y,ext\_Trans\_Reinf} \cdot s_1 + f_{y,int\_Trans\_Reinf} \cdot s_2) / (s_1 + s_2) = 555.56$

$\rho_l = Area_{Tot\_Long\_Rein} / (b \cdot d) = 0.01009575$

$b = 750.00$

$d = 707.00$

$f_{cE} = 33.00$

-----  
End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

## Calculation No. 7

column C1, Floor 1


Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: End

Local Axis: (3)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.

Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand, the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height, Hmax = 750.00  
Min Height, Hmin = 400.00  
Max Width, Wmax = 750.00  
Min Width, Wmin = 400.00  
Jacket Thickness, tj = 100.00  
Cover Thickness, c = 25.00  
Element Length, L = 3000.00  
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness, t = 1.00  
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions, NoDir = 1  
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers, NL = 1  
Radius of rounding corners, R = 40.00

-----  
Stepwise Properties  
-----

EDGE -A-  
Bending Moment,  $M_a = -320719.391$   
Shear Force,  $V_a = 131.62$   
EDGE -B-  
Bending Moment,  $M_b = -72292.074$   
Shear Force,  $V_b = -131.62$   
BOTH EDGES  
Axial Force,  $F = -18154.424$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{sl,t} = 0.00$   
-Compression:  $A_{sl,c} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{sl,ten} = 1137.257$   
-Compression:  $A_{sl,com} = 2208.54$   
-Middle:  $A_{sl,mid} = 2007.478$   
Mean Diameter of Tension Reinforcement,  $D_{bL,ten} = 16.80$

-----  
New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $V_R = 1.0 \cdot V_n = 1.1008E+006$   
 $V_n$  ((10.3), ASCE 41-17) =  $k_n \cdot V_{CoI} = 1.1008E+006$   
 $V_{CoI} = 1.1008E+006$   
 $k_n = 1.00$   
 $displacement\_ductility\_demand = 1.9512578E-005$

-----  
NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

-----  
= 1 (normal-weight concrete)  
Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f'_c^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)  
 $M/d = 2.00$   
 $M_u = 72292.074$   
 $V_u = 131.62$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 18154.424$   
 $A_g = 300000.00$   
From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$$

$V_{s,j1} = 471238.898$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{s,j2} = 251327.412$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$$

$V_{s,c1} = 88467.249$  is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression,

where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a_1)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

$$\text{orientation 1: } \alpha = b1 + 90^\circ = 90.00$$

$$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|), \text{ with:}$$

$$\text{total thickness per orientation, } t_{f1} = NL * t / \text{NoDir} = 1.00$$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe}((11-5), ACI 440) = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 797164.595$$

$$b_w = 400.00$$

-----  
displacement ductility demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END B -

for rotation axis 2 and integ. section (b)

-----  
From analysis, chord rotation  $\theta = 8.5741943E-009$

$$y = (M_y * L_s / 3) / E_{eff} = 0.00043942 \text{ ((4.29), Biskinis Phd)}$$

$$M_y = 3.6650E+008$$

$$L_s = M/V \text{ (with } L_s > 0.1 * L \text{ and } L_s < 2 * L) = 549.2484$$

$$\text{From table 10.5, ASCE 41_17: } E_{eff} = \text{factor} * E_c * I_g = 1.5270E+014$$

$$\text{factor} = 0.30$$

$$A_g = 440000.00$$

$$\text{Mean concrete strength: } f_c' = (f_c'_{jacket} * \text{Area}_{jacket} + f_c'_{core} * \text{Area}_{core}) / \text{Area}_{section} = 33.00$$

$$N = 18154.424$$

$$E_c * I_g = E_c_{jacket} * I_{g,jacket} + E_c_{core} * I_{g,core} = 5.0901E+014$$
  
-----

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7302957E-006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19388674$

$A = 0.01020577$

$B = 0.00451618$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 18154.424$

$b = 750.00$

" = 0.06082037

$y_{\text{comp}} = 1.6519231E-005$

with  $f_c^*$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e/A_c = 0.31291181$

Effective FRP thickness,  $t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$

effective strain from (12.5) and (12.12),  $e_{fe} = 0.004$

$f_u = 0.009$

$E_f = 82000.00$

$E_c = 26999.444$

$y = 0.19183796$

$A = 0.01001935$

$B = 0.00440616$

with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

**Calculation No. 8**

column C1, Floor 1


Limit State: Immediate Occupancy (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity ( $\theta_u$ )

Edge: End

Local Axis: (3)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{ou,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $NoDir = 1$   
Fiber orientations,  $bi: 0.00^\circ$   
Number of layers,  $NL = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 3  
EDGE -A-  
Shear Force,  $V_a = -0.00017144$   
EDGE -B-  
Shear Force,  $V_b = 0.00017144$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{l,com} = 2208.54$   
-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(Mu_{1+} , Mu_{1-}) = 8.1540E+008$   
 $Mu_{1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $Mu_{1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(Mu_{2+} , Mu_{2-}) = 8.1540E+008$   
 $Mu_{2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $Mu_{2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $Mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $M_u = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$   
 $f_c = 33.00$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N_L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} ((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} (\text{Length of stirrups along } Y) = 2060.00$$

$$A_{stir1} (\text{stirrups area}) = 78.53982$$

$$p_{sh2} (5.4d) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} (\text{Length of stirrups along } Y) = 1468.00$$

$$\text{Astir2 (stirrups area)} = 50.26548$$

$$\text{psh}_y * \text{Fywe} = \text{psh}_1 * \text{Fywe}_1 + \text{ps}_2 * \text{Fywe}_2 = 3.0194$$

$$\text{psh}_1 ((5.4d), \text{TBDY}) = \text{Lstir}_1 * \text{Astir}_1 / (\text{Asec} * \text{s}_1) = 0.00367709$$

$$\text{Lstir}_1 (\text{Length of stirrups along X}) = 2060.00$$

$$\text{Astir}_1 (\text{stirrups area}) = 78.53982$$

$$\text{psh}_2 ((5.4d), \text{TBDY}) = \text{Lstir}_2 * \text{Astir}_2 / (\text{Asec} * \text{s}_2) = 0.00067082$$

$$\text{Lstir}_2 (\text{Length of stirrups along X}) = 1468.00$$

$$\text{Astir}_2 (\text{stirrups area}) = 50.26548$$

$$\text{Asec} = 440000.00$$

$$\text{s}_1 = 100.00$$

$$\text{s}_2 = 250.00$$

$$\text{fywe}_1 = 694.45$$

$$\text{fywe}_2 = 694.45$$

$$\text{fce} = 33.00$$

$$\text{From } ((5.A.5), \text{TBDY}), \text{TBDY: } \text{cc} = 0.00243499$$

$$\text{c} = \text{confinement factor} = 1.0435$$

$$\text{y}_1 = 0.00140044$$

$$\text{sh}_1 = 0.0044814$$

$$\text{ft}_1 = 466.8167$$

$$\text{fy}_1 = 389.0139$$

$$\text{su}_1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/ld} = 0.30$$

$$\text{su}_1 = 0.4 * \text{esu}_1 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_1 \text{ nominal} = 0.08,$$

For calculation of esu1\_nominal and y1, sh1, ft1, fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

$$\text{y}_1, \text{sh}_1, \text{ft}_1, \text{fy}_1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_1 = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{ten, jacket}} + \text{fs}_{\text{core}} * \text{Asl}_{\text{ten, core}}) / \text{Asl}_{\text{ten}} = 389.0139$$

$$\text{with } \text{Es}_1 = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{ten, jacket}} + \text{Es}_{\text{core}} * \text{Asl}_{\text{ten, core}}) / \text{Asl}_{\text{ten}} = 200000.00$$

$$\text{y}_2 = 0.00140044$$

$$\text{sh}_2 = 0.0044814$$

$$\text{ft}_2 = 466.8167$$

$$\text{fy}_2 = 389.0139$$

$$\text{su}_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/lb, min} = 0.30$$

$$\text{su}_2 = 0.4 * \text{esu}_2 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_2 \text{ nominal} = 0.08,$$

For calculation of esu2\_nominal and y2, sh2, ft2, fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

$$\text{y}_2, \text{sh}_2, \text{ft}_2, \text{fy}_2, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_2 = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{com, jacket}} + \text{fs}_{\text{core}} * \text{Asl}_{\text{com, core}}) / \text{Asl}_{\text{com}} = 389.0139$$

$$\text{with } \text{Es}_2 = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{com, jacket}} + \text{Es}_{\text{core}} * \text{Asl}_{\text{com, core}}) / \text{Asl}_{\text{com}} = 200000.00$$

$$\text{y}_v = 0.00140044$$

$$\text{sh}_v = 0.0044814$$

$$\text{ft}_v = 466.8167$$

$$\text{fy}_v = 389.0139$$

$$\text{suv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/ld} = 0.30$$

$$\text{suv} = 0.4 * \text{esuv}_v \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esuv}_v \text{ nominal} = 0.08,$$

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv, ftv, fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

$$\text{y}_v, \text{sh}_v, \text{ft}_v, \text{fy}_v, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_v = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{mid, jacket}} + \text{fs}_{\text{mid}} * \text{Asl}_{\text{mid, core}}) / \text{Asl}_{\text{mid}} = 389.0139$$

$$\text{with } \text{Es}_v = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{mid, jacket}} + \text{Es}_{\text{mid}} * \text{Asl}_{\text{mid, core}}) / \text{Asl}_{\text{mid}} = 200000.00$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02528302$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.04909935$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02869934$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.0557338$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$\mu_u = M R_c (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{u1}$ -

Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$\mu_u = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_c (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

From EC8 A4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_u,f = 840.00$   
 $E_f = 82000.00$   
 $u,f = 0.015$

$ase((5.4d), \text{TBDY}) = (ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), \text{TBDY}) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_d = 0.30$$

$$s_u1 = 0.4 * e_{su1,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su1,nominal} = 0.08$ ,

For calculation of  $e_{su1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered  
characteristic value  $f_{sy1} = f_{s1}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s1} = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$$

$$\text{with } E_{s1} = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s,com,jacket} + f_{s,core} * A_{s,com,core}) / A_{s,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s,com,jacket} + E_{s,core} * A_{s,com,core}) / A_{s,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_uv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_0/l_{ou,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s,mid,jacket} + f_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s,mid,jacket} + E_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 200000.00$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.09206128$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.04740567$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.11310683$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.05824278$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{2+}$

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 8.4959181E-006$$

$$\mu_{2+} = 4.9689E+008$$

with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$\nu = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered

characteristic value  $f_{s2} = f_s/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, f_{y1}$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{s2} = (f_{s,jacket} \cdot A_{s,com,jacket} + f_{s,core} \cdot A_{s,com,core}) / A_{s,com} = 389.0139$

with  $E_{s2} = (E_{s,jacket} \cdot A_{s,com,jacket} + E_{s,core} \cdot A_{s,com,core}) / A_{s,com} = 200000.00$

$y_v = 0.00140044$

$sh_v = 0.0044814$

$ft_v = 466.8167$

$f_{y_v} = 389.0139$

$s_{u_v} = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$l_o/l_{o,min} = l_b/l_d = 0.30$

$s_{u_v} = 0.4 \cdot e_{s_{u_v,nominal}} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $e_{s_{u_v,nominal}} = 0.08$ ,

considering characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{s_{u_v,nominal}}$  and  $y_v, sh_v, ft_v, f_{y_v}$ , it is considered

characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, f_{y1}$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{s_v} = (f_{s,jacket} \cdot A_{s,mid,jacket} + f_{s,mid} \cdot A_{s,mid,core}) / A_{s,mid} = 389.0139$

with  $E_{s_v} = (E_{s,jacket} \cdot A_{s,mid,jacket} + E_{s,mid} \cdot A_{s,mid,core}) / A_{s,mid} = 200000.00$

$1 = A_{s,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.02528302$

$2 = A_{s,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.04909935$

$v = A_{s,mid} / (b \cdot d) \cdot (f_{s_v} / f_c) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$f_{cc} (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = A_{s,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.02869934$

$2 = A_{s,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.0557338$

$v = A_{s,mid} / (b \cdot d) \cdot (f_{s_v} / f_c) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$s_u (4.9) = 0.1476063$

$\mu_u = M_{Rc} (4.14) = 4.9689E+008$

$u = s_u (4.1) = 8.4959181E-006$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----  
-----

-----  
Calculation of  $\mu_{u2}$ -  
-----  
-----  
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$u = 9.2452857E-006$

$\mu_u = 8.1540E+008$

-----  
with full section properties:

$b = 400.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00174378$

$N = 16273.607$

$f_c = 33.00$

$cc (5A.5, TBDY) = 0.002$

Final value of  $\mu_{cu}$ :  $\mu_{cu}^* = \text{shear\_factor} \cdot \text{Max}(c_u, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $c_u = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$R = 40.00$

Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b_1) = 1.00$

$f_u, f = 840.00$

$E_f = 82000.00$

$u, f = 0.015$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$

$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

psh<sub>y</sub>\*Fywe = psh<sub>1</sub>\*Fywe<sub>1</sub>+ps<sub>2</sub>\*Fywe<sub>2</sub> = 3.0194  
psh<sub>1</sub> ((5.4d), TBDY) = Lstir<sub>1</sub>\*Astir<sub>1</sub>/(Asec\*s<sub>1</sub>) = 0.00367709  
Lstir<sub>1</sub> (Length of stirrups along X) = 2060.00  
Astir<sub>1</sub> (stirrups area) = 78.53982  
psh<sub>2</sub> ((5.4d), TBDY) = Lstir<sub>2</sub>\*Astir<sub>2</sub>/(Asec\*s<sub>2</sub>) = 0.00067082  
Lstir<sub>2</sub> (Length of stirrups along X) = 1468.00  
Astir<sub>2</sub> (stirrups area) = 50.26548

Asec = 440000.00

s<sub>1</sub> = 100.00

s<sub>2</sub> = 250.00

fywe<sub>1</sub> = 694.45

fywe<sub>2</sub> = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y<sub>1</sub> = 0.00140044

sh<sub>1</sub> = 0.0044814

ft<sub>1</sub> = 466.8167

fy<sub>1</sub> = 389.0139

su<sub>1</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su<sub>1</sub> = 0.4\*esu<sub>1\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>1\_nominal</sub> = 0.08,

For calculation of esu<sub>1\_nominal</sub> and y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, it is considered  
characteristic value fsy<sub>1</sub> = fs<sub>1</sub>/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>1</sub> = (fs<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + fs<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 389.0139

with Es<sub>1</sub> = (Es<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + Es<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 200000.00

y<sub>2</sub> = 0.00140044

sh<sub>2</sub> = 0.0044814

ft<sub>2</sub> = 466.8167

fy<sub>2</sub> = 389.0139

su<sub>2</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su<sub>2</sub> = 0.4\*esu<sub>2\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>2\_nominal</sub> = 0.08,

For calculation of esu<sub>2\_nominal</sub> and y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, it is considered  
characteristic value fsy<sub>2</sub> = fs<sub>2</sub>/1.2, from table 5.1, TBDY.

y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>2</sub> = (fs<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + fs<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 389.0139

with Es<sub>2</sub> = (Es<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + Es<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 200000.00

y<sub>v</sub> = 0.00140044

sh<sub>v</sub> = 0.0044814

ft<sub>v</sub> = 466.8167

fy<sub>v</sub> = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv = 0.4\*esuv<sub>nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv<sub>nominal</sub> = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv<sub>nominal</sub> and y<sub>v</sub>, sh<sub>v</sub>,ft<sub>v</sub>,fy<sub>v</sub>, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fsv = (fs<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + fs<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 389.0139

with Es<sub>v</sub> = (Es<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + Es<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 200000.00

1 = Asl<sub>ten</sub>/(b\*d)\*(fs<sub>1</sub>/fc) = 0.09206128

2 = Asl<sub>com</sub>/(b\*d)\*(fs<sub>2</sub>/fc) = 0.04740567

$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.08368017$   
 and confined core properties:  
 $b = 340.00$   
 $d = 677.00$   
 $d' = 13.00$   
 $f_{cc} (5A.2, TBDY) = 34.43547$   
 $cc (5A.5, TBDY) = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$   
 $1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.11310683$   
 $2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.05824278$   
 $v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.10280977$   
 Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)

--->  
 $v < v_{s,y2}$  - LHS eq.(4.5) is satisfied  
 --->  
 $su (4.9) = 0.21669624$   
 $Mu = MRc (4.14) = 8.1540E+008$   
 $u = su (4.1) = 9.2452857E-006$

-----  
 Calculation of ratio  $l_b/l_d$

-----  
 Inadequate Lap Length with  $l_b/l_d = 0.30$   
 -----  
 -----  
 -----

-----  
 Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$   
 -----

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$   
 $V_{r1} = V_{Col} ((10.3), ASCE 41-17) = k_{nl} * V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

-----  
 NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ '  
 where  $V_f$  is the contribution of FRPs (11.3), ACI 440).  
 -----

$= 1$  (normal-weight concrete)  
 Mean concrete strength:  $f'_c = (f'_{c,jacket} * Area_{jacket} + f'_{c,core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c^{0.5} \leq 8.3$   
 MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$   
 $Mu = 1518.009$   
 $Vu = 0.00017144$   
 $d = 0.8 * h = 600.00$   
 $Nu = 16273.607$   
 $Ag = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:  
 $V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col,j1 = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col,j2 = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{sc1} + V_{sc2} = 98297.73$   
 $V_{sc1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot_a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\rho = 1$  (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/d = 4.00$$

$$\mu_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$$

$V_{sj1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{sj2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

d = 440.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c1 is multiplied by Col,c1 = 1.00  
 s/d = 0.56818182  
 Vs,c2 = 0.00 is calculated for section flange core, with:  
 d = 160.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c2 is multiplied by Col,c2 = 0.00  
 s/d = 1.5625  
 Vf ((11-3)-(11.4), ACI 440) = 463792.00  
 f = 0.95, for fully-wrapped sections  
 wf/sf = 1 (FRP strips adjacent to one another).  
 In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression,  
 where  $\theta$  is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function  $Vf(\theta, a)$ , is implemented for every different fiber orientation  $a_i$ ,  
 as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.  
 orientation 1:  $\theta = b1 + 90^\circ = 90.00$   
 $Vf = \text{Min}(|Vf(45, \theta)|, |Vf(-45, a1)|)$ , with:  
 total thickness per orientation,  $tf1 = NL*t/NoDir = 1.00$   
 $dfv = d$  (figure 11.2, ACI 440) = 707.00  
 $ffe$  ((11-5), ACI 440) = 328.00  
 Ef = 82000.00  
 fe = 0.004, from (11.6a), ACI 440  
 with fu = 0.009  
 From (11-11), ACI 440:  $Vs + Vf \leq 915872.391$   
 bw = 400.00

-----  
 End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At local axis: 3  
 -----

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At Shear local axis: 2  
 (Bending local axis: 3)  
 Section Type: rcjlc3

Constant Properties

-----  
 Knowledge Factor,  $\phi = 0.87$   
 Mean strength values are used for both shear and moment calculations.  
 Consequently:  
 Jacket  
 New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$   
 New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$   
 Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 Existing Column  
 New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$   
 New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$   
 Concrete Elasticity,  $E_c = 26999.444$   
 Steel Elasticity,  $E_s = 200000.00$   
 #####  
 Note: Especially for the calculation of moment strengths,  
 the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14  
 Jacket  
 New material: Steel Strength,  $f_s = 1.25*f_{sm} = 694.45$   
 Existing Column  
 New material: Steel Strength,  $f_s = 1.25*f_{sm} = 694.45$   
 #####  
 Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Mean Confinement Factor overall section = 1.0435  
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 2  
EDGE -A-  
Shear Force,  $V_a = -0.0001715$   
EDGE -B-  
Shear Force,  $V_b = 0.0001715$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{sl,t} = 0.00$   
-Compression:  $A_{sl,c} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{sl,ten} = 1137.257$   
-Compression:  $A_{sl,com} = 2208.54$   
-Middle:  $A_{sl,mid} = 2007.478$

-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(\mu_{u1+} , \mu_{u1-}) = 8.1540E+008$   
 $\mu_{u1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $\mu_{u1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(\mu_{u2+} , \mu_{u2-}) = 8.1540E+008$   
 $\mu_{u2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $\mu_{u2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{u1+}$   
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006  
Mu = 4.9689E+008

with full section properties:

b = 750.00  
d = 707.00  
d' = 43.00  
v = 0.00093001  
N = 16273.607  
fc = 33.00  
co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $ase * sh, \min * fy_{we} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A 4.4.3(6),  $pf = 2t_f / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_{e} = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A 4.4.3(6),  $pf = 2t_f / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_{e} = 765.1636$

R = 40.00

Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase_1 * A_{ext} + ase_2 * A_{int}) / A_{sec} = 0.45746528$

$ase_1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

$ase_2 (> = ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

$$psh_{min} * Fy_{we} = \text{Min}(psh_x * Fy_{we}, psh_y * Fy_{we}) = 3.0194$$

Expression (5.4d) for  $psh_{min} * Fy_{we}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$psh_x * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along Y)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ (5.4d)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along Y)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$psh_y * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along X)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ ((5.4d), TBDY)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along X)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$Asec = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$fy_{we1} = 694.45$$

$$fy_{we2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/ld = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu1_{nominal} = 0.08,$$

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs1 = (fs_{jacket} * Asl_{ten,jacket} + fs_{core} * Asl_{ten,core}) / Asl_{ten} = 389.0139$$

$$\text{with } Es1 = (Es_{jacket} * Asl_{ten,jacket} + Es_{core} * Asl_{ten,core}) / Asl_{ten} = 200000.00$$

$$y2 = 0.00140044$$

$$sh2 = 0.0044814$$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/lb_{min} = 0.30$$

$$su2 = 0.4 * esu2_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu2_{nominal} = 0.08,$$

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs2 = (fs_{jacket} * Asl_{com,jacket} + fs_{core} * Asl_{com,core}) / Asl_{com} = 389.0139$$

$$\text{with } Es2 = (Es_{jacket} * Asl_{com,jacket} + Es_{core} * Asl_{com,core}) / Asl_{com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$su_v = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fsjacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05573338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

----

v < vs,y2 - LHS eq.(4.5) is satisfied

----

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30

-----  
Calculation of Mu1-

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008

-----  
with full section properties:

b = 400.00

d = 707.00

d' = 43.00

v = 0.00174378

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} \cdot \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase \cdot sh_{\min} \cdot fy_{we}/f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af \cdot pf \cdot f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$

Effective FRP thickness,  $tf = NL*tf*Cos(b1) = 1.00$

$f_u,f = 840.00$

$E_f = 82000.00$

$u,f = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2$  ( $\geq ase1$ ) =  $\text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$psh_{min}*F_{ywe} = \text{Min}(psh_x*F_{ywe}, psh_y*F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min}*F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$psh_x*F_{ywe} = psh1*F_{ywe1} + ps2*F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1}*A_{stir1}/(A_{sec}*s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2}*A_{stir2}/(A_{sec}*s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$psh_y*F_{ywe} = psh1*F_{ywe1} + ps2*F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1}*A_{stir1}/(A_{sec}*s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2}*A_{stir2}/(A_{sec}*s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00  
d = 677.00  
d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$\mu_u$  (4.9) = 0.21669624

$M_u$  = MRc (4.14) = 8.1540E+008

$u$  =  $\mu_u$  (4.1) = 9.2452857E-006

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$

-----  
Calculation of  $\mu_{u2+}$

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$u$  = 8.4959181E-006

$M_u$  = 4.9689E+008

-----  
with full section properties:

$b$  = 750.00

$d$  = 707.00

$d'$  = 43.00

$v$  = 0.00093001

$N$  = 16273.607

$f_c$  = 33.00

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $\mu_u$ :  $\mu_u^* = \text{shear\_factor} * \text{Max}(\mu_u, \mu_c) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\mu_u = 0.01241186$

$\mu_{we}$  ((5.4c), TBDY) =  $\alpha \text{se} * \text{sh}_{\min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha f_p f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha f = 0.31984848$

with Unconfined area =  $((b_{\max}-2R)^2 + (h_{\max}-2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

-----  
 $f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha f = 0.31984848$

with Unconfined area =  $((b_{\max}-2R)^2 + (h_{\max}-2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

-----  
 $R = 40.00$

Effective FRP thickness,  $t_f = N L^* t \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$\alpha \text{se}$  ((5.4d), TBDY) =  $(\alpha \text{se}_1 * A_{\text{ext}} + \alpha \text{se}_2 * A_{\text{int}})/A_{\text{sec}} = 0.45746528$

$\alpha \text{se}_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{u,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/lb,min = 0.30$$

$$su2 = 0.4*esu2\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs,jacket*Asl,com,jacket + fs,core*Asl,com,core)/Asl,com = 389.0139$$

$$\text{with } Es2 = (Es,jacket*Asl,com,jacket + Es,core*Asl,com,core)/Asl,com = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/ld = 0.30$$

$$suv = 0.4*esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs,jacket*Asl,mid,jacket + fs,mid*Asl,mid,core)/Asl,mid = 389.0139$$

$$\text{with } Esv = (Es,jacket*Asl,mid,jacket + Es,mid*Asl,mid,core)/Asl,mid = 200000.00$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02528302$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.04909935$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.0557338$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

---->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu2-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\alpha_w \text{ ((5.4c), TBDY) } = \alpha_{se} * \text{sh}_{,\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f^* f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t^* \text{Cos}(b_1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY) } = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{conf, \max 1} - A_{noConf1}) / A_{conf, \max 1}) * (A_{conf, \min 1} / A_{conf, \max 1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf, \min 1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf, \max 1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_{se2} (> \alpha_{se1}) = \text{Max}(((A_{conf, \max 2} - A_{noConf2}) / A_{conf, \max 2}) * (A_{conf, \min 2} / A_{conf, \max 2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf, \min 2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf, \max 2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh, \min} * F_{ywe} = \text{Min}(p_{sh, x} * F_{ywe}, p_{sh, y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh, \min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without

earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv$ ,  $shv,ftv,fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1,ft1,fy1$ , are also multiplied by  $Min(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs\_jacket * Asl\_mid\_jacket + fs\_mid * Asl\_mid\_core) / Asl\_mid = 389.0139$$

$$\text{with } Esv = (Es\_jacket * Asl\_mid\_jacket + Es\_mid * Asl\_mid\_core) / Asl\_mid = 200000.00$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.09206128$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.04740567$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.11310683$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.05824278$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $Vr = Min(Vr1, Vr2) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $Vr1 = 1.0898E+006$

$Vr1 = VCol ((10.3), ASCE 41-17) = knl * VCol0$

$$VCol0 = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $Vs = Av * fy * d / s$ ' is replaced by ' $Vs + f * Vf$ ' where  $Vf$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $fc' = (fc'_jacket * Area\_jacket + fc'_core * Area\_core) / Area\_section = 33.00$ , but  $fc'^{0.5} <= 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$Mu = 1518.777$$

$$Vu = 0.0001715$$

$$d = 0.8 * h = 600.00$$

$$Nu = 16273.607$$

$$Ag = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } Vs = Vs\_jacket + Vs\_core = 901155.609$$

where:

$$Vs\_jacket = Vs\_j1 + Vs\_j2 = 802857.879$$

$Vs\_j1 = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$Av = 157079.633$$

$$fy = 555.56$$

$$s = 100.00$$

$Vs\_j1$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$V_f((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a_i)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}((11-5), ACI 440) = 328.00$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}((10.3), ASCE 41-17) = knl \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\lambda = 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$M_u = 1518.776$$

$$V_u = 0.0001715$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b1 + 90^\circ = 90.00$

$$V_f = \text{Min}(|V_f(45, \alpha)|, |V_f(-45, \alpha)|), \text{ with:}$$

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$b_w = 400.00$$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 2  
-----

-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

Section Type: rcjlc3

Constant Properties  
-----

Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$   
Steel Elasticity,  $E_s = 200000.00$   
Max Height,  $H_{max} = 750.00$   
Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

#### ----- Stepwise Properties

Bending Moment,  $M = 505194.60$   
Shear Force,  $V_2 = 4865.29$   
Shear Force,  $V_3 = -131.62$   
Axial Force,  $F = -18154.424$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$   
Longitudinal External Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,jacket} = 829.3805$   
-Compression:  $As_{c,com,jacket} = 1746.726$   
-Middle:  $As_{c,mid,jacket} = 1545.664$   
Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,core} = 307.8761$   
-Compression:  $As_{c,com,core} = 461.8141$   
-Middle:  $As_{c,mid,core} = 461.8141$   
Mean Diameter of Tension Reinforcement,  $Db_L = 16.80$

-----  
-----  
New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u_R = 1.0^*$   $u = 0.00024001$   
 $u = y + p = 0.00024001$

-----  
- Calculation of  $y$  -

-----  
 $y = (M_y * L_s / 3) / E_{eff} = 0.00024001$  ((4.29), Biskinis Phd))  
 $M_y = 3.6650E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 300.00  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
factor = 0.30  
 $A_g = 440000.00$   
Mean concrete strength:  $fc' = (fc'_{jacket} * Area_{jacket} + fc'_{core} * Area_{core}) / Area_{section} = 33.00$

$$N = 18154.424$$

$$E_c \cdot I_g = E_c \cdot I_{g\_jacket} + E_c \cdot I_{g\_core} = 5.0901E+014$$

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$$

$$y_{\text{ten}} = 2.7302957E-006$$

$$\text{with } ((10.1), \text{ASCE 41-17}) f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$$

$$d = 707.00$$

$$y = 0.19388674$$

$$A = 0.01020577$$

$$B = 0.00451618$$

$$\text{with } p_t = 0.00729988$$

$$p_c = 0.00416509$$

$$p_v = 0.00378591$$

$$N = 18154.424$$

$$b = 750.00$$

$$" = 0.06082037$$

$$y_{\text{comp}} = 1.6519231E-005$$

$$\text{with } f_c^* (12.3, \text{ACI 440}) = 33.60672$$

$$f_c = 33.00$$

$$f_l = 0.61848273$$

$$b = b_{\text{max}} = 750.00$$

$$h = h_{\text{max}} = 750.00$$

$$A_g = 0.44$$

$$g = p_t + p_c + p_v = 0.01009575$$

$$r_c = 40.00$$

$$A_e/A_c = 0.31291181$$

$$\text{Effective FRP thickness, } t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$$

$$\text{effective strain from (12.5) and (12.12), } e_{fe} = 0.004$$

$$f_u = 0.009$$

$$E_f = 82000.00$$

$$E_c = 26999.444$$

$$y = 0.19183796$$

$$A = 0.01001935$$

$$B = 0.00440616$$

$$\text{with } E_s = 200000.00$$

CONFIRMATION:  $y = 0.192811 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

- Calculation of  $p$  -

From table 10-8:  $p = 0.00$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/d < 1$

$$\text{shear control ratio } V_y E / V_c I_{OE} = 0.49879178$$

$$d = d_{\text{external}} = 707.00$$

$$s = s_{\text{external}} = 0.00$$

$$- t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$$

$$\text{jacket: } s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s1 = 100.00$$

$$\text{core: } s2 = Av2 * Lstir2 / (s2 * Ag) = 0.00067082$$

$Av2 = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$Lstir2 = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s2 = 250.00$$

The term  $2 * tf / bw * (ffe / fs)$  is implemented to account for FRP contribution

where  $f = 2 * tf / bw$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $ffe / fs$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $fs$  of jacket is used.

$$NUD = 18154.424$$

$$Ag = 440000.00$$

$$fcE = (fc\_jacket * Area\_jacket + fc\_core * Area\_core) / section\_area = 33.00$$

$$fyIE = (fy\_ext\_Long\_Reinf * Area\_ext\_Long\_Reinf + fy\_int\_Long\_Reinf * Area\_int\_Long\_Reinf) / Area\_Tot\_Long\_Rein = 555.56$$

$$fytE = (fy\_ext\_Trans\_Reinf * s1 + fy\_int\_Trans\_Reinf * s2) / (s1 + s2) = 555.56$$

$$pl = Area\_Tot\_Long\_Rein / (b * d) = 0.01009575$$

$$b = 750.00$$

$$d = 707.00$$

$$fcE = 33.00$$

End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

## Calculation No. 9

column C1, Floor 1



Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: Start

Local Axis: (2)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2  
Integration Section: (a)  
Section Type: rcjcs

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$   
Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.  
Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand,  
the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as  
Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{ou,min} = l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

EDGE -A-

Bending Moment,  $M_a = -2.3693E+007$

Shear Force,  $V_a = -7630.77$

EDGE -B-

Bending Moment,  $M_b = 793215.62$

Shear Force,  $V_b = 7630.77$

BOTH EDGES

Axial Force,  $F = -19223.50$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{t,ten} = 1137.257$

-Compression:  $As_{c,com} = 2208.54$

-Middle:  $As_{c,mid} = 2007.478$

Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $VR = 1.0 \cdot V_n = 949074.782$

$V_n$  ((10.3), ASCE 41-17) =  $k_n \cdot V_{CoI} = 949074.782$

$V_{CoI} = 949074.782$

$k_n = 1.00$

displacement\_ductility\_demand = 0.03368972

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 2.3693E+007$

$V_u = 7630.77$

$d = 0.8 \cdot h = 600.00$

$N_u = 19223.50$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$

$V_{s,j1} = 251327.412$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col_{j1} = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 471238.898$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col_{j2} = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col_{c1} = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 88467.249$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col_{c2} = 1.00$

$s/d = 0.56818182$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression, where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $\theta$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 90^\circ$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_f = NL \cdot t / N_{\text{Dir}} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 797164.595$

$b_w = 400.00$

displacement ductility demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END A -

for rotation axis 3 and integ. section (a)

From analysis, chord rotation  $\theta = 8.3761548E-005$

$y = (M_y \cdot L_s / 3) / E_{\text{eff}} = 0.00248626$  ((4.29), Biskinis Phd)

$M_y = 3.6682E+008$

$L_s = M/V$  (with  $L_s > 0.1 \cdot L$  and  $L_s < 2 \cdot L$ ) = 3104.971

From table 10.5, ASCE 41\_17:  $E_{\text{eff}} = \text{factor} \cdot E_c \cdot I_g = 1.5270E+014$

factor = 0.30

$A_g = 440000.00$

Mean concrete strength:  $f'_c = (f'_{c, \text{jacket}} \cdot A_{\text{jacket}} + f'_{c, \text{core}} \cdot A_{\text{core}}) / A_{\text{section}} = 33.00$

$N = 19223.50$

$E_c \cdot I_g = E_{c, \text{jacket}} \cdot I_{g, \text{jacket}} + E_{c, \text{core}} \cdot I_{g, \text{core}} = 5.0901E+014$

Calculation of Yielding Moment  $M_y$

Calculation of  $\delta / y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7307817E-006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (I_b / I_d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 19223.50$

$b = 750.00$

$\lambda = 0.06082037$

$y_{\text{comp}} = 1.6517162E-005$

with  $f'_c$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e / A_c = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(\theta) = 1.00$

effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$

$f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19186199$   
 $A = 0.01001485$   
 $B = 0.00440616$   
with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $I_b/I_d$

Inadequate Lap Length with  $I_b/I_d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

## Calculation No. 10

column C1, Floor 1



Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity (  $\theta$  )

Edge: Start

Local Axis: (2)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

-----  
At local axis: 3

EDGE -A-

Shear Force,  $V_a = -0.00017144$

EDGE -B-

Shear Force,  $V_b = 0.00017144$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{l,ten} = 1137.257$

-Compression:  $As_{l,com} = 2208.54$

-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$

Member Controlled by Flexure ( $V_e/V_r < 1$ )

Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$

with

$M_{pr1} = \text{Max}(\mu_{1+}, \mu_{1-}) = 8.1540\text{E}+008$

$\mu_{1+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination

$\mu_{1-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination

$M_{pr2} = \text{Max}(\mu_{2+}, \mu_{2-}) = 8.1540\text{E}+008$

$\mu_{2+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination

$\mu_{2-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$\mu = 8.4959181\text{E}-006$

$M_u = 4.9689\text{E}+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $\mu$ :  $\mu^* = \text{shear\_factor} * \text{Max}(\mu_c, \mu_{cc}) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\mu_c = 0.01241186$

$\mu_{cc}$  ((5.4c), TBDY) =  $\alpha s_e * \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha^* p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$R = 40.00$

Effective FRP thickness,  $t_f = N L^* t^* \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$\alpha_{se}$  ((5.4d), TBDY) =  $(\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$

$\alpha_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.  
 $A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$   
 $s1 = 100.00$   
 $s2 = 250.00$   
 $f_{ywe1} = 694.45$   
 $f_{ywe2} = 694.45$   
 $f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$   
 $sh1 = 0.0044814$   
 $ft1 = 466.8167$   
 $fy1 = 389.0139$   
 $su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{u,min} = lb/ld = 0.30$

$su1 = 0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$   
 $sh2 = 0.0044814$   
 $ft2 = 466.8167$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/lb,min = 0.30$$

$$su2 = 0.4*esu2\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs,jacket*Asl,com,jacket + fs,core*Asl,com,core)/Asl,com = 389.0139$$

$$\text{with } Es2 = (Es,jacket*Asl,com,jacket + Es,core*Asl,com,core)/Asl,com = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/ld = 0.30$$

$$suv = 0.4*esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs,jacket*Asl,mid,jacket + fs,mid*Asl,mid,core)/Asl,mid = 389.0139$$

$$\text{with } Esv = (Es,jacket*Asl,mid,jacket + Es,mid*Asl,mid,core)/Asl,mid = 200000.00$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02528302$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.04909935$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.05573338$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu1-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

-----

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, TBDY) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e^* \text{ sh}_{,\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f^* f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t^* \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$\alpha_s_e \text{ ((5.4d), TBDY) } = (\alpha_s_e1 * A_{\text{ext}} + \alpha_s_e2 * A_{\text{int}}) / A_{\text{sec}} = 0.45746528$$

$$\alpha_s_e1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_s_e2 (> = \alpha_s_e1) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}}) / A_{\text{conf,max2}}) * (A_{\text{conf,min2}} / A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max2}} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{\text{conf,min2}} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max2}}$  by a length equal to half the clear spacing between internal hoops.

$A_{\text{noConf2}} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,\min} * f_{ywe} = \text{Min}(p_{sh,x} * f_{ywe}, p_{sh,y} * f_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,\min} * f_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00  
s1 = 100.00  
s2 = 250.00  
fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,  
 considering characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY  
 For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
 characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY.  
 $y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.  
 with  $fsv = (fs_{jacket} * Asl_{mid,jacket} + fs_{mid} * Asl_{mid,core}) / Asl_{mid} = 389.0139$   
 with  $Esv = (Es_{jacket} * Asl_{mid,jacket} + Es_{mid} * Asl_{mid,core}) / Asl_{mid} = 200000.00$   
 $1 = Asl_{ten} / (b * d) * (fs1 / fc) = 0.09206128$   
 $2 = Asl_{com} / (b * d) * (fs2 / fc) = 0.04740567$   
 $v = Asl_{mid} / (b * d) * (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$   
 $d = 677.00$   
 $d' = 13.00$   
 $fcc$  (5A.2, TBDY) = 34.43547  
 $cc$  (5A.5, TBDY) = 0.00243499  
 $c =$  confinement factor = 1.0435  
 $1 = Asl_{ten} / (b * d) * (fs1 / fc) = 0.11310683$   
 $2 = Asl_{com} / (b * d) * (fs2 / fc) = 0.05824278$   
 $v = Asl_{mid} / (b * d) * (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)

---->  
 $v < vs_{y2}$  - LHS eq.(4.5) is satisfied

---->  
 $su$  (4.9) = 0.21669624  
 $Mu = MRc$  (4.14) = 8.1540E+008  
 $u = su$  (4.1) = 9.2452857E-006

-----  
 Calculation of ratio  $lb/ld$

-----  
 Inadequate Lap Length with  $lb/ld = 0.30$   
 -----

-----  
 Calculation of  $Mu_{2+}$   
 -----

-----  
 Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$   
 $Mu = 4.9689E+008$

-----  
 with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$

$fc = 33.00$   
 $co$  (5A.5, TBDY) = 0.002

Final value of  $cu$ :  $cu^* = shear\_factor * Max(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

where  $we$  ((5.4c), TBDY) =  $ase * sh_{min} * fy_{we} / f_{ce} + Min(fx, fy) = 0.0496383$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $fx = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (Unconfined\ area) / (total\ area)$

$af = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_e = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = NL * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}, 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}})/A_{\text{conf,max2}}) * (A_{\text{conf,min2}}/A_{\text{conf,max2}}, 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max2}} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{\text{conf,min2}} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{\text{conf,max2}}$  by a length equal to half the clear spacing between internal hoops.

$A_{\text{noConf2}} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s_1 = 100.00$$

$$s_2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

From ((5.A.5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$su1 = 0.4 * esu1\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered  
characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs,jacket * Asl,ten,jacket + fs,core * Asl,ten,core) / Asl,ten = 389.0139$

with  $Es1 = (Es,jacket * Asl,ten,jacket + Es,core * Asl,ten,core) / Asl,ten = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/lb,min = 0.30$

$su2 = 0.4 * esu2\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered  
characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs,jacket * Asl,com,jacket + fs,core * Asl,com,core) / Asl,com = 389.0139$

with  $Es2 = (Es,jacket * Asl,com,jacket + Es,core * Asl,com,core) / Asl,com = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs,jacket * Asl,mid,jacket + fs,mid * Asl,mid,core) / Asl,mid = 389.0139$

with  $Es_v = (Es,jacket * Asl,mid,jacket + Es,mid * Asl,mid,core) / Asl,mid = 200000.00$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02528302$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.04909935$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$fcc (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02869934$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.0557338$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u(4.9) = 0.1476063$$

$$M_u = M_{Rc}(4.14) = 4.9689E+008$$

$$u = s_u(4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u2}$   
-----  
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$M_u = 8.1540E+008$$

-----  
with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha(5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \phi_u: \phi_u^* = \text{shear\_factor} * \text{Max}(\phi_u, \phi_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \phi_u = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e \cdot \text{sh, min} * f_{ywe} / f_{ce} + \text{Min}(\phi_x, \phi_y) = 0.0496383$$

where  $\phi = \alpha * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$\phi_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2) / 3 = 140733.333$$

$$b_{\text{max}} = 750.00$$

$$h_{\text{max}} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$\phi_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2) / 3 = 140733.333$$

$$b_{\text{max}} = 750.00$$

$$h_{\text{max}} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY) } = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max1 = 353600.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

Aconf,min1 = 293525.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max1 by a length equal to half the clear spacing between external hoops.

AnoConf1 = 158733.333 is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
ase2 ( $\geq$  ase1) =  $\text{Max}(((Aconf,max2 - AnoConf2)/Aconf,max2) * (Aconf,min2/Aconf,max2), 0) = 0.45746528$

The definitions of AnoConf, Aconf,min and Aconf,max are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max2 = 171264.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

Aconf,min2 = 54741.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max2 by a length equal to half the clear spacing between internal hoops.

AnoConf2 = 106242.667 is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
psh,min\*Fywe =  $\text{Min}(psh,x*Fywe, psh,y*Fywe) = 3.0194$

Expression (5.4d) for psh,min\*Fywe has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
psh\_x\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along Y) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 (5.4d) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along Y) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
psh\_y\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along X) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 ((5.4d), TBDY) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along X) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 =  $0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1, ft1, fy1, it is considered characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1, ft1, fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs\_jacket * Asl\_ten\_jacket + fs\_core * Asl\_ten\_core) / Asl\_ten = 389.0139$

with Es1 =  $(Es\_jacket * Asl\_ten\_jacket + Es\_core * Asl\_ten\_core) / Asl\_ten = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{sl,com,jacket} + f_{s,core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{sl,com,jacket} + E_{s,core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{uv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{sl,mid,jacket} + f_{s,mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{sl,mid,jacket} + E_{s,mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$$

$$1 = A_{sl,ten} / (b * d) * (f_{s1} / f_c) = 0.09206128$$

$$2 = A_{sl,com} / (b * d) * (f_{s2} / f_c) = 0.04740567$$

$$v = A_{sl,mid} / (b * d) * (f_{sv} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten} / (b * d) * (f_{s1} / f_c) = 0.11310683$$

$$2 = A_{sl,com} / (b * d) * (f_{s2} / f_c) = 0.05824278$$

$$v = A_{sl,mid} / (b * d) * (f_{sv} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$

$$V_{r1} = V_{Co1} ((10.3), ASCE 41-17) = k_{nl} * V_{Co10}$$

$$V_{Co10} = 1.0898E+006$$

$$k_{nl} = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)  
 Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)  
 $M/Vd = 4.00$   
 $\mu_u = 1518.009$   
 $V_u = 0.00017144$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 16273.607$   
 $A_g = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{sjacket} + V_{s,core} = 901155.609$   
 where:  
 $V_{sjacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col_{j1} = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col_{j2} = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$   
 $V_{s,c1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c1}$  is multiplied by  $Col_{c1} = 1.00$   
 $s/d = 0.56818182$   
 $V_{s,c2} = 0.00$  is calculated for section flange core, with:  
 $d = 160.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c2}$  is multiplied by  $Col_{c2} = 0.00$   
 $s/d = 1.5625$   
 $V_f$  ((11-3)-(11.4), ACI 440) = 463792.00  
 $f = 0.95$ , for fully-wrapped sections  
 $w_f/s_f = 1$  (FRP strips adjacent to one another).  
 In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \cot \alpha) \sin \alpha$  which is more a generalised expression,  
 where  $\theta$  is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ ,  
 as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.  
 orientation 1:  $\theta = 45^\circ + 90^\circ = 135^\circ$   
 $V_f = \text{Min}(|V_f(45, 1)|, |V_f(-45, 1)|)$ , with:  
 total thickness per orientation,  $t_{f1} = NL \cdot t / N_{Dir} = 1.00$   
 $d_{fv} = d$  (figure 11.2, ACI 440) = 707.00  
 $f_{fe}$  ((11-5), ACI 440) = 328.00  
 $E_f = 82000.00$   
 $f_e = 0.004$ , from (11.6a), ACI 440  
 with  $f_u = 0.009$   
 From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $b_w = 400.00$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$   
 $V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '

where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{\text{jacket}} \cdot \text{Area}_{\text{jacket}} + f_c'_{\text{core}} \cdot \text{Area}_{\text{core}}) / \text{Area}_{\text{section}} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.009$

$V_u = 0.00017144$

$d = 0.8 \cdot h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,\text{jacket}} + V_{s,\text{core}} = 901155.609$

where:

$V_{s,\text{jacket}} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 523602.964$  is calculated for section web jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $\text{Col},j1 = 1.00$

$s/d = 0.16666667$

$V_{s,j2} = 279254.914$  is calculated for section flange jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $\text{Col},j2 = 1.00$

$s/d = 0.3125$

$V_{s,\text{core}} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $\text{Col},c1 = 1.00$

$s/d = 0.56818182$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $\text{Col},c2 = 0.00$

$s/d = 1.5625$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \alpha)|, |V_f(-45, \alpha)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L \cdot t / N_{\text{Dir}} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 3

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 2

(Bending local axis: 3)

Section Type: rcjcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

Stepwise Properties

At local axis: 2

EDGE -A-

Shear Force,  $V_a = -0.0001715$

EDGE -B-

Shear Force,  $V_b = 0.0001715$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $As_{lc} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{l,ten} = 1137.257$   
-Compression:  $As_{l,com} = 2208.54$   
-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with

$M_{pr1} = \text{Max}(M_{u1+}, M_{u1-}) = 8.1540E+008$   
 $M_{u1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination  
 $M_{u1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(M_{u2+}, M_{u2-}) = 8.1540E+008$   
 $M_{u2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination  
 $M_{u2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $M_{u1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $M_u = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$   
 $f_c = 33.00$   
 $\phi_c$  (5A.5, TBDY) = 0.002  
Final value of  $\phi_{cu}$ :  $\phi_{cu}^* = \text{shear\_factor} * \text{Max}(\phi_{cu}, \phi_c) = 0.01241186$   
The Shear\_factor is considered equal to 1 (pure moment strength)  
From (5.4b), TBDY:  $\phi_{cu} = 0.01241186$   
 $\phi_{we}$  ((5.4c), TBDY) =  $\phi_{we} * \text{sh}_{,min} * f_{ywe}/f_{ce} + \text{Min}(\phi_x, \phi_y) = 0.0496383$   
where  $\phi = \phi_{af} * \phi_{ff,e}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $\phi_x = 0.03708128$   
Expression ((15B.6), TBDY) is modified as  $\phi_{af} = 1 - (\text{Unconfined area})/(\text{total area})$   
 $\phi_{af} = 0.31984848$   
with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$   
 $b_{max} = 750.00$   
 $h_{max} = 750.00$   
From EC8 A.4.4.3(6),  $\phi_{pf} = 2t_f/b_w = 0.005$   
 $b_w = 400.00$   
effective stress from (A.35),  $\phi_{ff,e} = 765.1636$

-----  
 $\phi_y = 0.03708128$   
Expression ((15B.6), TBDY) is modified as  $\phi_{af} = 1 - (\text{Unconfined area})/(\text{total area})$   
 $\phi_{af} = 0.31984848$   
with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$   
 $b_{max} = 750.00$   
 $h_{max} = 750.00$   
From EC8 A.4.4.3(6),  $\phi_{pf} = 2t_f/b_w = 0.005$   
 $b_w = 400.00$   
effective stress from (A.35),  $\phi_{ff,e} = 765.1636$   
-----

R = 40.00

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_f = 0.015$

$ase((5.4d), TBDY) = (ase_1 \cdot A_{ext} + ase_2 \cdot A_{int}) / A_{sec} = 0.45746528$

$ase_1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) \cdot (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) \cdot (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} \cdot F_{ywe} = \text{Min}(p_{sh,x} \cdot F_{ywe}, p_{sh,y} \cdot F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} \cdot F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} \cdot F_{ywe} = p_{sh1} \cdot F_{ywe1} + p_{sh2} \cdot F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), TBDY) = L_{stir1} \cdot A_{stir1} / (A_{sec} \cdot s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} \cdot A_{stir2} / (A_{sec} \cdot s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} \cdot F_{ywe} = p_{sh1} \cdot F_{ywe1} + p_{sh2} \cdot F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), TBDY) = L_{stir1} \cdot A_{stir1} / (A_{sec} \cdot s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), TBDY) = L_{stir2} \cdot A_{stir2} / (A_{sec} \cdot s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c$  = confinement factor = 1.0435

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o / l_{ou,min} = l_b / l_d = 0.30$

$$su1 = 0.4 * esu1\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs1 = (fs\_jacket * Asl,ten,jacket + fs\_core * Asl,ten,core) / Asl,ten = 389.0139$$

$$\text{with } Es1 = (Es\_jacket * Asl,ten,jacket + Es\_core * Asl,ten,core) / Asl,ten = 200000.00$$

$$y2 = 0.00140044$$

$$sh2 = 0.0044814$$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$$lo/lou,min = lb/lb,min = 0.30$$

$$su2 = 0.4 * esu2\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y2, sh2, ft2, fy2$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs\_jacket * Asl,com,jacket + fs\_core * Asl,com,core) / Asl,com = 389.0139$$

$$\text{with } Es2 = (Es\_jacket * Asl,com,jacket + Es\_core * Asl,com,core) / Asl,com = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$$lo/lou,min = lb/ld = 0.30$$

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$yv, shv, ftv, fyv$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs\_jacket * Asl,mid,jacket + fs\_mid * Asl,mid,core) / Asl,mid = 389.0139$$

$$\text{with } Esv = (Es\_jacket * Asl,mid,jacket + Es\_mid * Asl,mid,core) / Asl,mid = 200000.00$$

$$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02528302$$

$$2 = Asl,com / (b * d) * (fs2 / fc) = 0.04909935$$

$$v = Asl,mid / (b * d) * (fsv / fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02869934$$

$$2 = Asl,com / (b * d) * (fs2 / fc) = 0.0557338$$

$$v = Asl,mid / (b * d) * (fsv / fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Mu1-

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_s,jacket * A_{sl,ten,jacket} + f_s,core * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es1 = (E_s,jacket * A_{sl,ten,jacket} + E_s,core * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (f_s,jacket * A_{sl,com,jacket} + f_s,core * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with  $Es2 = (E_s,jacket * A_{sl,com,jacket} + E_s,core * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

su (4.9) = 0.21669624

Mu = MRc (4.14) = 8.1540E+008

u = su (4.1) = 9.2452857E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu2+  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006

Mu = 4.9689E+008  
-----

with full section properties:

b = 750.00

d = 707.00

d' = 43.00

v = 0.00093001

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu: cu\* = shear\_factor \* Max( cu, cc) = 0.01241186

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY: cu = 0.01241186

we ((5.4c), TBDY) = ase\* sh,min\*fywe/fce+ Min( fx, fy) = 0.0496383

where f = af\*pf\*ffe/fce is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = N_L * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f,e} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (\geq a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

psh2 ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 =  $0.4 * esu1_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $Min(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs_{jacket} * A_{sl,ten,jacket} + fs_{core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with Es1 =  $(Es_{jacket} * A_{sl,ten,jacket} + Es_{core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 =  $0.4 * esu2_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $Min(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 =  $(fs_{jacket} * A_{sl,com,jacket} + fs_{core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with Es2 =  $(Es_{jacket} * A_{sl,com,jacket} + Es_{core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv =  $0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY  
For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $Min(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv =  $(fs_{jacket} * A_{sl,mid,jacket} + fs_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$

with Esv =  $(Es_{jacket} * A_{sl,mid,jacket} + Es_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$

1 =  $A_{sl,ten} / (b * d) * (fs1 / fc) = 0.02528302$

2 =  $A_{sl,com} / (b * d) * (fs2 / fc) = 0.04909935$

v =  $A_{sl,mid} / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

b = 690.00

d = 677.00

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.0557338$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $Mu_2$ -

Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$fc = 33.00$$

$$co (5A.5, TBDY) = 0.002$$

$$\text{Final value of } cu: cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } cu = 0.01241186$$

$$w_e ((5.4c), TBDY) = ase * sh, \min * fy_w / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff,e = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$$af = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } pf = 2tf/bw = 0.005$$

$$bw = 400.00$$

$$\text{effective stress from (A.35), } ff,e = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } tf = NL * t * \text{Cos}(b1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$ase \text{ ((5.4d), TBDY)} = (ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$$

$$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$ase2 \text{ (>=ase1)} = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$l_o / l_{ou,min} = l_b / d = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs_{jacket} \cdot Asl_{ten,jacket} + fs_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 389.0139$

with  $Es1 = (Es_{jacket} \cdot Asl_{ten,jacket} + Es_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/lb_{,min} = 0.30$

$su2 = 0.4 \cdot esu2\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs_{jacket} \cdot Asl_{com,jacket} + fs_{core} \cdot Asl_{com,core}) / Asl_{com} = 389.0139$

with  $Es2 = (Es_{jacket} \cdot Asl_{com,jacket} + Es_{core} \cdot Asl_{com,core}) / Asl_{com} = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/ld = 0.30$

$suv = 0.4 \cdot esuv\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} \cdot Asl_{mid,jacket} + fs_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 389.0139$

with  $Es_v = (Es_{jacket} \cdot Asl_{mid,jacket} + Es_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 200000.00$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.09206128$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.04740567$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$fcc$  (5A.2, TBDY) = 34.43547

$cc$  (5A.5, TBDY) = 0.00243499

$c$  = confinement factor = 1.0435

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.11310683$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.05824278$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs_{y2}$  - LHS eq.(4.5) is satisfied

--->

$su$  (4.9) = 0.21669624

$Mu = MRc$  (4.14) = 8.1540E+008

$u = su$  (4.1) = 9.2452857E-006

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898\text{E}+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898\text{E}+006$

$V_{r1} = V_{Co1} ((10.3), \text{ASCE } 41-17) = k_{nl} * V_{Co10}$

$V_{Co10} = 1.0898\text{E}+006$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ '

where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{\text{jacket}} * \text{Area}_{\text{jacket}} + f_c'_{\text{core}} * \text{Area}_{\text{core}}) / \text{Area}_{\text{section}} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.777$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,\text{jacket}} + V_{s,\text{core}} = 901155.609$

where:

$V_{s,\text{jacket}} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.16666667$

$V_{s,\text{core}} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$s/d = 0.56818182$

$V_f ((11-3)-(11.4), \text{ACI } 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression,

where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a_1)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L * t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} ((11-5), \text{ACI } 440) = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $bw = 400.00$

Calculation of Shear Strength at edge 2,  $V_r2 = 1.0898E+006$   
 $V_r2 = V_{Col} ((10.3), ASCE 41-17) = knl * V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)  
Mean concrete strength:  $f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)

$M / Vd = 4.00$

$\mu_u = 1518.776$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$s/d = 0.56818182$

$V_f ((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f / s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression,  
where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a_1)$ , is implemented for every different fiber orientation  $a_i$ ,  
as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha_1 = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} ((11-5), ACI 440) = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

-----  
-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
At local axis: 2

-----  
-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

Section Type: rcjcs

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
-----  
Stepwise Properties

Bending Moment,  $M = -502156.692$

Shear Force,  $V_2 = -7630.77$

Shear Force,  $V_3 = 206.4342$

Axial Force,  $F = -19223.50$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $A_{sc} = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten = 1137.257$

-Compression:  $Asl,com = 2208.54$

-Middle:  $Asl,mid = 2007.478$

Longitudinal External Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,jacket = 829.3805$

-Compression:  $Asl,com,jacket = 1746.726$

-Middle:  $Asl,mid,jacket = 1545.664$

Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,core = 307.8761$

-Compression:  $Asl,com,core = 461.8141$

-Middle:  $Asl,mid,core = 461.8141$

Mean Diameter of Tension Reinforcement,  $DbL = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u,R = 1.0^*$   $u = 0.03194781$

$u = y + p = 0.03194781$

- Calculation of  $y$  -

$y = (My*Ls/3)/Eleff = 0.00194781$  ((4.29),Biskinis Phd))

$My = 3.6682E+008$

$Ls = M/V$  (with  $Ls > 0.1*L$  and  $Ls < 2*L$ ) = 2432.526

From table 10.5, ASCE 41\_17:  $Eleff = factor*Ec*Ig = 1.5270E+014$

factor = 0.30

$Ag = 440000.00$

Mean concrete strength:  $fc' = (fc'_jacket*Area_jacket + fc'_core*Area_core)/Area_section = 33.00$

$N = 19223.50$

$Ec*Ig = Ec_jacket*Ig_jacket + Ec_core*Ig_core = 5.0901E+014$

Calculation of Yielding Moment  $My$

Calculation of  $y$  and  $My$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $bw = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{ten}, y_{com})$

$y_{ten} = 2.7307817E-006$

with ((10.1), ASCE 41-17)  $fy = \text{Min}(fy, 1.25*fy*(b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $pt = 0.00729988$

$pc = 0.00416509$

$pv = 0.00378591$

$N = 19223.50$

$b = 750.00$

" = 0.06082037

$y_{comp} = 1.6517162E-005$

with  $fc^*$  (12.3, (ACI 440)) = 33.60672

$fc = 33.00$

$fl = 0.61848273$

$b = bmax = 750.00$

$h = hmax = 750.00$

$Ag = 0.44$

$g = pt + pc + pv = 0.01009575$

$rc = 40.00$

$Ae/Ac = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b1) = 1.00$   
 effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$   
 $f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $\gamma = 0.19186199$   
 $A = 0.01001485$   
 $B = 0.00440616$   
 with  $E_s = 200000.00$

CONFIRMATION:  $\gamma = 0.19289193 < t/d$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

- Calculation of  $\rho$  -

From table 10-8:  $\rho = 0.03$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/l_d < 1$

shear control ratio  $V_y E / V_{CoI} E = 0.49879178$

$d = d_{external} = 707.00$

$s = s_{external} = 0.00$

-  $t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$

jacket:  $s_1 = A_{v1} \cdot L_{stir1} / (s_1 \cdot A_g) = 0.00367709$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{stir1} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_1 = 100.00$

core:  $s_2 = A_{v2} \cdot L_{stir2} / (s_2 \cdot A_g) = 0.00067082$

$A_{v2} = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$L_{stir2} = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_2 = 250.00$

The term  $2 \cdot t_f / b_w \cdot (f_{fe} / f_s)$  is implemented to account for FRP contribution

where  $f = 2 \cdot t_f / b_w$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $f_{fe} / f_s$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $f_s$  of jacket is used.

$N_{UD} = 19223.50$

$A_g = 440000.00$

$f_{cE} = (f_{c,jacket} \cdot Area_{jacket} + f_{c,core} \cdot Area_{core}) / section\_area = 33.00$

$f_{yIE} = (f_{y,ext\_Long\_Reinf} \cdot Area_{ext\_Long\_Reinf} + f_{y,int\_Long\_Reinf} \cdot Area_{int\_Long\_Reinf}) / Area_{Tot\_Long\_Rein} =$

555.56

$f_{ytE} = (f_{y,ext\_Trans\_Reinf} \cdot s_1 + f_{y,int\_Trans\_Reinf} \cdot s_2) / (s_1 + s_2) = 555.56$

$\rho_l = Area_{Tot\_Long\_Rein} / (b \cdot d) = 0.01009575$

$b = 750.00$

$d = 707.00$

$f_{cE} = 33.00$

End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (a)

## Calculation No. 11

column C1, Floor 1


Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: Start

Local Axis: (3)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.

Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand, the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height, Hmax = 750.00  
Min Height, Hmin = 400.00  
Max Width, Wmax = 750.00  
Min Width, Wmin = 400.00  
Jacket Thickness, tj = 100.00  
Cover Thickness, c = 25.00  
Element Length, L = 3000.00  
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness, t = 1.00  
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions, NoDir = 1  
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers, NL = 1  
Radius of rounding corners, R = 40.00

-----  
Stepwise Properties  
-----

EDGE -A-  
Bending Moment,  $M_a = -502156.692$   
Shear Force,  $V_a = 206.4342$   
EDGE -B-  
Bending Moment,  $M_b = -114246.474$   
Shear Force,  $V_b = -206.4342$   
BOTH EDGES  
Axial Force,  $F = -19223.50$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{sl,t} = 0.00$   
-Compression:  $A_{sl,c} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{sl,ten} = 1137.257$   
-Compression:  $A_{sl,com} = 2208.54$   
-Middle:  $A_{sl,mid} = 2007.478$   
Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

-----  
New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $V_R = 1.0 \cdot V_n = 949074.782$   
 $V_n ((10.3), ASCE 41-17) = k_n \cdot V_{CoI} = 949074.782$   
 $V_{CoI} = 949074.782$   
 $k_n = 1.00$   
 $displacement\_ductility\_demand = 0.01636228$

-----  
NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

-----  
= 1 (normal-weight concrete)  
Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f_c'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)  
 $M / Vd = 4.00$   
 $M_u = 502156.692$   
 $V_u = 206.4342$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 19223.50$   
 $A_g = 300000.00$   
From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$$

$V_{s,j1} = 471238.898$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{s,j2} = 251327.412$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$$

$V_{s,c1} = 88467.249$  is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression,

where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

$$\text{orientation 1: } \alpha = b1 + 90^\circ = 90.00$$

$$V_f = \text{Min}(|V_f(45, a_1)|, |V_f(-45, a_1)|), \text{ with:}$$

$$\text{total thickness per orientation, } t_{f1} = NL * t / \text{NoDir} = 1.00$$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe}((11-5), ACI 440) = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 797164.595$$

$$b_w = 400.00$$

-----  
displacement\_ductility\_demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END A -

for rotation axis 2 and integ. section (a)

-----  
From analysis, chord rotation  $\theta = 3.1870654E-005$

$$y = (M_y * L_s / 3) / E_{eff} = 0.00194781 \text{ ((4.29), Biskinis Phd)}$$

$$M_y = 3.6682E+008$$

$$L_s = M/V \text{ (with } L_s > 0.1 * L \text{ and } L_s < 2 * L) = 2432.526$$

$$\text{From table 10.5, ASCE 41_17: } E_{eff} = \text{factor} * E_c * I_g = 1.5270E+014$$

$$\text{factor} = 0.30$$

$$A_g = 440000.00$$

$$\text{Mean concrete strength: } f_c' = (f_c'_{jacket} * \text{Area}_{jacket} + f_c'_{core} * \text{Area}_{core}) / \text{Area}_{section} = 33.00$$

$$N = 19223.50$$

$$E_c * I_g = E_c * I_{g,jacket} + E_c * I_{g,core} = 5.0901E+014$$
  
-----

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7307817\text{E-}006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 19223.50$

$b = 750.00$

" = 0.06082037

$y_{\text{comp}} = 1.6517162\text{E-}005$

with  $f_c^*$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e/A_c = 0.31291181$

Effective FRP thickness,  $t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$

effective strain from (12.5) and (12.12),  $e_{fe} = 0.004$

$f_u = 0.009$

$E_f = 82000.00$

$E_c = 26999.444$

$y = 0.19186199$

$A = 0.01001485$

$B = 0.00440616$

with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

**Calculation No. 12**

column C1, Floor 1


Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity ( $\theta_u$ )

Edge: Start

Local Axis: (3)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $NoDir = 1$   
Fiber orientations,  $bi: 0.00^\circ$   
Number of layers,  $NL = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 3  
EDGE -A-  
Shear Force,  $V_a = -0.00017144$   
EDGE -B-  
Shear Force,  $V_b = 0.00017144$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(Mu_{1+} , Mu_{1-}) = 8.1540E+008$   
 $Mu_{1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $Mu_{1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(Mu_{2+} , Mu_{2-}) = 8.1540E+008$   
 $Mu_{2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $Mu_{2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $Mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $Mu = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$   
 $f_c = 33.00$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N_L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} ((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1}/(A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} (\text{Length of stirrups along } Y) = 2060.00$$

$$A_{stir1} (\text{stirrups area}) = 78.53982$$

$$p_{sh2} (5.4d) = L_{stir2} * A_{stir2}/(A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} (\text{Length of stirrups along } Y) = 1468.00$$

$$\text{Astir2 (stirrups area)} = 50.26548$$

$$\text{psh}_y * \text{Fywe} = \text{psh}_1 * \text{Fywe}_1 + \text{ps}_2 * \text{Fywe}_2 = 3.0194$$

$$\text{psh}_1 ((5.4d), \text{TBDY}) = \text{Lstir}_1 * \text{Astir}_1 / (\text{Asec} * \text{s}_1) = 0.00367709$$

$$\text{Lstir}_1 (\text{Length of stirrups along X}) = 2060.00$$

$$\text{Astir}_1 (\text{stirrups area}) = 78.53982$$

$$\text{psh}_2 ((5.4d), \text{TBDY}) = \text{Lstir}_2 * \text{Astir}_2 / (\text{Asec} * \text{s}_2) = 0.00067082$$

$$\text{Lstir}_2 (\text{Length of stirrups along X}) = 1468.00$$

$$\text{Astir}_2 (\text{stirrups area}) = 50.26548$$

$$\text{Asec} = 440000.00$$

$$\text{s}_1 = 100.00$$

$$\text{s}_2 = 250.00$$

$$\text{fywe}_1 = 694.45$$

$$\text{fywe}_2 = 694.45$$

$$\text{fce} = 33.00$$

$$\text{From } ((5.A.5), \text{TBDY}), \text{TBDY: } \text{cc} = 0.00243499$$

$$\text{c} = \text{confinement factor} = 1.0435$$

$$\text{y}_1 = 0.00140044$$

$$\text{sh}_1 = 0.0044814$$

$$\text{ft}_1 = 466.8167$$

$$\text{fy}_1 = 389.0139$$

$$\text{su}_1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/ld} = 0.30$$

$$\text{su}_1 = 0.4 * \text{esu}_1 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_1 \text{ nominal} = 0.08,$$

For calculation of esu1\_nominal and y1, sh1, ft1, fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

$$\text{y}_1, \text{sh}_1, \text{ft}_1, \text{fy}_1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_1 = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{ten, jacket}} + \text{fs}_{\text{core}} * \text{Asl}_{\text{ten, core}}) / \text{Asl}_{\text{ten}} = 389.0139$$

$$\text{with } \text{Es}_1 = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{ten, jacket}} + \text{Es}_{\text{core}} * \text{Asl}_{\text{ten, core}}) / \text{Asl}_{\text{ten}} = 200000.00$$

$$\text{y}_2 = 0.00140044$$

$$\text{sh}_2 = 0.0044814$$

$$\text{ft}_2 = 466.8167$$

$$\text{fy}_2 = 389.0139$$

$$\text{su}_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/lb, min} = 0.30$$

$$\text{su}_2 = 0.4 * \text{esu}_2 \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_2 \text{ nominal} = 0.08,$$

For calculation of esu2\_nominal and y2, sh2, ft2, fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

$$\text{y}_2, \text{sh}_2, \text{ft}_2, \text{fy}_2, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_2 = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{com, jacket}} + \text{fs}_{\text{core}} * \text{Asl}_{\text{com, core}}) / \text{Asl}_{\text{com}} = 389.0139$$

$$\text{with } \text{Es}_2 = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{com, jacket}} + \text{Es}_{\text{core}} * \text{Asl}_{\text{com, core}}) / \text{Asl}_{\text{com}} = 200000.00$$

$$\text{y}_v = 0.00140044$$

$$\text{sh}_v = 0.0044814$$

$$\text{ft}_v = 466.8167$$

$$\text{fy}_v = 389.0139$$

$$\text{suv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou, min} = \text{lb/ld} = 0.30$$

$$\text{suv} = 0.4 * \text{esuv}_v \text{ nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esuv}_v \text{ nominal} = 0.08,$$

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv, ftv, fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

$$\text{y}_v, \text{sh}_v, \text{ft}_v, \text{fy}_v, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_v = (\text{fs}_{\text{jacket}} * \text{Asl}_{\text{mid, jacket}} + \text{fs}_{\text{mid}} * \text{Asl}_{\text{mid, core}}) / \text{Asl}_{\text{mid}} = 389.0139$$

$$\text{with } \text{Es}_v = (\text{Es}_{\text{jacket}} * \text{Asl}_{\text{mid, jacket}} + \text{Es}_{\text{mid}} * \text{Asl}_{\text{mid, core}}) / \text{Asl}_{\text{mid}} = 200000.00$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02528302$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.04909935$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02869934$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.0557338$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$\mu_u = M R_c (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{u1}$ -

Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$\mu_u = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

From EC8 A4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_u,f = 840.00$   
 $E_f = 82000.00$   
 $u,f = 0.015$

$ase((5.4d), \text{TBDY}) = (ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), \text{TBDY}) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_d = 0.30$$

$$s_u1 = 0.4 * e_{su1,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su1,nominal} = 0.08$ ,

For calculation of  $e_{su1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered  
characteristic value  $f_{sy1} = f_{s1}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s1} = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$$

$$\text{with } E_{s1} = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s,com,jacket} + f_{s,core} * A_{s,com,core}) / A_{s,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s,com,jacket} + E_{s,core} * A_{s,com,core}) / A_{s,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{uv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s,mid,jacket} + f_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s,mid,jacket} + E_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 200000.00$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.09206128$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.04740567$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.11310683$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.05824278$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{2+}$

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 8.4959181E-006$$

$$\mu_u = 4.9689E+008$$

with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered

characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{s2} = (f_{s,jacket} \cdot A_{s1,com,jacket} + f_{s,core} \cdot A_{s1,com,core})/A_{s1,com} = 389.0139$

with  $E_{s2} = (E_{s,jacket} \cdot A_{s1,com,jacket} + E_{s,core} \cdot A_{s1,com,core})/A_{s1,com} = 200000.00$

$y_v = 0.00140044$

$sh_v = 0.0044814$

$ft_v = 466.8167$

$fy_v = 389.0139$

$s_{uv} = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$s_{uv} = 0.4 \cdot e_{suv,nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered

characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{sv} = (f_{s,jacket} \cdot A_{s,mid,jacket} + f_{s,mid} \cdot A_{s,mid,core})/A_{s,mid} = 389.0139$

with  $E_{sv} = (E_{s,jacket} \cdot A_{s,mid,jacket} + E_{s,mid} \cdot A_{s,mid,core})/A_{s,mid} = 200000.00$

$1 = A_{s1,ten}/(b \cdot d) \cdot (f_{s1}/f_c) = 0.02528302$

$2 = A_{s1,com}/(b \cdot d) \cdot (f_{s2}/f_c) = 0.04909935$

$v = A_{s1,mid}/(b \cdot d) \cdot (f_{sv}/f_c) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$f_{cc} (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = A_{s1,ten}/(b \cdot d) \cdot (f_{s1}/f_c) = 0.02869934$

$2 = A_{s1,com}/(b \cdot d) \cdot (f_{s2}/f_c) = 0.0557338$

$v = A_{s1,mid}/(b \cdot d) \cdot (f_{sv}/f_c) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$s_u (4.9) = 0.1476063$

$\mu_u = M_{Rc} (4.14) = 4.9689E+008$

$u = s_u (4.1) = 8.4959181E-006$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----  
-----

-----  
Calculation of  $\mu_{u2}$ -  
-----  
-----  
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$u = 9.2452857E-006$

$\mu_u = 8.1540E+008$

-----  
with full section properties:

$b = 400.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00174378$

$N = 16273.607$

$f_c = 33.00$

$cc (5A.5, TBDY) = 0.002$

Final value of  $\mu_u$ :  $\mu_u^* = \text{shear\_factor} \cdot \text{Max}(c_u, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $c_u = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$R = 40.00$

Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b_1) = 1.00$

$f_u, f = 840.00$

$E_f = 82000.00$

$u, f = 0.015$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$

$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

psh<sub>y</sub>\*Fywe = psh<sub>1</sub>\*Fywe<sub>1</sub>+ps<sub>2</sub>\*Fywe<sub>2</sub> = 3.0194  
psh<sub>1</sub> ((5.4d), TBDY) = Lstir<sub>1</sub>\*Astir<sub>1</sub>/(Asec\*s<sub>1</sub>) = 0.00367709  
Lstir<sub>1</sub> (Length of stirrups along X) = 2060.00  
Astir<sub>1</sub> (stirrups area) = 78.53982  
psh<sub>2</sub> ((5.4d), TBDY) = Lstir<sub>2</sub>\*Astir<sub>2</sub>/(Asec\*s<sub>2</sub>) = 0.00067082  
Lstir<sub>2</sub> (Length of stirrups along X) = 1468.00  
Astir<sub>2</sub> (stirrups area) = 50.26548

Asec = 440000.00

s<sub>1</sub> = 100.00

s<sub>2</sub> = 250.00

fywe<sub>1</sub> = 694.45

fywe<sub>2</sub> = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y<sub>1</sub> = 0.00140044

sh<sub>1</sub> = 0.0044814

ft<sub>1</sub> = 466.8167

fy<sub>1</sub> = 389.0139

su<sub>1</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su<sub>1</sub> = 0.4\*esu<sub>1\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>1\_nominal</sub> = 0.08,

For calculation of esu<sub>1\_nominal</sub> and y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, it is considered  
characteristic value fsy<sub>1</sub> = fs<sub>1</sub>/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>1</sub> = (fs<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + fs<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 389.0139

with Es<sub>1</sub> = (Es<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + Es<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 200000.00

y<sub>2</sub> = 0.00140044

sh<sub>2</sub> = 0.0044814

ft<sub>2</sub> = 466.8167

fy<sub>2</sub> = 389.0139

su<sub>2</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su<sub>2</sub> = 0.4\*esu<sub>2\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>2\_nominal</sub> = 0.08,

For calculation of esu<sub>2\_nominal</sub> and y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, it is considered  
characteristic value fsy<sub>2</sub> = fs<sub>2</sub>/1.2, from table 5.1, TBDY.

y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>2</sub> = (fs<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + fs<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 389.0139

with Es<sub>2</sub> = (Es<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + Es<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 200000.00

y<sub>v</sub> = 0.00140044

sh<sub>v</sub> = 0.0044814

ft<sub>v</sub> = 466.8167

fy<sub>v</sub> = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv = 0.4\*esuv<sub>nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv<sub>nominal</sub> = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv<sub>nominal</sub> and y<sub>v</sub>, sh<sub>v</sub>,ft<sub>v</sub>,fy<sub>v</sub>, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fsv = (fs<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + fs<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 389.0139

with Es<sub>v</sub> = (Es<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + Es<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 200000.00

1 = Asl<sub>ten</sub>/(b\*d)\*(fs<sub>1</sub>/fc) = 0.09206128

2 = Asl<sub>com</sub>/(b\*d)\*(fs<sub>2</sub>/fc) = 0.04740567

$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.08368017$   
 and confined core properties:  
 $b = 340.00$   
 $d = 677.00$   
 $d' = 13.00$   
 $f_{cc} (5A.2, TBDY) = 34.43547$   
 $cc (5A.5, TBDY) = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$   
 $1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.11310683$   
 $2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.05824278$   
 $v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.10280977$   
 Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)

--->  
 $v < v_{s,y2}$  - LHS eq.(4.5) is satisfied  
 --->  
 $su (4.9) = 0.21669624$   
 $Mu = MRc (4.14) = 8.1540E+008$   
 $u = su (4.1) = 9.2452857E-006$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$   
 $V_{r1} = V_{Col} ((10.3), ASCE 41-17) = k_{nl} * V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)  
 Mean concrete strength:  $f'_c = (f'_{c,jacket} * Area_{jacket} + f'_{c,core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$   
 $Mu = 1518.009$   
 $Vu = 0.00017144$   
 $d = 0.8 * h = 600.00$   
 $Nu = 16273.607$   
 $Ag = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:  
 $V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col,j1 = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col,j2 = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{sc1} + V_{sc2} = 98297.73$   
 $V_{sc1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 45^\circ$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\lambda = 1$  (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/d = 4.00$$

$$M_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$$

$V_{sj1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{sj2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

d = 440.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c1 is multiplied by Col,c1 = 1.00  
 s/d = 0.56818182  
 Vs,c2 = 0.00 is calculated for section flange core, with:  
 d = 160.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c2 is multiplied by Col,c2 = 0.00  
 s/d = 1.5625  
 Vf ((11-3)-(11.4), ACI 440) = 463792.00  
 f = 0.95, for fully-wrapped sections  
 wf/sf = 1 (FRP strips adjacent to one another).  
 In (11.3) sin + cos is replaced with (cot + cota)sina which is more a generalised expression,  
 where is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function Vf( , ), is implemented for every different fiber orientation ai,  
 as well as for 2 crack directions, = 45° and = -45° to take into consideration the cyclic seismic loading.  
 orientation 1: 1 = b1 + 90° = 90.00  
 Vf = Min(|Vf(45, 1)|, |Vf(-45,a1)|), with:  
 total thickness per orientation, tf1 = NL\*t/NoDir = 1.00  
 dfv = d (figure 11.2, ACI 440) = 707.00  
 ffe ((11-5), ACI 440) = 328.00  
 Ef = 82000.00  
 fe = 0.004, from (11.6a), ACI 440  
 with fu = 0.009  
 From (11-11), ACI 440: Vs + Vf <= 915872.391  
 bw = 400.00

-----  
 End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At local axis: 3

-----  
 Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At Shear local axis: 2  
 (Bending local axis: 3)  
 Section Type: rcjics

Constant Properties

-----  
 Knowledge Factor, = 0.87  
 Mean strength values are used for both shear and moment calculations.  
 Consequently:  
 Jacket  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 Existing Column  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 #####  
 Note: Especially for the calculation of moment strengths,  
 the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14  
 Jacket  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 Existing Column  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 #####  
 Max Height, Hmax = 750.00

Min Height, Hmin = 400.00  
Max Width, Wmax = 750.00  
Min Width, Wmin = 400.00  
Jacket Thickness, tj = 100.00  
Cover Thickness, c = 25.00  
Mean Confinement Factor overall section = 1.0435  
Element Length, L = 3000.00  
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with lo/lo,min = 0.30  
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness, t = 1.00  
Tensile Strength, ffu = 840.00  
Tensile Modulus, Ef = 82000.00  
Elongation, efu = 0.009  
Number of directions, NoDir = 1  
Fiber orientations, bi: 0.00°  
Number of layers, NL = 1  
Radius of rounding corners, R = 40.00

-----  
Stepwise Properties  
-----

At local axis: 2  
EDGE -A-  
Shear Force, Va = -0.0001715  
EDGE -B-  
Shear Force, Vb = 0.0001715  
BOTH EDGES  
Axial Force, F = -16273.607  
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension: Aslt = 0.00  
-Compression: Aslc = 5353.274  
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension: Asl,ten = 1137.257  
-Compression: Asl,com = 2208.54  
-Middle: Asl,mid = 2007.478  
-----  
-----

Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(\mu_{u1+}, \mu_{u1-}) = 8.1540\text{E}+008$   
 $\mu_{u1+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $\mu_{u1-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(\mu_{u2+}, \mu_{u2-}) = 8.1540\text{E}+008$   
 $\mu_{u2+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $\mu_{u2-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{u1+}$   
-----  
-----

Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006  
Mu = 4.9689E+008

with full section properties:

b = 750.00  
d = 707.00  
d' = 43.00  
v = 0.00093001  
N = 16273.607  
fc = 33.00  
co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase * sh, \min * fy_{we} / f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af * pf * ff_e / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

bw = 400.00

effective stress from (A.35),  $ff_e = 765.1636$

fy = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

bw = 400.00

effective stress from (A.35),  $ff_e = 765.1636$

R = 40.00

Effective FRP thickness,  $tf = NL * t * \text{Cos}(b1) = 1.00$

fu,f = 840.00

Ef = 82000.00

u,f = 0.015

ase ((5.4d), TBDY) =  $(ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$

ase1 =  $\text{Max}(((A_{conf, \max 1} - A_{noConf1}) / A_{conf, \max 1}) * (A_{conf, \min 1} / A_{conf, \max 1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf, \min 1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf, \max 1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

ase2 ( $\geq ase1$ ) =  $\text{Max}(((A_{conf, \max 2} - A_{noConf2}) / A_{conf, \max 2}) * (A_{conf, \min 2} / A_{conf, \max 2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf, \min 2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf, \max 2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

$$psh_{min} * Fy_{we} = \text{Min}(psh_x * Fy_{we}, psh_y * Fy_{we}) = 3.0194$$

Expression (5.4d) for  $psh_{min} * Fy_{we}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$psh_x * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along Y)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ (5.4d)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along Y)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$psh_y * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along X)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ ((5.4d), TBDY)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along X)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$Asec = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$fy_{we1} = 694.45$$

$$fy_{we2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/ld = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu1_{nominal} = 0.08,$$

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs1 = (fs_{jacket} * Asl_{ten,jacket} + fs_{core} * Asl_{ten,core}) / Asl_{ten} = 389.0139$$

$$\text{with } Es1 = (Es_{jacket} * Asl_{ten,jacket} + Es_{core} * Asl_{ten,core}) / Asl_{ten} = 200000.00$$

$$y2 = 0.00140044$$

$$sh2 = 0.0044814$$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/lb_{min} = 0.30$$

$$su2 = 0.4 * esu2_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

$$\text{From table 5A.1, TBDY: } esu2_{nominal} = 0.08,$$

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$$y1, sh1, ft1, fy1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (lb/ld)^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } fs2 = (fs_{jacket} * Asl_{com,jacket} + fs_{core} * Asl_{com,core}) / Asl_{com} = 389.0139$$

$$\text{with } Es2 = (Es_{jacket} * Asl_{com,jacket} + Es_{core} * Asl_{com,core}) / Asl_{com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$su_v = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fsjacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.0557338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

v < vs,y2 - LHS eq.(4.5) is satisfied

---->

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu1-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008  
-----

with full section properties:

b = 400.00

d = 707.00

d' = 43.00

v = 0.00174378

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} \cdot \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase \cdot sh_{\min} \cdot fy_{we}/f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af \cdot pf \cdot f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$

Effective FRP thickness,  $tf = NL*tf*Cos(b1) = 1.00$

$f_u,f = 840.00$

$E_f = 82000.00$

$u,f = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2$  ( $\geq ase1$ ) =  $\text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$psh_{min}*F_{ywe} = \text{Min}(psh_x*F_{ywe}, psh_y*F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min}*F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$psh_x*F_{ywe} = psh1*F_{ywe1} + ps2*F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1}*A_{stir1}/(A_{sec}*s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2}*A_{stir2}/(A_{sec}*s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$psh_y*F_{ywe} = psh1*F_{ywe1} + ps2*F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1}*A_{stir1}/(A_{sec}*s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2}*A_{stir2}/(A_{sec}*s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY  
For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00  
d = 677.00  
d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$s_u$  (4.9) = 0.21669624

$M_u = M_{Rc}$  (4.14) = 8.1540E+008

$u = s_u$  (4.1) = 9.2452857E-006

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u2+}$   
-----  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$

$M_u = 4.9689E+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $\alpha$ :  $\alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\alpha = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $\alpha s_e * \text{sh\_min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha^* p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$

$b_{\text{max}} = 750.00$

$h_{\text{max}} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$

$b_{\text{max}} = 750.00$

$h_{\text{max}} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$R = 40.00$

Effective FRP thickness,  $t_f = N L^* t^* \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$\alpha_s$  ((5.4d), TBDY) =  $(\alpha s_1^* A_{\text{ext}} + \alpha s_2^* A_{\text{int}})/A_{\text{sec}} = 0.45746528$

$\alpha s_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{u,min} = lb/ld = 0.30$

$su1 = 0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/lb,min = 0.30$$

$$su2 = 0.4*esu2\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs,jacket*Asl,com,jacket + fs,core*Asl,com,core)/Asl,com = 389.0139$$

$$\text{with } Es2 = (Es,jacket*Asl,com,jacket + Es,core*Asl,com,core)/Asl,com = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lou,min = lb/ld = 0.30$$

$$suv = 0.4*esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25*(lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs,jacket*Asl,mid,jacket + fs,mid*Asl,mid,core)/Asl,mid = 389.0139$$

$$\text{with } Esv = (Es,jacket*Asl,mid,jacket + Es,mid*Asl,mid,core)/Asl,mid = 200000.00$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02528302$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.04909935$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl,ten/(b*d)*(fs1/fc) = 0.02869934$$

$$2 = Asl,com/(b*d)*(fs2/fc) = 0.0557338$$

$$v = Asl,mid/(b*d)*(fsv/fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

---->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu2-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\alpha_w \text{ ((5.4c), TBDY) } = \alpha_{se} * \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* \rho^* f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } \rho_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } \rho_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t \cos(b_1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY) } = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{conf, \max 1} - A_{noConf1}) / A_{conf, \max 1}) * (A_{conf, \min 1} / A_{conf, \max 1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf, \min 1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf, \max 1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_{se2} (> \alpha_{se1}) = \text{Max}(((A_{conf, \max 2} - A_{noConf2}) / A_{conf, \max 2}) * (A_{conf, \min 2} / A_{conf, \max 2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf, \min 2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf, \max 2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\rho_{sh, \min} * f_{ywe} = \text{Min}(\rho_{sh, x} * f_{ywe}, \rho_{sh, y} * f_{ywe}) = 3.0194$$

Expression (5.4d) for  $\rho_{sh, \min} * f_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without

earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv$ ,  $shv$ ,  $ftv$ ,  $fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1$ ,  $ft1$ ,  $fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs\_jacket * Asl\_mid\_jacket + fs\_mid * Asl\_mid\_core) / Asl\_mid = 389.0139$$

$$\text{with } Esv = (Es\_jacket * Asl\_mid\_jacket + Es\_mid * Asl\_mid\_core) / Asl\_mid = 200000.00$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.09206128$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.04740567$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.11310683$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.05824278$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $Vr = \text{Min}(Vr1, Vr2) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $Vr1 = 1.0898E+006$

$$Vr1 = VCol ((10.3), ASCE 41-17) = knl * VCol0$$

$$VCol0 = 1.0898E+006$$

$$knl = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $Vs = Av * fy * d / s$ ' is replaced by ' $Vs + f * Vf$ ' where  $Vf$  is the contribution of FRPs (11.3), ACI 440).

$$= 1 \text{ (normal-weight concrete)}$$

Mean concrete strength:  $fc' = (fc'_jacket * Area\_jacket + fc'_core * Area\_core) / Area\_section = 33.00$ , but  $fc'^{0.5} <= 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/d = 4.00$$

$$Mu = 1518.777$$

$$Vu = 0.0001715$$

$$d = 0.8 * h = 600.00$$

$$Nu = 16273.607$$

$$Ag = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } Vs = Vs\_jacket + Vs\_core = 901155.609$$

where:

$$Vs\_jacket = Vs\_j1 + Vs\_j2 = 802857.879$$

$Vs\_j1 = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$Av = 157079.633$$

$$fy = 555.56$$

$$s = 100.00$$

$Vs\_j1$  is multiplied by  $Col\_j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$V_f((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a_i)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}((11-5), ACI 440) = 328.00$

$$E_f = 82000.00$$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}((10.3), ASCE 41-17) = knl \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\lambda = 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.776$$

$$V_u = 0.0001715$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b1 + 90^\circ = 90.00$

$$V_f = \text{Min}(|V_f(45, \alpha)|, |V_f(-45, \alpha)|), \text{ with:}$$

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

with  $f_u = 0.009$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$b_w = 400.00$$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 2  
-----

-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

Section Type: rcjlc3

Constant Properties  
-----

Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$   
Steel Elasticity,  $E_s = 200000.00$   
Max Height,  $H_{max} = 750.00$   
Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

#### Stepwise Properties

Bending Moment,  $M = -2.3693E+007$   
Shear Force,  $V_2 = -7630.77$   
Shear Force,  $V_3 = 206.4342$   
Axial Force,  $F = -19223.50$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$   
Longitudinal External Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,jacket} = 829.3805$   
-Compression:  $As_{c,com,jacket} = 1746.726$   
-Middle:  $As_{c,mid,jacket} = 1545.664$   
Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,core} = 307.8761$   
-Compression:  $As_{c,com,core} = 461.8141$   
-Middle:  $As_{c,mid,core} = 461.8141$   
Mean Diameter of Tension Reinforcement,  $Db_L = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u_R = 1.0^*$   $u = 0.03248626$   
 $u = y + p = 0.03248626$

- Calculation of  $y$  -

$y = (M_y * L_s / 3) / E_{eff} = 0.00248626$  ((4.29), Biskinis Phd))  
 $M_y = 3.6682E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 3104.971  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
factor = 0.30  
 $A_g = 440000.00$   
Mean concrete strength:  $fc' = (fc'_{jacket} * Area_{jacket} + fc'_{core} * Area_{core}) / Area_{section} = 33.00$

$$N = 19223.50$$

$$E_c \cdot I_g = E_c \cdot I_{g\_jacket} + E_c \cdot I_{g\_core} = 5.0901E+014$$

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$$

$$y_{\text{ten}} = 2.7307817E-006$$

$$\text{with } ((10.1), \text{ASCE 41-17}) f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$$

$$d = 707.00$$

$$y = 0.19403023$$

$$A = 0.01021225$$

$$B = 0.00452265$$

$$\text{with } p_t = 0.00729988$$

$$p_c = 0.00416509$$

$$p_v = 0.00378591$$

$$N = 19223.50$$

$$b = 750.00$$

$$" = 0.06082037$$

$$y_{\text{comp}} = 1.6517162E-005$$

$$\text{with } f_c^* (12.3, \text{ACI 440}) = 33.60672$$

$$f_c = 33.00$$

$$f_l = 0.61848273$$

$$b = b_{\text{max}} = 750.00$$

$$h = h_{\text{max}} = 750.00$$

$$A_g = 0.44$$

$$g = p_t + p_c + p_v = 0.01009575$$

$$r_c = 40.00$$

$$A_e/A_c = 0.31291181$$

$$\text{Effective FRP thickness, } t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$$

$$\text{effective strain from (12.5) and (12.12), } e_{fe} = 0.004$$

$$f_u = 0.009$$

$$E_f = 82000.00$$

$$E_c = 26999.444$$

$$y = 0.19186199$$

$$A = 0.01001485$$

$$B = 0.00440616$$

$$\text{with } E_s = 200000.00$$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

- Calculation of  $p$  -

From table 10-8:  $p = 0.03$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/d < 1$

$$\text{shear control ratio } V_y E / C_o I_o E = 0.49879178$$

$$d = d_{\text{external}} = 707.00$$

$$s = s_{\text{external}} = 0.00$$

$$- t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$$

$$\text{jacket: } s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s1 = 100.00$$

$$\text{core: } s2 = Av2 * Lstir2 / (s2 * Ag) = 0.00067082$$

$Av2 = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$Lstir2 = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s2 = 250.00$$

The term  $2 * tf / bw * (ffe / fs)$  is implemented to account for FRP contribution

where  $f = 2 * tf / bw$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $ffe / fs$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $fs$  of jacket is used.

$$NUD = 19223.50$$

$$Ag = 440000.00$$

$$fcE = (fc\_jacket * Area\_jacket + fc\_core * Area\_core) / section\_area = 33.00$$

$$fyIE = (fy\_ext\_Long\_Reinf * Area\_ext\_Long\_Reinf + fy\_int\_Long\_Reinf * Area\_int\_Long\_Reinf) / Area\_Tot\_Long\_Rein = 555.56$$

$$fytE = (fy\_ext\_Trans\_Reinf * s1 + fy\_int\_Trans\_Reinf * s2) / (s1 + s2) = 555.56$$

$$pl = Area\_Tot\_Long\_Rein / (b * d) = 0.01009575$$

$$b = 750.00$$

$$d = 707.00$$

$$fcE = 33.00$$

End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (a)

## Calculation No. 13

column C1, Floor 1



Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: End

Local Axis: (2)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2  
Integration Section: (b)  
Section Type: rcjcs

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$   
Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.  
Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand,  
the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as  
Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{ou,min} = l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

EDGE -A-

Bending Moment,  $M_a = -2.3693E+007$

Shear Force,  $V_a = -7630.77$

EDGE -B-

Bending Moment,  $M_b = 793215.62$

Shear Force,  $V_b = 7630.77$

BOTH EDGES

Axial Force,  $F = -19223.50$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{t,ten} = 1137.257$

-Compression:  $As_{c,com} = 2208.54$

-Middle:  $As_{c,mid} = 2007.478$

Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $VR = 1.0 \cdot V_n = 1.1010E+006$

$V_n$  ((10.3), ASCE 41-17) =  $k_n \cdot V_{CoIO} = 1.1010E+006$

$V_{CoI} = 1.1010E+006$

$k_n = 1.00$

displacement\_ductility\_demand = 0.10358096

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 2.00$

$\mu_u = 793215.62$

$V_u = 7630.77$

$d = 0.8 \cdot h = 600.00$

$N_u = 19223.50$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$

$V_{s,j1} = 251327.412$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col_{j1} = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 471238.898$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 500.00$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col_{j2} = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col_{c1} = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 88467.249$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 500.00$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col_{c2} = 1.00$

$s/d = 0.56818182$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \csc \theta) \sin \alpha$  which is more a generalised expression, where  $\theta$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $\theta$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_f = NL \cdot t / N_{\text{Dir}} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 797164.595$

$b_w = 400.00$

displacement ductility demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END B -

for rotation axis 3 and integ. section (b)

From analysis, chord rotation  $\theta = 2.4882320E-005$

$y = (M_y \cdot L_s / 3) / E_{\text{eff}} = 0.00024022$  ((4.29), Biskinis Phd)

$M_y = 3.6682E+008$

$L_s = M/V$  (with  $L_s > 0.1 \cdot L$  and  $L_s < 2 \cdot L$ ) = 300.00

From table 10.5, ASCE 41\_17:  $E_{\text{eff}} = \text{factor} \cdot E_c \cdot I_g = 1.5270E+014$

factor = 0.30

$A_g = 440000.00$

Mean concrete strength:  $f'_c = (f'_{c, \text{jacket}} \cdot A_{\text{jacket}} + f'_{c, \text{core}} \cdot A_{\text{core}}) / A_{\text{section}} = 33.00$

$N = 19223.50$

$E_c \cdot I_g = E_{c, \text{jacket}} \cdot I_{g, \text{jacket}} + E_{c, \text{core}} \cdot I_{g, \text{core}} = 5.0901E+014$

Calculation of Yielding Moment  $M_y$

Calculation of  $\delta / y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7307817E-006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (I_b / I_d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 19223.50$

$b = 750.00$

$\lambda = 0.06082037$

$y_{\text{comp}} = 1.6517162E-005$

with  $f'_c$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e / A_c = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(\theta) = 1.00$

effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$

$f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19186199$   
 $A = 0.01001485$   
 $B = 0.00440616$   
with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $I_b/I_d$

Inadequate Lap Length with  $I_b/I_d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

## Calculation No. 14

column C1, Floor 1



Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity (  $\theta$  )

Edge: End

Local Axis: (2)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i = 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties

-----  
At local axis: 3

EDGE -A-

Shear Force,  $V_a = -0.00017144$

EDGE -B-

Shear Force,  $V_b = 0.00017144$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $As_t = 0.00$

-Compression:  $As_c = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $As_{l,ten} = 1137.257$

-Compression:  $As_{l,com} = 2208.54$

-Middle:  $As_{l,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$

Member Controlled by Flexure ( $V_e/V_r < 1$ )

Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$

with  
 $M_{pr1} = \text{Max}(\mu_{1+}, \mu_{1-}) = 8.1540\text{E}+008$   
 $\mu_{1+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination

$\mu_{1-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination

$M_{pr2} = \text{Max}(\mu_{2+}, \mu_{2-}) = 8.1540\text{E}+008$

$\mu_{2+} = 4.9689\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination

$\mu_{2-} = 8.1540\text{E}+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$\mu = 8.4959181\text{E}-006$

$\mu_u = 4.9689\text{E}+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $\mu_u$ :  $\mu_u^* = \text{shear\_factor} * \text{Max}(\mu_u, \mu_c) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $\mu_u = 0.01241186$

$\omega$  ((5.4c), TBDY) =  $\alpha * \text{sh}_{\min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{fe} = 765.1636$   
-----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha_f = 0.31984848$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$b_{\max} = 750.00$

$h_{\max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{fe} = 765.1636$   
-----

$R = 40.00$

Effective FRP thickness,  $t_f = N L * t * \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$\alpha_{se}$  ((5.4d), TBDY) =  $(\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int})/A_{sec} = 0.45746528$

$\alpha_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.  
 $A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh_1 * F_{ywe1} + ps_2 * F_{ywe2} = 3.0194$   
 $psh_1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh_2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh_1 * F_{ywe1} + ps_2 * F_{ywe2} = 3.0194$   
 $psh_1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh_2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$   
 $s_1 = 100.00$   
 $s_2 = 250.00$   
 $f_{ywe1} = 694.45$   
 $f_{ywe2} = 694.45$   
 $f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y_1 = 0.00140044$   
 $sh_1 = 0.0044814$   
 $ft_1 = 466.8167$   
 $fy_1 = 389.0139$   
 $su_1 = 0.00512$

using (30) in BisKinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{u,min} = l_b/l_d = 0.30$

$su_1 = 0.4 * esu_{1,nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu_{1,nominal} = 0.08$ ,

For calculation of  $esu_{1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs_1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es_1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y_2 = 0.00140044$   
 $sh_2 = 0.0044814$   
 $ft_2 = 466.8167$

$$f_y2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2$ ,  $sh_2, ft_2, f_y2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1$ ,  $sh_1, ft_1, f_y1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s1,com,jacket} + f_{s,core} * A_{s1,com,core}) / A_{s1,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s1,com,jacket} + E_{s,core} * A_{s1,com,core}) / A_{s1,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$f_{y_v} = 389.0139$$

$$s_{u_v} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_d = 0.30$$

$$s_{u_v} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v$ ,  $sh_v, ft_v, f_{y_v}$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1$ ,  $sh_1, ft_1, f_{y1}$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s1,mid,jacket} + f_{s,mid} * A_{s1,mid,core}) / A_{s1,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s1,mid,jacket} + E_{s,mid} * A_{s1,mid,core}) / A_{s1,mid} = 200000.00$$

$$1 = A_{s1,ten} / (b * d) * (f_{s1} / f_c) = 0.02528302$$

$$2 = A_{s1,com} / (b * d) * (f_{s2} / f_c) = 0.04909935$$

$$v = A_{s1,mid} / (b * d) * (f_{sv} / f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s1,ten} / (b * d) * (f_{s1} / f_c) = 0.02869934$$

$$2 = A_{s1,com} / (b * d) * (f_{s2} / f_c) = 0.05573338$$

$$v = A_{s1,mid} / (b * d) * (f_{sv} / f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$M_u = M_{Rc} (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u1}$ -  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$M_u = 8.1540E+008$$
  
-----

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, TBDY) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e^* \text{ sh}_{,\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f^* f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t^* \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY) } = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int}) / A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_{se2} (> = \alpha_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,\min} * f_{ywe} = \text{Min}(p_{sh,x} * f_{ywe}, p_{sh,y} * f_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,\min} * f_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00  
s1 = 100.00  
s2 = 250.00  
fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,  
considering characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY  
For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
characteristic value  $fsv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $Min(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} \cdot Asl_{mid,jacket} + fs_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 389.0139$

with  $Esv = (Es_{jacket} \cdot Asl_{mid,jacket} + Es_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 200000.00$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.09206128$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.04740567$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$fcc$  (5A.2, TBDY) = 34.43547

$cc$  (5A.5, TBDY) = 0.00243499

$c =$  confinement factor = 1.0435

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.11310683$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.05824278$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->

$v < vs_{y2}$  - LHS eq.(4.5) is satisfied

--->

$su$  (4.9) = 0.21669624

$Mu = MRc$  (4.14) = 8.1540E+008

$u = su$  (4.1) = 9.2452857E-006

-----  
Calculation of ratio  $lb/ld$

-----  
Inadequate Lap Length with  $lb/ld = 0.30$   
-----  
-----

-----  
Calculation of  $Mu_{2+}$   
-----  
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$

$Mu = 4.9689E+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$fc = 33.00$

$co$  (5A.5, TBDY) = 0.002

Final value of  $cu$ :  $cu^* = shear\_factor \cdot Max(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

where  $we$  ((5.4c), TBDY) =  $ase \cdot sh_{min} \cdot fy_{we} / f_{ce} + Min(fx, fy) = 0.0496383$

where  $f = af \cdot pf \cdot f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $fx = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (Unconfined\ area) / (total\ area)$

$af = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf / bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff_e = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = NL * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$$A_{sec} = 440000.00$$

$$s_1 = 100.00$$

$$s_2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

From ((5.A.5), TBDY), TBDY:  $cc = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$su1 = 0.4 * esu1\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered  
characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs,jacket * Asl,ten,jacket + fs,core * Asl,ten,core) / Asl,ten = 389.0139$

with  $Es1 = (Es,jacket * Asl,ten,jacket + Es,core * Asl,ten,core) / Asl,ten = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/lb,min = 0.30$

$su2 = 0.4 * esu2\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered  
characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs,jacket * Asl,com,jacket + fs,core * Asl,com,core) / Asl,com = 389.0139$

with  $Es2 = (Es,jacket * Asl,com,jacket + Es,core * Asl,com,core) / Asl,com = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$lo/lou,min = lb/ld = 0.30$

$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered  
characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs,jacket * Asl,mid,jacket + fs,mid * Asl,mid,core) / Asl,mid = 389.0139$

with  $Es_v = (Es,jacket * Asl,mid,jacket + Es,mid * Asl,mid,core) / Asl,mid = 200000.00$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02528302$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.04909935$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$fcc (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = Asl,ten / (b * d) * (fs1 / fc) = 0.02869934$

$2 = Asl,com / (b * d) * (fs2 / fc) = 0.0557338$

$v = Asl,mid / (b * d) * (fsv / fc) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u(4.9) = 0.1476063$$

$$M_u = M_{Rc}(4.14) = 4.9689E+008$$

$$u = s_u(4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u2}$   
-----  
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:

$$\phi_u = 9.2452857E-006$$

$$M_u = 8.1540E+008$$

-----  
with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha(5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \phi_u: \phi_u^* = \text{shear\_factor} * \text{Max}(\phi_u, \phi_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \phi_u = 0.01241186$$

$$\omega_e \text{ ((5.4c), TBDY) } = \alpha s_e * \text{sh, min} * f_{ywe}/f_{ce} + \text{Min}(\phi_x, \phi_y) = 0.0496383$$

where  $\phi = \alpha * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$\phi_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$$

$$b_{\text{max}} = 750.00$$

$$h_{\text{max}} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$\phi_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$$

$$b_{\text{max}} = 750.00$$

$$h_{\text{max}} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{fe} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(\beta_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$\alpha_{se} \text{ ((5.4d), TBDY) } = (\alpha_{se1} * A_{ext} + \alpha_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$\alpha_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max1 = 353600.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

Aconf,min1 = 293525.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max1 by a length equal to half the clear spacing between external hoops.

AnoConf1 = 158733.333 is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
ase2 ( $\geq$  ase1) =  $\text{Max}(((Aconf,max2 - AnoConf2)/Aconf,max2) * (Aconf,min2/Aconf,max2), 0) = 0.45746528$

The definitions of AnoConf, Aconf,min and Aconf,max are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

Aconf,max2 = 171264.00 is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

Aconf,min2 = 54741.00 is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area Aconf,max2 by a length equal to half the clear spacing between internal hoops.

AnoConf2 = 106242.667 is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
psh,min\*Fywe =  $\text{Min}(psh,x*Fywe, psh,y*Fywe) = 3.0194$

Expression (5.4d) for psh,min\*Fywe has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
psh\_x\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194

psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along Y) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 (5.4d) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along Y) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
psh\_y\*Fywe = psh1\*Fywe1 + ps2\*Fywe2 = 3.0194

psh1 ((5.4d), TBDY) =  $Lstir1 * Astir1 / (Asec * s1) = 0.00367709$

Lstir1 (Length of stirrups along X) = 2060.00

Astir1 (stirrups area) = 78.53982

psh2 ((5.4d), TBDY) =  $Lstir2 * Astir2 / (Asec * s2) = 0.00067082$

Lstir2 (Length of stirrups along X) = 1468.00

Astir2 (stirrups area) = 50.26548

-----  
Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 =  $0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1, ft1, fy1, it is considered characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1, ft1, fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(fs\_jacket * Asl\_ten\_jacket + fs\_core * Asl\_ten\_core) / Asl\_ten = 389.0139$

with Es1 =  $(Es\_jacket * Asl\_ten\_jacket + Es\_core * Asl\_ten\_core) / Asl\_ten = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{s_u2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_u2,nominal} = 0.08$ ,

For calculation of  $e_{s_u2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{s_y2} = f_{s_2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_2} = (f_{s,jacket} * A_{s_l,com,jacket} + f_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 389.0139$$

$$\text{with } E_{s_2} = (E_{s,jacket} * A_{s_l,com,jacket} + E_{s,core} * A_{s_l,com,core}) / A_{s_l,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{u_v} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{o,u,min} = l_b/l_d = 0.30$$

$$s_{u_v} = 0.4 * e_{s_{u_v},nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{s_{u_v},nominal} = 0.08$ ,

considering characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{s_{u_v},nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{s_{y_v}} = f_{s_v}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s_v} = (f_{s,jacket} * A_{s_l,mid,jacket} + f_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 389.0139$$

$$\text{with } E_{s_v} = (E_{s,jacket} * A_{s_l,mid,jacket} + E_{s,mid} * A_{s_l,mid,core}) / A_{s_l,mid} = 200000.00$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.09206128$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.04740567$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s_l,ten} / (b * d) * (f_{s_1} / f_c) = 0.11310683$$

$$2 = A_{s_l,com} / (b * d) * (f_{s_2} / f_c) = 0.05824278$$

$$v = A_{s_l,mid} / (b * d) * (f_{s_v} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y_2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$

$$V_{r1} = V_{CoI} ((10.3), ASCE 41-17) = k_{nl} * V_{CoI0}$$

$$V_{CoI0} = 1.0898E+006$$

$$k_{nl} = 1 \text{ (zero step-static loading)}$$

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)  
 Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)  
 $M/Vd = 4.00$   
 $\mu_u = 1518.009$   
 $V_u = 0.00017144$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 16273.607$   
 $A_g = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{sjacket} + V_{s,core} = 901155.609$   
 where:  
 $V_{sjacket} = V_{sj1} + V_{sj2} = 802857.879$   
 $V_{sj1} = 523602.964$  is calculated for section web jacket, with:  
 $d = 600.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj1}$  is multiplied by  $Col_{j1} = 1.00$   
 $s/d = 0.16666667$   
 $V_{sj2} = 279254.914$  is calculated for section flange jacket, with:  
 $d = 320.00$   
 $A_v = 157079.633$   
 $f_y = 555.56$   
 $s = 100.00$   
 $V_{sj2}$  is multiplied by  $Col_{j2} = 1.00$   
 $s/d = 0.3125$   
 $V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$   
 $V_{s,c1} = 98297.73$  is calculated for section web core, with:  
 $d = 440.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c1}$  is multiplied by  $Col_{c1} = 1.00$   
 $s/d = 0.56818182$   
 $V_{s,c2} = 0.00$  is calculated for section flange core, with:  
 $d = 160.00$   
 $A_v = 100530.965$   
 $f_y = 555.56$   
 $s = 250.00$   
 $V_{s,c2}$  is multiplied by  $Col_{c2} = 0.00$   
 $s/d = 1.5625$   
 $V_f$  ((11-3)-(11.4), ACI 440) = 463792.00  
 $f = 0.95$ , for fully-wrapped sections  
 $w_f/s_f = 1$  (FRP strips adjacent to one another).  
 In (11.3)  $\sin \theta + \cos \theta$  is replaced with  $(\cot \theta + \cot \alpha) \sin \alpha$  which is more a generalised expression,  
 where  $\theta$  is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function  $V_f(\theta, \alpha)$ , is implemented for every different fiber orientation  $\alpha_i$ ,  
 as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.  
 orientation 1:  $\theta = b_1 + 90^\circ = 90.00$   
 $V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:  
 total thickness per orientation,  $t_{f1} = NL \cdot t / NoDir = 1.00$   
 $d_{fv} = d$  (figure 11.2, ACI 440) = 707.00  
 $f_{fe}$  ((11-5), ACI 440) = 328.00  
 $E_f = 82000.00$   
 $f_e = 0.004$ , from (11.6a), ACI 440  
 with  $f_u = 0.009$   
 From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $b_w = 400.00$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$   
 $V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$   
 $V_{Col0} = 1.0898E+006$   
 $k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '

where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.009$

$V_u = 0.00017144$

$d = 0.8 \cdot h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 523602.964$  is calculated for section web jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col_{j1} = 1.00$

$s/d = 0.16666667$

$V_{s,j2} = 279254.914$  is calculated for section flange jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col_{j2} = 1.00$

$s/d = 0.3125$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col_{c1} = 1.00$

$s/d = 0.56818182$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col_{c2} = 0.00$

$s/d = 1.5625$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \csc) \sin \alpha$  which is more a generalised expression, where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, \theta)$ , is implemented for every different fiber orientation  $\alpha_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 45^\circ + 90^\circ = 135^\circ$

$V_f = \text{Min}(|V_f(45, 135)|, |V_f(-45, 135)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / NoDir = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 3

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 2

(Bending local axis: 3)

Section Type: rcjcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_o/l_{ou,min} = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

Stepwise Properties

At local axis: 2

EDGE -A-

Shear Force,  $V_a = -0.0001715$

EDGE -B-

Shear Force,  $V_b = 0.0001715$

BOTH EDGES

Axial Force,  $F = -16273.607$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $Aslc = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $Asl,ten = 1137.257$   
-Compression:  $Asl,com = 2208.54$   
-Middle:  $Asl,mid = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $Ve/Vr = 0.49879178$   
Member Controlled by Flexure ( $Ve/Vr < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $Ve = (Mpr1 + Mpr2)/ln = 543597.759$   
with

$Mpr1 = \text{Max}(Mu1+ , Mu1-) = 8.1540E+008$   
 $Mu1+ = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction which is defined for the static loading combination  
 $Mu1- = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment direction which is defined for the static loading combination  
 $Mpr2 = \text{Max}(Mu2+ , Mu2-) = 8.1540E+008$   
 $Mu2+ = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction which is defined for the the static loading combination  
 $Mu2- = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment direction which is defined for the the static loading combination

-----  
Calculation of  $Mu1+$   
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:  
 $u = 8.4959181E-006$   
 $Mu = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$

$fc = 33.00$

$co$  (5A.5, TBDY) = 0.002

Final value of  $cu$ :  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $ase * sh_{min} * fy_{we} / f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af * pf * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $fx = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff,e = 765.1636$

-----  
 $fy = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

$af = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$

$bw = 400.00$

effective stress from (A.35),  $ff,e = 765.1636$   
-----

R = 40.00

Effective FRP thickness,  $t_f = NL * t * \cos(b_1) = 1.00$

$f_u, f = 840.00$

$E_f = 82000.00$

$u, f = 0.015$

$ase ((5.4d), TBDY) = (ase_1 * A_{ext} + ase_2 * A_{int}) / A_{sec} = 0.45746528$

$ase_1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase_2 (>= ase_1) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2} (5.4d) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2} ((5.4d), TBDY) = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s_1 = 100.00$

$s_2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y_1 = 0.00140044$

$sh_1 = 0.0044814$

$ft_1 = 466.8167$

$fy_1 = 389.0139$

$su_1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o / l_{ou,min} = l_b / d = 0.30$

$$su_1 = 0.4 * esu_{1\_nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu_{1\_nominal} = 0.08$ ,

For calculation of  $esu_{1\_nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered characteristic value  $fsy_1 = fs_1/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs_1 = (fs_{jacket} * Asl_{ten,jacket} + fs_{core} * Asl_{ten,core}) / Asl_{ten} = 389.0139$$

$$\text{with } Es_1 = (Es_{jacket} * Asl_{ten,jacket} + Es_{core} * Asl_{ten,core}) / Asl_{ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$su_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/lb_{min} = 0.30$$

$$su_2 = 0.4 * esu_{2\_nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu_{2\_nominal} = 0.08$ ,

For calculation of  $esu_{2\_nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered characteristic value  $fsy_2 = fs_2/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs_2 = (fs_{jacket} * Asl_{com,jacket} + fs_{core} * Asl_{com,core}) / Asl_{com} = 389.0139$$

$$\text{with } Es_2 = (Es_{jacket} * Asl_{com,jacket} + Es_{core} * Asl_{com,core}) / Asl_{com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/ld = 0.30$$

$$suv = 0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv_{nominal} = 0.08$ ,

considering characteristic value  $fsy_v = fsv/1.2$ , from table 5.1, TBDY  
For calculation of  $esuv_{nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered characteristic value  $fsy_v = fsv/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs_{jacket} * Asl_{mid,jacket} + fs_{mid} * Asl_{mid,core}) / Asl_{mid} = 389.0139$$

$$\text{with } Es_v = (Es_{jacket} * Asl_{mid,jacket} + Es_{mid} * Asl_{mid,core}) / Asl_{mid} = 200000.00$$

$$1 = Asl_{ten} / (b * d) * (fs_1 / fc) = 0.02528302$$

$$2 = Asl_{com} / (b * d) * (fs_2 / fc) = 0.04909935$$

$$v = Asl_{mid} / (b * d) * (fsv / fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl_{ten} / (b * d) * (fs_1 / fc) = 0.02869934$$

$$2 = Asl_{com} / (b * d) * (fs_2 / fc) = 0.0557338$$

$$v = Asl_{mid} / (b * d) * (fsv / fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y_2}$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Mu1-

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L^* t \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{s2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_s,jacket * A_{sl,ten,jacket} + f_s,core * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with  $Es1 = (E_s,jacket * A_{sl,ten,jacket} + E_s,core * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (f_s,jacket * A_{sl,com,jacket} + f_s,core * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with  $Es2 = (E_s,jacket * A_{sl,com,jacket} + E_s,core * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

v < vs,y2 - LHS eq.(4.5) is satisfied

--->

su (4.9) = 0.21669624

Mu = MRc (4.14) = 8.1540E+008

u = su (4.1) = 9.2452857E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----  
-----

-----  
Calculation of Mu2+  
-----  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006

Mu = 4.9689E+008  
-----

with full section properties:

b = 750.00

d = 707.00

d' = 43.00

v = 0.00093001

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu: cu\* = shear\_factor \* Max( cu, cc) = 0.01241186

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY: cu = 0.01241186

we ((5.4c), TBDY) = ase\* sh,min\*fywe/fce+ Min( fx, fy) = 0.0496383

where f = af\*pf\*ffe/fce is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$$b_w = 400.00$$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$$R = 40.00$$

Effective FRP thickness,  $t_f = NL * t * \cos(b_1) = 1.00$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f,e} = 0.015$$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (\geq a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

psh2 ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 =  $0.4 * esu1_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 =  $(f_{s,jacket} * A_{sl,ten,jacket} + f_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 389.0139$

with Es1 =  $(E_{s,jacket} * A_{sl,ten,jacket} + E_{s,core} * A_{sl,ten,core}) / A_{sl,ten} = 200000.00$

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 =  $0.4 * esu2_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 =  $(f_{s,jacket} * A_{sl,com,jacket} + f_{s,core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$

with Es2 =  $(E_{s,jacket} * A_{sl,com,jacket} + E_{s,core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv =  $0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY  
For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 * (lb/d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv =  $(f_{s,jacket} * A_{sl,mid,jacket} + f_{s,mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$

with Esv =  $(E_{s,jacket} * A_{sl,mid,jacket} + E_{s,mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$

1 =  $A_{sl,ten} / (b * d) * (fs1 / fc) = 0.02528302$

2 =  $A_{sl,com} / (b * d) * (fs2 / fc) = 0.04909935$

v =  $A_{sl,mid} / (b * d) * (fsv / fc) = 0.04462942$

and confined core properties:

b = 690.00

d = 677.00

$d' = 13.00$   
 $f_{cc} (5A.2, TBDY) = 34.43547$   
 $cc (5A.5, TBDY) = 0.00243499$   
 $c = \text{confinement factor} = 1.0435$   
 $1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02869934$   
 $2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.0557338$   
 $v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.05065988$   
 Case/Assumption: Unconfined full section - Steel rupture  
 ' satisfies Eq. (4.3)

--->  
 $v < v_{s,y2}$  - LHS eq.(4.5) is satisfied  
 --->

$su (4.9) = 0.1476063$   
 $Mu = MRc (4.14) = 4.9689E+008$   
 $u = su (4.1) = 8.4959181E-006$

-----  
 Calculation of ratio  $l_b/l_d$

-----  
 Inadequate Lap Length with  $l_b/l_d = 0.30$   
 -----  
 -----

-----  
 Calculation of  $Mu_2$ -  
 -----

-----  
 Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:  
 $u = 9.2452857E-006$   
 $Mu = 8.1540E+008$   
 -----

with full section properties:

$b = 400.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00174378$   
 $N = 16273.607$   
 $f_c = 33.00$   
 $co (5A.5, TBDY) = 0.002$   
 Final value of  $cu$ :  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$   
 The Shear\_factor is considered equal to 1 (pure moment strength)  
 From (5.4b), TBDY:  $cu = 0.01241186$   
 $w_e ((5.4c), TBDY) = a_{se} * sh_{,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$   
 where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
 -----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
 -----

$R = 40.00$

Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b_1) = 1.00$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$ase \text{ ((5.4d), TBDY)} = (ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$$

$$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$ase2 \text{ (>=ase1)} = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along Y)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ (5.4d)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along Y)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} \text{ ((5.4d), TBDY)} = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$$

$$L_{stir1} \text{ (Length of stirrups along X)} = 2060.00$$

$$A_{stir1} \text{ (stirrups area)} = 78.53982$$

$$p_{sh2} \text{ ((5.4d), TBDY)} = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$$

$$L_{stir2} \text{ (Length of stirrups along X)} = 1468.00$$

$$A_{stir2} \text{ (stirrups area)} = 50.26548$$

$$A_{sec} = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$f_{ywe1} = 694.45$$

$$f_{ywe2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$l_o / l_{ou,min} = l_b / d = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (fs_{jacket} \cdot Asl_{ten,jacket} + fs_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 389.0139$

with  $Es1 = (Es_{jacket} \cdot Asl_{ten,jacket} + Es_{core} \cdot Asl_{ten,core}) / Asl_{ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/lb_{,min} = 0.30$

$su2 = 0.4 \cdot esu2\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs2 = (fs_{jacket} \cdot Asl_{com,jacket} + fs_{core} \cdot Asl_{com,core}) / Asl_{com} = 389.0139$

with  $Es2 = (Es_{jacket} \cdot Asl_{com,jacket} + Es_{core} \cdot Asl_{com,core}) / Asl_{com} = 200000.00$

$yv = 0.00140044$

$shv = 0.0044814$

$ftv = 466.8167$

$fyv = 389.0139$

$suv = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lo_{ou,min} = lb/ld = 0.30$

$suv = 0.4 \cdot esuv\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv, shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fsv = (fs_{jacket} \cdot Asl_{mid,jacket} + fs_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 389.0139$

with  $Es_v = (Es_{jacket} \cdot Asl_{mid,jacket} + Es_{mid} \cdot Asl_{mid,core}) / Asl_{mid} = 200000.00$

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.09206128$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.04740567$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.08368017$

and confined core properties:

$b = 340.00$

$d = 677.00$

$d' = 13.00$

$fcc$  (5A.2, TBDY) = 34.43547

$cc$  (5A.5, TBDY) = 0.00243499

$c$  = confinement factor = 1.0435

$1 = Asl_{ten} / (b \cdot d) \cdot (fs1 / fc) = 0.11310683$

$2 = Asl_{com} / (b \cdot d) \cdot (fs2 / fc) = 0.05824278$

$v = Asl_{mid} / (b \cdot d) \cdot (fsv / fc) = 0.10280977$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs_{y2}$  - LHS eq.(4.5) is satisfied

--->

$su$  (4.9) = 0.21669624

$Mu = MRc$  (4.14) = 8.1540E+008

$u = su$  (4.1) = 9.2452857E-006

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898\text{E}+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898\text{E}+006$

$V_{r1} = V_{Co1} \text{ ((10.3), ASCE 41-17)} = k_{nl} * V_{Co10}$

$V_{Co10} = 1.0898\text{E}+006$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{\text{jacket}} * \text{Area}_{\text{jacket}} + f_c'_{\text{core}} * \text{Area}_{\text{core}}) / \text{Area}_{\text{section}} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$M/Vd = 4.00$

$\mu_u = 1518.777$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,\text{jacket}} + V_{s,\text{core}} = 901155.609$

where:

$V_{s,\text{jacket}} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $\text{Col},j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $\text{Col},j2 = 1.00$

$s/d = 0.16666667$

$V_{s,\text{core}} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $\text{Col},c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $\text{Col},c2 = 1.00$

$s/d = 0.56818182$

$V_f \text{ ((11-3)-(11.4), ACI 440)} = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression,

where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a_1)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|)$ , with:

total thickness per orientation,  $t_{f1} = N_L * t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$   
 $bw = 400.00$

Calculation of Shear Strength at edge 2,  $V_r2 = 1.0898E+006$

$V_r2 = V_{Col} \text{ ((10.3), ASCE 41-17)} = knl * V_{Col0}$

$V_{Col0} = 1.0898E+006$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_s + f * V_f$ '  
where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$= 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} * Area_{jacket} + f_c'_{core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$   
MPa (22.5.3.1, ACI 318-14)

$M / Vd = 4.00$

$\mu_u = 1518.776$

$V_u = 0.0001715$

$d = 0.8 * h = 600.00$

$N_u = 16273.607$

$A_g = 300000.00$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$d = 320.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$s/d = 0.3125$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$d = 600.00$

$A_v = 157079.633$

$f_y = 555.56$

$s = 100.00$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$s/d = 0.16666667$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$d = 160.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$s/d = 1.5625$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$d = 440.00$

$A_v = 100530.965$

$f_y = 555.56$

$s = 250.00$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$s/d = 0.56818182$

$V_f \text{ ((11-3)-(11.4), ACI 440)} = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f / s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a) \sin a$  which is more a generalised expression,  
where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a)$ , is implemented for every different fiber orientation  $a_i$ ,  
as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\alpha_1 = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$

$E_f = 82000.00$

$f_e = 0.004$ , from (11.6a), ACI 440

with  $f_u = 0.009$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$b_w = 400.00$

-----  
-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
At local axis: 2

-----  
-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

Section Type: rcjcs

Constant Properties

-----  
Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)

Longitudinal Bars With Ends Lapped Starting at the End Sections

Inadequate Lap Length with  $l_b/l_d = 0.30$

FRP Wrapping Data

Type: Carbon

Dry properties (design values)

Thickness,  $t = 1.00$

Tensile Strength,  $f_{fu} = 840.00$

Tensile Modulus,  $E_f = 82000.00$

Elongation,  $e_{fu} = 0.009$

Number of directions,  $N_{oDir} = 1$

Fiber orientations,  $b_i: 0.00^\circ$

Number of layers,  $N_L = 1$

Radius of rounding corners,  $R = 40.00$

-----  
-----  
Stepwise Properties

Bending Moment,  $M = -114246.474$

Shear Force,  $V_2 = 7630.77$

Shear Force,  $V_3 = -206.4342$

Axial Force,  $F = -19223.50$

Longitudinal Reinforcement Area Distribution (in 2 divisions)

-Tension:  $A_{st} = 0.00$

-Compression:  $A_{sc} = 5353.274$

Longitudinal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten = 1137.257$

-Compression:  $Asl,com = 2208.54$

-Middle:  $Asl,mid = 2007.478$

Longitudinal External Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,jacket = 829.3805$

-Compression:  $Asl,com,jacket = 1746.726$

-Middle:  $Asl,mid,jacket = 1545.664$

Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)

-Tension:  $Asl,ten,core = 307.8761$

-Compression:  $Asl,com,core = 461.8141$

-Middle:  $Asl,mid,core = 461.8141$

Mean Diameter of Tension Reinforcement,  $DbL = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u,R = 1.0^*$   $u = 0.03044315$

$u = y + p = 0.03044315$

- Calculation of  $y$  -

$y = (My*Ls/3)/Eleff = 0.00044315$  ((4.29),Biskinis Phd))

$My = 3.6682E+008$

$Ls = M/V$  (with  $Ls > 0.1*L$  and  $Ls < 2*L$ ) = 553.4279

From table 10.5, ASCE 41\_17:  $Eleff = factor*Ec*Ig = 1.5270E+014$

$factor = 0.30$

$Ag = 440000.00$

Mean concrete strength:  $fc' = (fc'_jacket*Area_jacket + fc'_core*Area_core)/Area_section = 33.00$

$N = 19223.50$

$Ec*Ig = Ec_jacket*Ig_jacket + Ec_core*Ig_core = 5.0901E+014$

Calculation of Yielding Moment  $My$

Calculation of  $y$  and  $My$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $bw = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{ten}, y_{com})$

$y_{ten} = 2.7307817E-006$

with ((10.1), ASCE 41-17)  $fy = \text{Min}(fy, 1.25*fy*(b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $pt = 0.00729988$

$pc = 0.00416509$

$pv = 0.00378591$

$N = 19223.50$

$b = 750.00$

" = 0.06082037

$y_{comp} = 1.6517162E-005$

with  $fc^*$  (12.3, (ACI 440)) = 33.60672

$fc = 33.00$

$fl = 0.61848273$

$b = b_{max} = 750.00$

$h = h_{max} = 750.00$

$Ag = 0.44$

$g = pt + pc + pv = 0.01009575$

$rc = 40.00$

$Ae/Ac = 0.31291181$

Effective FRP thickness,  $t_f = NL \cdot t \cdot \cos(b_1) = 1.00$   
effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$   
 $f_u = 0.009$   
 $E_f = 82000.00$   
 $E_c = 26999.444$   
 $y = 0.19186199$   
 $A = 0.01001485$   
 $B = 0.00440616$   
with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.19289193 < t/d$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$

-----  
- Calculation of  $p$  -

-----  
From table 10-8:  $p = 0.03$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/l_d < 1$

shear control ratio  $V_y E / V_{CoI} E = 0.49879178$

$d = d_{\text{external}} = 707.00$

$s = s_{\text{external}} = 0.00$

-  $t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$

jacket:  $s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_1 = 100.00$

core:  $s_2 = A_{v2} \cdot L_{\text{stir2}} / (s_2 \cdot A_g) = 0.00067082$

$A_{v2} = 50.26548$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir2}} = 1468.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$s_2 = 250.00$

The term  $2 \cdot t_f / b_w \cdot (f_{fe} / f_s)$  is implemented to account for FRP contribution

where  $f = 2 \cdot t_f / b_w$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $f_{fe} / f_s$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $f_s$  of jacket is used.

$N_{UD} = 19223.50$

$A_g = 440000.00$

$f_{cE} = (f_{c_{\text{jacket}}} \cdot \text{Area}_{\text{jacket}} + f_{c_{\text{core}}} \cdot \text{Area}_{\text{core}}) / \text{section\_area} = 33.00$

$f_{yIE} = (f_{y_{\text{ext\_Long\_Reinf}}} \cdot \text{Area}_{\text{ext\_Long\_Reinf}} + f_{y_{\text{int\_Long\_Reinf}}} \cdot \text{Area}_{\text{int\_Long\_Reinf}}) / \text{Area}_{\text{Tot\_Long\_Rein}} = 555.56$

$f_{yIE} = (f_{y_{\text{ext\_Trans\_Reinf}}} \cdot s_1 + f_{y_{\text{int\_Trans\_Reinf}}} \cdot s_2) / (s_1 + s_2) = 555.56$

$p_l = \text{Area}_{\text{Tot\_Long\_Rein}} / (b \cdot d) = 0.01009575$

$b = 750.00$

$d = 707.00$

$f_{cE} = 33.00$

-----  
End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 2

Integration Section: (b)

## Calculation No. 15

column C1, Floor 1



Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Shear capacity VRd

Edge: End

Local Axis: (3)



Start Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

Section Type: rcjlc

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Member Shear Force is generally considered as Force-Controlled Action according to Table C7-1, ASCE 41-17.

Lower-bound strengths are used for Force-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{c\_lower\_bound} = 25.00$

New material of Primary Member: Steel Strength,  $f_s = f_{s\_lower\_bound} = 500.00$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of  $\gamma$  for displacement ductility demand, the expected (mean value) strengths are used (7.5.1.3, ASCE 41-17) because bending is considered as Deformation-Controlled Action (Table C7-1, ASCE 41-17).

Jacket

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

Existing Column

New material: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material: Steel Strength,  $f_s = f_{sm} = 555.56$

#####

Max Height, Hmax = 750.00  
 Min Height, Hmin = 400.00  
 Max Width, Wmax = 750.00  
 Min Width, Wmin = 400.00  
 Jacket Thickness, tj = 100.00  
 Cover Thickness, c = 25.00  
 Element Length, L = 3000.00  
 Primary Member  
 Ribbed Bars  
 Ductile Steel  
 Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
 Longitudinal Bars With Ends Lapped Starting at the End Sections  
 Inadequate Lap Length with  $l_o/l_{o,min} = l_b/l_d = 0.30$   
 FRP Wrapping Data  
 Type: Carbon  
 Dry properties (design values)  
 Thickness, t = 1.00  
 Tensile Strength,  $f_{fu} = 840.00$   
 Tensile Modulus,  $E_f = 82000.00$   
 Elongation,  $e_{fu} = 0.009$   
 Number of directions, NoDir = 1  
 Fiber orientations,  $b_i = 0.00^\circ$   
 Number of layers, NL = 1  
 Radius of rounding corners, R = 40.00

-----  
 Stepwise Properties  
 -----

EDGE -A-  
 Bending Moment,  $M_a = -502156.692$   
 Shear Force,  $V_a = 206.4342$   
 EDGE -B-  
 Bending Moment,  $M_b = -114246.474$   
 Shear Force,  $V_b = -206.4342$   
 BOTH EDGES  
 Axial Force,  $F = -19223.50$   
 Longitudinal Reinforcement Area Distribution (in 2 divisions)  
   -Tension:  $A_{sl,t} = 0.00$   
   -Compression:  $A_{sl,c} = 5353.274$   
 Longitudinal Reinforcement Area Distribution (in 3 divisions)  
   -Tension:  $A_{sl,ten} = 1137.257$   
   -Compression:  $A_{sl,com} = 2208.54$   
   -Middle:  $A_{sl,mid} = 2007.478$   
 Mean Diameter of Tension Reinforcement,  $Db_{L,ten} = 16.80$

-----  
 New component: From table 7-7, ASCE 41\_17: Final Shear Capacity  $V_R = 1.0 \cdot V_n = 1.1010E+006$   
 $V_n ((10.3), ASCE 41-17) = k_n \cdot V_{CoI0} = 1.1010E+006$   
 $V_{CoI} = 1.1010E+006$   
 $k_n = 1.00$   
 $displacement\_ductility\_demand = 1.6835633E-005$

-----  
 NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ '  
 where  $V_f$  is the contribution of FRPs (11.3), ACI 440).  
 -----

= 1 (normal-weight concrete)  
 Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 25.00$ , but  $f'_c^{0.5} \leq 8.3$   
 MPa (22.5.3.1, ACI 318-14)  
 $M/Vd = 2.00$   
 $M_u = 114246.474$   
 $V_u = 206.4342$   
 $d = 0.8 \cdot h = 600.00$   
 $N_u = 19223.50$   
 $A_g = 300000.00$   
 From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 811033.559$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 722566.31$$

$V_{s,j1} = 471238.898$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{s,j2} = 251327.412$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 500.00$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 88467.249$$

$V_{s,c1} = 88467.249$  is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 500.00$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$$f = 0.95, \text{ for fully-wrapped sections}$$

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression,

where  $\alpha$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\alpha, a_1)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\alpha = 45^\circ$  and  $\alpha = -45^\circ$  to take into consideration the cyclic seismic loading.

$$\text{orientation 1: } \alpha_1 = b_1 + 90^\circ = 90.00$$

$$V_f = \text{Min}(|V_f(45, \alpha_1)|, |V_f(-45, \alpha_1)|), \text{ with:}$$

$$\text{total thickness per orientation, } t_{f1} = NL * t / \text{NoDir} = 1.00$$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe}((11-5), ACI 440) = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 797164.595$$

$$b_w = 400.00$$

-----  
displacement\_ductility\_demand is calculated as  $\delta / y$

- Calculation of  $\delta / y$  for END B -

for rotation axis 2 and integ. section (b)

-----  
From analysis, chord rotation  $\theta = 7.4607111E-009$

$$y = (M_y * L_s / 3) / E_{eff} = 0.00044315 \text{ ((4.29), Biskinis Phd)}$$

$$M_y = 3.6682E+008$$

$$L_s = M/V \text{ (with } L_s > 0.1 * L \text{ and } L_s < 2 * L) = 553.4279$$

$$\text{From table 10.5, ASCE 41_17: } E_{eff} = \text{factor} * E_c * I_g = 1.5270E+014$$

$$\text{factor} = 0.30$$

$$A_g = 440000.00$$

$$\text{Mean concrete strength: } f_c' = (f_c'_{jacket} * \text{Area}_{jacket} + f_c'_{core} * \text{Area}_{core}) / \text{Area}_{section} = 33.00$$

$$N = 19223.50$$

$$E_c * I_g = E_c * I_{g,jacket} + E_c * I_{g,core} = 5.0901E+014$$
  
-----

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$

$y_{\text{ten}} = 2.7307817\text{E-}006$

with ((10.1), ASCE 41-17)  $f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$

$d = 707.00$

$y = 0.19403023$

$A = 0.01021225$

$B = 0.00452265$

with  $p_t = 0.00214476$

$p_c = 0.00416509$

$p_v = 0.00378591$

$N = 19223.50$

$b = 750.00$

" = 0.06082037

$y_{\text{comp}} = 1.6517162\text{E-}005$

with  $f_c^*$  (12.3, (ACI 440)) = 33.60672

$f_c = 33.00$

$f_l = 0.61848273$

$b = b_{\text{max}} = 750.00$

$h = h_{\text{max}} = 750.00$

$A_g = 0.44$

$g = p_t + p_c + p_v = 0.01009575$

$r_c = 40.00$

$A_e/A_c = 0.31291181$

Effective FRP thickness,  $t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$

effective strain from (12.5) and (12.12),  $\epsilon_{fe} = 0.004$

$f_u = 0.009$

$E_f = 82000.00$

$E_c = 26999.444$

$y = 0.19186199$

$A = 0.01001485$

$B = 0.00440616$

with  $E_s = 200000.00$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

End Of Calculation of Shear Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

**Calculation No. 16**

column C1, Floor 1


Limit State: Life Safety (data interpolation between analysis steps 1 and 2)

Analysis: Uniform +X

Check: Chord rotation capacity ( $\theta_u$ )

Edge: End

Local Axis: (3)



Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At Shear local axis: 3

(Bending local axis: 2)

Section Type: rcjlcs

Constant Properties

Knowledge Factor,  $\gamma = 0.87$

Mean strength values are used for both shear and moment calculations.

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

#####

Note: Especially for the calculation of moment strengths,

the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14

Jacket

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

Existing Column

New material: Steel Strength,  $f_s = 1.25 \cdot f_{sm} = 694.45$

#####

Max Height,  $H_{max} = 750.00$

Min Height,  $H_{min} = 400.00$

Max Width,  $W_{max} = 750.00$

Min Width,  $W_{min} = 400.00$

Jacket Thickness,  $t_j = 100.00$

Cover Thickness,  $c = 25.00$

Mean Confinement Factor overall section = 1.0435

Element Length,  $L = 3000.00$

Primary Member

Ribbed Bars

Ductile Steel

Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $NoDir = 1$   
Fiber orientations,  $bi: 0.00^\circ$   
Number of layers,  $NL = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 3  
EDGE -A-  
Shear Force,  $V_a = -0.00017144$   
EDGE -B-  
Shear Force,  $V_b = 0.00017144$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$

-----  
-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(Mu_{1+} , Mu_{1-}) = 8.1540E+008$   
 $Mu_{1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $Mu_{1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(Mu_{2+} , Mu_{2-}) = 8.1540E+008$   
 $Mu_{2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $Mu_{2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $Mu_{1+}$   
-----

-----  
Calculation of ultimate curvature  $\phi_u$  according to 4.1, Biskinis/Fardis 2013:  
 $\phi_u = 8.4959181E-006$   
 $M_u = 4.9689E+008$

-----  
with full section properties:

$b = 750.00$   
 $d = 707.00$   
 $d' = 43.00$   
 $v = 0.00093001$   
 $N = 16273.607$   
 $f_c = 33.00$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N_L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{,f} = 0.015$$

$$a_{se} ((5.4d), TBDY) = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$$

$$p_{sh1} ((5.4d), TBDY) = L_{stir1} * A_{stir1}/(A_{sec} * s_1) = 0.00367709$$

$$L_{stir1} (\text{Length of stirrups along } Y) = 2060.00$$

$$A_{stir1} (\text{stirrups area}) = 78.53982$$

$$p_{sh2} (5.4d) = L_{stir2} * A_{stir2}/(A_{sec} * s_2) = 0.00067082$$

$$L_{stir2} (\text{Length of stirrups along } Y) = 1468.00$$

$$\text{Astir2 (stirrups area)} = 50.26548$$

$$\text{psh}_y * \text{Fywe} = \text{psh}_1 * \text{Fywe}_1 + \text{ps}_2 * \text{Fywe}_2 = 3.0194$$

$$\text{psh}_1 ((5.4d), \text{TBDY}) = \text{Lstir}_1 * \text{Astir}_1 / (\text{Asec} * \text{s}_1) = 0.00367709$$

$$\text{Lstir}_1 (\text{Length of stirrups along X}) = 2060.00$$

$$\text{Astir}_1 (\text{stirrups area}) = 78.53982$$

$$\text{psh}_2 ((5.4d), \text{TBDY}) = \text{Lstir}_2 * \text{Astir}_2 / (\text{Asec} * \text{s}_2) = 0.00067082$$

$$\text{Lstir}_2 (\text{Length of stirrups along X}) = 1468.00$$

$$\text{Astir}_2 (\text{stirrups area}) = 50.26548$$

$$\text{Asec} = 440000.00$$

$$\text{s}_1 = 100.00$$

$$\text{s}_2 = 250.00$$

$$\text{fywe}_1 = 694.45$$

$$\text{fywe}_2 = 694.45$$

$$\text{fce} = 33.00$$

$$\text{From } ((5.A5), \text{TBDY}), \text{TBDY: } \text{cc} = 0.00243499$$

$$\text{c} = \text{confinement factor} = 1.0435$$

$$\text{y}_1 = 0.00140044$$

$$\text{sh}_1 = 0.0044814$$

$$\text{ft}_1 = 466.8167$$

$$\text{fy}_1 = 389.0139$$

$$\text{su}_1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/ld} = 0.30$$

$$\text{su}_1 = 0.4 * \text{esu}_1 \text{nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_1 \text{nominal} = 0.08,$$

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

$$\text{y}_1, \text{sh}_1, \text{ft}_1, \text{fy}_1, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_1 = (\text{fs,jacket} * \text{Asl,ten,jacket} + \text{fs,core} * \text{Asl,ten,core}) / \text{Asl,ten} = 389.0139$$

$$\text{with } \text{Es}_1 = (\text{Es,jacket} * \text{Asl,ten,jacket} + \text{Es,core} * \text{Asl,ten,core}) / \text{Asl,ten} = 200000.00$$

$$\text{y}_2 = 0.00140044$$

$$\text{sh}_2 = 0.0044814$$

$$\text{ft}_2 = 466.8167$$

$$\text{fy}_2 = 389.0139$$

$$\text{su}_2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/lb,min} = 0.30$$

$$\text{su}_2 = 0.4 * \text{esu}_2 \text{nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esu}_2 \text{nominal} = 0.08,$$

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

$$\text{y}_2, \text{sh}_2, \text{ft}_2, \text{fy}_2, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_2 = (\text{fs,jacket} * \text{Asl,com,jacket} + \text{fs,core} * \text{Asl,com,core}) / \text{Asl,com} = 389.0139$$

$$\text{with } \text{Es}_2 = (\text{Es,jacket} * \text{Asl,com,jacket} + \text{Es,core} * \text{Asl,com,core}) / \text{Asl,com} = 200000.00$$

$$\text{y}_v = 0.00140044$$

$$\text{sh}_v = 0.0044814$$

$$\text{ft}_v = 466.8167$$

$$\text{fy}_v = 389.0139$$

$$\text{suv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$\text{lo/lou,min} = \text{lb/ld} = 0.30$$

$$\text{suv} = 0.4 * \text{esuv}_v \text{nominal } ((5.5), \text{TBDY}) = 0.032$$

$$\text{From table 5A.1, TBDY: } \text{esuv}_v \text{nominal} = 0.08,$$

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

$$\text{y}_v, \text{sh}_v, \text{ft}_v, \text{fy}_v, \text{ are also multiplied by } \text{Min}(1, 1.25 * (\text{lb/ld})^{2/3}), \text{ from 10.3.5, ASCE 41-17.}$$

$$\text{with } \text{fs}_v = (\text{fs,jacket} * \text{Asl,mid,jacket} + \text{fs,mid} * \text{Asl,mid,core}) / \text{Asl,mid} = 389.0139$$

$$\text{with } \text{Esv} = (\text{Es,jacket} * \text{Asl,mid,jacket} + \text{Es,mid} * \text{Asl,mid,core}) / \text{Asl,mid} = 200000.00$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02528302$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.04909935$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.02869934$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.0557338$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.1476063$$

$$\mu_u = M R_c (4.14) = 4.9689E+008$$

$$u = s_u (4.1) = 8.4959181E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{u1}$ -

Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$\mu_u = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o (5A.5, TBDY) = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e ((5.4c), TBDY) = a_{se} * s_{h,min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$$

$$b_{max} = 750.00$$

$$h_{max} = 750.00$$

From EC8 A4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_u,f = 840.00$   
 $E_f = 82000.00$   
 $u,f = 0.015$

$ase((5.4d), \text{TBDY}) = (ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d)) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}((5.4d), \text{TBDY}) = L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}((5.4d), \text{TBDY}) = L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c =$  confinement factor = 1.0435

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_d = 0.30$$

$$s_u1 = 0.4 * e_{su1,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su1,nominal} = 0.08$ ,

For calculation of  $e_{su1,nominal}$  and  $y_1, sh_1, ft_1, fy_1$ , it is considered  
characteristic value  $f_{sy1} = f_{s1}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s1} = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$$

$$\text{with } E_{s1} = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$$

$$y_2 = 0.00140044$$

$$sh_2 = 0.0044814$$

$$ft_2 = 466.8167$$

$$fy_2 = 389.0139$$

$$s_u2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$$

$$s_u2 = 0.4 * e_{su2,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{su2,nominal} = 0.08$ ,

For calculation of  $e_{su2,nominal}$  and  $y_2, sh_2, ft_2, fy_2$ , it is considered  
characteristic value  $f_{sy2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_2, sh_2, ft_2, fy_2$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{s2} = (f_{s,jacket} * A_{s,com,jacket} + f_{s,core} * A_{s,com,core}) / A_{s,com} = 389.0139$$

$$\text{with } E_{s2} = (E_{s,jacket} * A_{s,com,jacket} + E_{s,core} * A_{s,com,core}) / A_{s,com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$s_{uv} = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$l_o/l_{ou,min} = l_b/l_d = 0.30$$

$$s_{uv} = 0.4 * e_{suv,nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered  
characteristic value  $f_{syv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } f_{sv} = (f_{s,jacket} * A_{s,mid,jacket} + f_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 389.0139$$

$$\text{with } E_{sv} = (E_{s,jacket} * A_{s,mid,jacket} + E_{s,mid} * A_{s,mid,core}) / A_{s,mid} = 200000.00$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.09206128$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.04740567$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{s,ten} / (b * d) * (f_{s1} / f_c) = 0.11310683$$

$$2 = A_{s,com} / (b * d) * (f_{s2} / f_c) = 0.05824278$$

$$v = A_{s,mid} / (b * d) * (f_{sv} / f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$\mu_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of  $\mu_{2+}$

Calculation of ultimate curvature  $\mu$  according to 4.1, Biskinis/Fardis 2013:

$$\mu = 8.4959181E-006$$

$$\mu = 4.9689E+008$$

with full section properties:

$$b = 750.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00093001$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$c_o \text{ (5A.5, TBDY)} = 0.002$$

$$\text{Final value of } c_u: c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } c_u = 0.01241186$$

$$w_e \text{ ((5.4c), TBDY)} = a_{se} * s_{h,\min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = a_f * p_f * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area})/(\text{total area})$

$$a_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f/b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_{u,f} = 840.00$$

$$E_f = 82000.00$$

$$u_{f} = 0.015$$

$$a_{se} \text{ ((5.4d), TBDY)} = (a_{se1} * A_{ext} + a_{se2} * A_{int})/A_{sec} = 0.45746528$$

$$a_{se1} = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length

equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$a_{se2} (>= a_{se1}) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}})/A_{\text{conf,max2}}) * (A_{\text{conf,min2}}/A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $p_{sh,y} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$su1 = 0.4 * esu1\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1\_nominal = 0.08$ ,

For calculation of  $esu1\_nominal$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s,ten,jacket} + f_{s,core} * A_{s,ten,core}) / A_{s,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s,ten,jacket} + E_{s,core} * A_{s,ten,core}) / A_{s,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$ft2 = 466.8167$

$fy2 = 389.0139$

$su2 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$l_o/l_{ou,min} = l_b/l_{b,min} = 0.30$

$su2 = 0.4 * esu2\_nominal$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu2\_nominal = 0.08$ ,

For calculation of  $esu2\_nominal$  and  $y2, sh2, ft2, fy2$ , it is considered

characteristic value  $f_{s2} = f_{s2}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{s2} = (f_{s,jacket} \cdot A_{s1,com,jacket} + f_{s,core} \cdot A_{s1,com,core}) / A_{s1,com} = 389.0139$

with  $E_{s2} = (E_{s,jacket} \cdot A_{s1,com,jacket} + E_{s,core} \cdot A_{s1,com,core}) / A_{s1,com} = 200000.00$

$y_v = 0.00140044$

$sh_v = 0.0044814$

$ft_v = 466.8167$

$fy_v = 389.0139$

$s_{uv} = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor

and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

$l_o/l_{ou,min} = l_b/l_d = 0.30$

$s_{uv} = 0.4 \cdot e_{suv,nominal} ((5.5), TBDY) = 0.032$

From table 5A.1, TBDY:  $e_{suv,nominal} = 0.08$ ,

considering characteristic value  $f_{sv} = f_{sv}/1.2$ , from table 5.1, TBDY

For calculation of  $e_{suv,nominal}$  and  $y_v, sh_v, ft_v, fy_v$ , it is considered

characteristic value  $f_{sv} = f_{sv}/1.2$ , from table 5.1, TBDY.

$y_1, sh_1, ft_1, fy_1$ , are also multiplied by  $\text{Min}(1, 1.25 \cdot (l_b/l_d)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $f_{sv} = (f_{s,jacket} \cdot A_{s1,mid,jacket} + f_{s,mid} \cdot A_{s1,mid,core}) / A_{s1,mid} = 389.0139$

with  $E_{sv} = (E_{s,jacket} \cdot A_{s1,mid,jacket} + E_{s,mid} \cdot A_{s1,mid,core}) / A_{s1,mid} = 200000.00$

$1 = A_{s1,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.02528302$

$2 = A_{s1,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.04909935$

$v = A_{s1,mid} / (b \cdot d) \cdot (f_{sv} / f_c) = 0.04462942$

and confined core properties:

$b = 690.00$

$d = 677.00$

$d' = 13.00$

$f_{cc} (5A.2, TBDY) = 34.43547$

$cc (5A.5, TBDY) = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$1 = A_{s1,ten} / (b \cdot d) \cdot (f_{s1} / f_c) = 0.02869934$

$2 = A_{s1,com} / (b \cdot d) \cdot (f_{s2} / f_c) = 0.0557338$

$v = A_{s1,mid} / (b \cdot d) \cdot (f_{sv} / f_c) = 0.05065988$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

---

$s_u (4.9) = 0.1476063$

$\mu_u = M R_c (4.14) = 4.9689E+008$

$u = s_u (4.1) = 8.4959181E-006$

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $\mu_{u2}$ -  
-----  
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

$u = 9.2452857E-006$

$\mu_u = 8.1540E+008$

-----  
with full section properties:

$b = 400.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00174378$

$N = 16273.607$

$f_c = 33.00$

$cc (5A.5, TBDY) = 0.002$

Final value of  $\mu_u$ :  $\mu_u^* = \text{shear\_factor} \cdot \text{Max}(c_u, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $c_u = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $a_{se} * s_{h,min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = a_f * p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $a_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$a_f = 0.31984848$

with Unconfined area =  $((b_{max} - 2R)^2 + (h_{max} - 2R)^2) / 3 = 140733.333$

$b_{max} = 750.00$

$h_{max} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f / b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$

$R = 40.00$

Effective FRP thickness,  $t_f = NL * t * \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{f} = 0.015$

$a_{se}$  ((5.4d), TBDY) =  $(a_{se1} * A_{ext} + a_{se2} * A_{int}) / A_{sec} = 0.45746528$

$a_{se1} = \text{Max}(((A_{conf,max1} - A_{noConf1}) / A_{conf,max1}) * (A_{conf,min1} / A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$a_{se2} (>= a_{se1}) = \text{Max}(((A_{conf,max2} - A_{noConf2}) / A_{conf,max2}) * (A_{conf,min2} / A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$p_{sh,min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$

Expression (5.4d) for  $p_{sh,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$p_{sh,x} * F_{ywe} = p_{sh1} * F_{ywe1} + p_{sh2} * F_{ywe2} = 3.0194$

$p_{sh1}$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s_1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$p_{sh2}$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s_2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

psh<sub>y</sub>\*Fywe = psh<sub>1</sub>\*Fywe<sub>1</sub>+ps<sub>2</sub>\*Fywe<sub>2</sub> = 3.0194  
psh<sub>1</sub> ((5.4d), TBDY) = Lstir<sub>1</sub>\*Astir<sub>1</sub>/(Asec\*s<sub>1</sub>) = 0.00367709  
Lstir<sub>1</sub> (Length of stirrups along X) = 2060.00  
Astir<sub>1</sub> (stirrups area) = 78.53982  
psh<sub>2</sub> ((5.4d), TBDY) = Lstir<sub>2</sub>\*Astir<sub>2</sub>/(Asec\*s<sub>2</sub>) = 0.00067082  
Lstir<sub>2</sub> (Length of stirrups along X) = 1468.00  
Astir<sub>2</sub> (stirrups area) = 50.26548

Asec = 440000.00

s<sub>1</sub> = 100.00

s<sub>2</sub> = 250.00

fywe<sub>1</sub> = 694.45

fywe<sub>2</sub> = 694.45

fce = 33.00

From ((5.A5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y<sub>1</sub> = 0.00140044

sh<sub>1</sub> = 0.0044814

ft<sub>1</sub> = 466.8167

fy<sub>1</sub> = 389.0139

su<sub>1</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su<sub>1</sub> = 0.4\*esu<sub>1\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>1\_nominal</sub> = 0.08,

For calculation of esu<sub>1\_nominal</sub> and y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, it is considered  
characteristic value fsy<sub>1</sub> = fs<sub>1</sub>/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>1</sub> = (fs<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + fs<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 389.0139

with Es<sub>1</sub> = (Es<sub>jacket</sub>\*Asl<sub>ten,jacket</sub> + Es<sub>core</sub>\*Asl<sub>ten,core</sub>)/Asl<sub>ten</sub> = 200000.00

y<sub>2</sub> = 0.00140044

sh<sub>2</sub> = 0.0044814

ft<sub>2</sub> = 466.8167

fy<sub>2</sub> = 389.0139

su<sub>2</sub> = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su<sub>2</sub> = 0.4\*esu<sub>2\_nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu<sub>2\_nominal</sub> = 0.08,

For calculation of esu<sub>2\_nominal</sub> and y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, it is considered  
characteristic value fsy<sub>2</sub> = fs<sub>2</sub>/1.2, from table 5.1, TBDY.

y<sub>2</sub>, sh<sub>2</sub>,ft<sub>2</sub>,fy<sub>2</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fs<sub>2</sub> = (fs<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + fs<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 389.0139

with Es<sub>2</sub> = (Es<sub>jacket</sub>\*Asl<sub>com,jacket</sub> + Es<sub>core</sub>\*Asl<sub>com,core</sub>)/Asl<sub>com</sub> = 200000.00

y<sub>v</sub> = 0.00140044

sh<sub>v</sub> = 0.0044814

ft<sub>v</sub> = 466.8167

fy<sub>v</sub> = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

suv = 0.4\*esuv<sub>nominal</sub> ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv<sub>nominal</sub> = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv<sub>nominal</sub> and y<sub>v</sub>, sh<sub>v</sub>,ft<sub>v</sub>,fy<sub>v</sub>, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y<sub>1</sub>, sh<sub>1</sub>,ft<sub>1</sub>,fy<sub>1</sub>, are also multiplied by Min(1,1.25\*(lb/d)<sup>2/3</sup>), from 10.3.5, ASCE 41-17.

with fsv = (fs<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + fs<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 389.0139

with Es<sub>v</sub> = (Es<sub>jacket</sub>\*Asl<sub>mid,jacket</sub> + Es<sub>mid</sub>\*Asl<sub>mid,core</sub>)/Asl<sub>mid</sub> = 200000.00

1 = Asl<sub>ten</sub>/(b\*d)\*(fs<sub>1</sub>/fc) = 0.09206128

2 = Asl<sub>com</sub>/(b\*d)\*(fs<sub>2</sub>/fc) = 0.04740567

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$f_{cc} (5A.2, TBDY) = 34.43547$$

$$c_c (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten}/(b*d)*(f_{s1}/f_c) = 0.11310683$$

$$2 = A_{sl,com}/(b*d)*(f_{s2}/f_c) = 0.05824278$$

$$v = A_{sl,mid}/(b*d)*(f_{sv}/f_c) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$$s_u (4.9) = 0.21669624$$

$$M_u = M_{Rc} (4.14) = 8.1540E+008$$

$$u = s_u (4.1) = 9.2452857E-006$$

Calculation of ratio  $l_b/l_d$

Inadequate Lap Length with  $l_b/l_d = 0.30$

Calculation of Shear Strength  $V_r = \text{Min}(V_{r1}, V_{r2}) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $V_{r1} = 1.0898E+006$

$V_{r1} = V_{Col} ((10.3), ASCE 41-17) = k_{nl} * V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v * f_y * d / s$ ' is replaced by ' $V_{s+} = f * V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} * Area_{jacket} + f'_{c,core} * Area_{core}) / Area_{section} = 33.00$ , but  $f_c^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$M_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 * h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$$

$V_{sj1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj1}$  is multiplied by  $Col_{j1} = 1.00$

$$s/d = 0.16666667$$

$V_{sj2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj2}$  is multiplied by  $Col_{j2} = 1.00$

$$s/d = 0.3125$$

$$V_{s,core} = V_{sc1} + V_{sc2} = 98297.73$$

$V_{sc1} = 98297.73$  is calculated for section web core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 1.00$

$$s/d = 0.56818182$$

$V_{s,c2} = 0.00$  is calculated for section flange core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 0.00$

$$s/d = 1.5625$$

$V_f$  ((11-3)-(11.4), ACI 440) = 463792.00

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot_a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = 45^\circ$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, \theta)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}$  ((11-5), ACI 440) = 328.00

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}$  ((10.3), ASCE 41-17) =  $k_{nl} \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$k_{nl} = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs ((11.3), ACI 440).

$\rho = 1$  (normal-weight concrete)

Mean concrete strength:  $f'_c = (f'_{c,jacket} \cdot Area_{jacket} + f'_{c,core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f'_c^{0.5} \leq 8.3$  MPa ((22.5.3.1), ACI 318-14)

$$M/d = 4.00$$

$$\mu_u = 1518.009$$

$$V_u = 0.00017144$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{sj1} + V_{sj2} = 802857.879$$

$V_{sj1} = 523602.964$  is calculated for section web jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.16666667$$

$V_{sj2} = 279254.914$  is calculated for section flange jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{sj2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.3125$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 98297.73$  is calculated for section web core, with:

d = 440.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c1 is multiplied by Col,c1 = 1.00  
 s/d = 0.56818182  
 Vs,c2 = 0.00 is calculated for section flange core, with:  
 d = 160.00  
 Av = 100530.965  
 fy = 555.56  
 s = 250.00  
 Vs,c2 is multiplied by Col,c2 = 0.00  
 s/d = 1.5625  
 Vf ((11-3)-(11.4), ACI 440) = 463792.00  
 f = 0.95, for fully-wrapped sections  
 wf/sf = 1 (FRP strips adjacent to one another).  
 In (11.3) sin + cos is replaced with (cot + cota)sina which is more a generalised expression,  
 where is the angle of the crack direction (see KANEPE).  
 This later relation, considered as a function Vf( , ), is implemented for every different fiber orientation ai,  
 as well as for 2 crack directions, = 45° and = -45° to take into consideration the cyclic seismic loading.  
 orientation 1: 1 = b1 + 90° = 90.00  
 Vf = Min(|Vf(45, 1)|, |Vf(-45,a1)|), with:  
 total thickness per orientation, tf1 = NL\*t/NoDir = 1.00  
 dfv = d (figure 11.2, ACI 440) = 707.00  
 ffe ((11-5), ACI 440) = 328.00  
 Ef = 82000.00  
 fe = 0.004, from (11.6a), ACI 440  
 with fu = 0.009  
 From (11-11), ACI 440: Vs + Vf <= 915872.391  
 bw = 400.00

-----  
 End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At local axis: 3  
 -----

Start Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1  
 At Shear local axis: 2  
 (Bending local axis: 3)  
 Section Type: rcjlc3

Constant Properties

-----  
 Knowledge Factor, = 0.87  
 Mean strength values are used for both shear and moment calculations.  
 Consequently:  
 Jacket  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 Existing Column  
 New material of Primary Member: Concrete Strength, fc = fcm = 33.00  
 New material of Primary Member: Steel Strength, fs = fsm = 555.56  
 Concrete Elasticity, Ec = 26999.444  
 Steel Elasticity, Es = 200000.00  
 #####  
 Note: Especially for the calculation of moment strengths,  
 the above steel re-bar strengths are multiplied by 1.25 according to R18.6.5, ACI 318-14  
 Jacket  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 Existing Column  
 New material: Steel Strength, fs = 1.25\*fsm = 694.45  
 #####  
 Max Height, Hmax = 750.00

Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Mean Confinement Factor overall section = 1.0435  
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_o/l_{o,min} = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

-----  
Stepwise Properties  
-----

At local axis: 2  
EDGE -A-  
Shear Force,  $V_a = -0.0001715$   
EDGE -B-  
Shear Force,  $V_b = 0.0001715$   
BOTH EDGES  
Axial Force,  $F = -16273.607$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $A_{sl,t} = 0.00$   
-Compression:  $A_{sl,c} = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $A_{sl,ten} = 1137.257$   
-Compression:  $A_{sl,com} = 2208.54$   
-Middle:  $A_{sl,mid} = 2007.478$

-----  
Calculation of Shear Capacity ratio ,  $V_e/V_r = 0.49879178$   
Member Controlled by Flexure ( $V_e/V_r < 1$ )  
Calculation of Shear Demand from fig. R18.6.5, ACI 318-14  $V_e = (M_{pr1} + M_{pr2})/l_n = 543597.759$   
with  
 $M_{pr1} = \text{Max}(\mu_{u1+} , \mu_{u1-}) = 8.1540E+008$   
 $\mu_{u1+} = 4.9689E+008$ , is the ultimate moment strength at the edge 1 of the member in the actual moment direction  
which is defined for the static loading combination  
 $\mu_{u1-} = 8.1540E+008$ , is the ultimate moment strength at the edge 1 of the member in the opposite moment  
direction which is defined for the static loading combination  
 $M_{pr2} = \text{Max}(\mu_{u2+} , \mu_{u2-}) = 8.1540E+008$   
 $\mu_{u2+} = 4.9689E+008$ , is the ultimate moment strength at the edge 2 of the member in the actual moment direction  
which is defined for the the static loading combination  
 $\mu_{u2-} = 8.1540E+008$ , is the ultimate moment strength at the edge 2 of the member in the opposite moment  
direction which is defined for the the static loading combination

-----  
Calculation of  $\mu_{u1+}$   
-----

-----  
Calculation of ultimate curvature  $\mu_u$  according to 4.1, Biskinis/Fardis 2013:

u = 8.4959181E-006  
Mu = 4.9689E+008

with full section properties:

b = 750.00  
d = 707.00  
d' = 43.00  
v = 0.00093001  
N = 16273.607  
fc = 33.00  
co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} * \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase * sh, \min * fy_{we} / f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af * pf * ff_e / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

bw = 400.00

effective stress from (A.35),  $ff_e = 765.1636$

fy = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area}) / (\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A 4.4.3(6),  $pf = 2tf / bw = 0.005$

bw = 400.00

effective stress from (A.35),  $ff_e = 765.1636$

R = 40.00

Effective FRP thickness,  $tf = NL * t * \text{Cos}(b1) = 1.00$

fu,f = 840.00

Ef = 82000.00

u,f = 0.015

ase ((5.4d), TBDY) =  $(ase1 * A_{ext} + ase2 * A_{int}) / A_{sec} = 0.45746528$

ase1 =  $\text{Max}(((A_{conf, \max 1} - A_{noConf1}) / A_{conf, \max 1}) * (A_{conf, \min 1} / A_{conf, \max 1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 1} = 353600.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf, \min 1} = 293525.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf, \max 1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

ase2 ( $\geq ase1$ ) =  $\text{Max}(((A_{conf, \max 2} - A_{noConf2}) / A_{conf, \max 2}) * (A_{conf, \min 2} / A_{conf, \max 2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf, \min}$  and  $A_{conf, \max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf, \max 2} = 171264.00$  is the confined core area at levels of member with hoops and

is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf, \min 2} = 54741.00$  is the confined core area at midway between the levels of hoops and

is calculated by reducing all the dimensions of the area  $A_{conf, \max 2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2 / 6$  as defined at (A.2).

$$psh_{min} * Fy_{we} = \text{Min}(psh_x * Fy_{we}, psh_y * Fy_{we}) = 3.0194$$

Expression (5.4d) for  $psh_{min} * Fy_{we}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$$psh_x * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along Y)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ (5.4d)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along Y)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$psh_y * Fy_{we} = psh1 * Fy_{we1} + ps2 * Fy_{we2} = 3.0194$$

$$psh1 \text{ ((5.4d), TBDY)} = Lstir1 * Astir1 / (Asec * s1) = 0.00367709$$

$$Lstir1 \text{ (Length of stirrups along X)} = 2060.00$$

$$Astir1 \text{ (stirrups area)} = 78.53982$$

$$psh2 \text{ ((5.4d), TBDY)} = Lstir2 * Astir2 / (Asec * s2) = 0.00067082$$

$$Lstir2 \text{ (Length of stirrups along X)} = 1468.00$$

$$Astir2 \text{ (stirrups area)} = 50.26548$$

$$Asec = 440000.00$$

$$s1 = 100.00$$

$$s2 = 250.00$$

$$fy_{we1} = 694.45$$

$$fy_{we2} = 694.45$$

$$f_{ce} = 33.00$$

$$\text{From ((5.A5), TBDY), TBDY: } cc = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$y1 = 0.00140044$$

$$sh1 = 0.0044814$$

$$ft1 = 466.8167$$

$$fy1 = 389.0139$$

$$su1 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/ld = 0.30$$

$$su1 = 0.4 * esu1_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs1 = (fs_{jacket} * Asl_{ten,jacket} + fs_{core} * Asl_{ten,core}) / Asl_{ten} = 389.0139$$

$$\text{with } Es1 = (Es_{jacket} * Asl_{ten,jacket} + Es_{core} * Asl_{ten,core}) / Asl_{ten} = 200000.00$$

$$y2 = 0.00140044$$

$$sh2 = 0.0044814$$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with Shear\_factor = 1.00

$$lo/lou_{min} = lb/lb_{min} = 0.30$$

$$su2 = 0.4 * esu2_{nominal} \text{ ((5.5), TBDY)} = 0.032$$

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2, sh2, ft2, fy2$ , it is considered characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs_{jacket} * Asl_{com,jacket} + fs_{core} * Asl_{com,core}) / Asl_{com} = 389.0139$$

$$\text{with } Es2 = (Es_{jacket} * Asl_{com,jacket} + Es_{core} * Asl_{com,core}) / Asl_{com} = 200000.00$$

$$y_v = 0.00140044$$

$$sh_v = 0.0044814$$

$$ft_v = 466.8167$$

$$fy_v = 389.0139$$

$$su_v = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor and also multiplied by the shear\_factor according to 15.7.1.4, with

Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fsjacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02528302

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04909935

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.04462942

and confined core properties:

b = 690.00

d = 677.00

d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.02869934

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.0557338

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.05065988

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

v < vs,y2 - LHS eq.(4.5) is satisfied

---->

su (4.9) = 0.1476063

Mu = MRc (4.14) = 4.9689E+008

u = su (4.1) = 8.4959181E-006

-----  
Calculation of ratio lb/ld

-----  
Inadequate Lap Length with lb/ld = 0.30  
-----  
-----

-----  
Calculation of Mu1-  
-----  
-----

-----  
Calculation of ultimate curvature u according to 4.1, Biskinis/Fardis 2013:

u = 9.2452857E-006

Mu = 8.1540E+008  
-----

with full section properties:

b = 400.00

d = 707.00

d' = 43.00

v = 0.00174378

N = 16273.607

fc = 33.00

co (5A.5, TBDY) = 0.002

Final value of cu:  $cu^* = \text{shear\_factor} \cdot \text{Max}(cu, cc) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $cu = 0.01241186$

we ((5.4c), TBDY) =  $ase \cdot sh_{\min} \cdot fy_{we}/f_{ce} + \text{Min}(fx, fy) = 0.0496383$

where  $f = af \cdot pf \cdot f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
fx = 0.03708128

Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$

af = 0.31984848

with Unconfined area =  $((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2)/3 = 140733.333$

bmax = 750.00

hmax = 750.00

From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$fy = 0.03708128$   
Expression ((15B.6), TBDY) is modified as  $af = 1 - (\text{Unconfined area})/(\text{total area})$   
 $af = 0.31984848$   
with Unconfined area =  $((b_{max}-2R)^2 + (h_{max}-2R)^2)/3 = 140733.333$   
 $b_{max} = 750.00$   
 $h_{max} = 750.00$   
From EC8 A.4.4.3(6),  $pf = 2tf/bw = 0.005$   
 $bw = 400.00$   
effective stress from (A.35),  $ff,e = 765.1636$

$R = 40.00$   
Effective FRP thickness,  $tf = NL*t*\text{Cos}(b1) = 1.00$   
 $f_{u,f} = 840.00$   
 $E_f = 82000.00$   
 $u_{,f} = 0.015$

$ase$  ((5.4d), TBDY) =  $(ase1*A_{ext} + ase2*A_{int})/A_{sec} = 0.45746528$

$ase1 = \text{Max}(((A_{conf,max1} - A_{noConf1})/A_{conf,max1}) * (A_{conf,min1}/A_{conf,max1}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$ase2$  ( $\geq ase1$ ) =  $\text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$psh_{,min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{,min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

$psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along Y) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along Y) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

$psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$   
 $psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$   
 $L_{stir1}$  (Length of stirrups along X) = 2060.00  
 $A_{stir1}$  (stirrups area) = 78.53982  
 $psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$   
 $L_{stir2}$  (Length of stirrups along X) = 1468.00  
 $A_{stir2}$  (stirrups area) = 50.26548

$A_{sec} = 440000.00$   
 $s1 = 100.00$   
 $s2 = 250.00$

fywe1 = 694.45  
fywe2 = 694.45  
fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499  
c = confinement factor = 1.0435

y1 = 0.00140044  
sh1 = 0.0044814  
ft1 = 466.8167  
fy1 = 389.0139  
su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044  
sh2 = 0.0044814  
ft2 = 466.8167  
fy2 = 389.0139  
su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044  
shv = 0.0044814  
ftv = 466.8167  
fyv = 389.0139  
suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/ld = 0.30

suv = 0.4\*esuv\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esuv\_nominal = 0.08,

considering characteristic value fsyv = fsv/1.2, from table 5.1, TBDY

For calculation of esuv\_nominal and yv, shv,ftv,fyv, it is considered  
characteristic value fsyv = fsv/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{ld})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fsv = (fs,jacket\*Asl,mid,jacket + fs,mid\*Asl,mid,core)/Asl,mid = 389.0139

with Esv = (Es,jacket\*Asl,mid,jacket + Es,mid\*Asl,mid,core)/Asl,mid = 200000.00

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.09206128

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.04740567

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.08368017

and confined core properties:

b = 340.00  
d = 677.00  
d' = 13.00

fcc (5A.2, TBDY) = 34.43547

cc (5A.5, TBDY) = 0.00243499

c = confinement factor = 1.0435

1 = Asl,ten/(b\*d)\*(fs1/fc) = 0.11310683

2 = Asl,com/(b\*d)\*(fs2/fc) = 0.05824278

v = Asl,mid/(b\*d)\*(fsv/fc) = 0.10280977

Case/Assumption: Unconfined full section - Steel rupture  
' satisfies Eq. (4.3)

--->

$v < v_{s,y2}$  - LHS eq.(4.5) is satisfied

--->

$s_u$  (4.9) = 0.21669624

$M_u = M_{Rc}$  (4.14) = 8.1540E+008

$u = s_u$  (4.1) = 9.2452857E-006

-----  
Calculation of ratio  $l_b/l_d$

-----  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
-----  
-----

-----  
Calculation of  $M_{u2+}$   
-----

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$u = 8.4959181E-006$

$M_u = 4.9689E+008$   
-----

with full section properties:

$b = 750.00$

$d = 707.00$

$d' = 43.00$

$v = 0.00093001$

$N = 16273.607$

$f_c = 33.00$

$\alpha$  (5A.5, TBDY) = 0.002

Final value of  $c_u$ :  $c_u^* = \text{shear\_factor} * \text{Max}(c_u, c_c) = 0.01241186$

The Shear\_factor is considered equal to 1 (pure moment strength)

From (5.4b), TBDY:  $c_u = 0.01241186$

$w_e$  ((5.4c), TBDY) =  $\alpha s_e * \text{sh, min} * f_{ywe}/f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$

where  $f = \alpha f_p * f_{fe}/f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

-----  
 $f_x = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha f = 0.31984848$

with Unconfined area =  $((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$

$b_{\text{max}} = 750.00$

$h_{\text{max}} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$f_y = 0.03708128$

Expression ((15B.6), TBDY) is modified as  $\alpha f = 1 - (\text{Unconfined area})/(\text{total area})$

$\alpha f = 0.31984848$

with Unconfined area =  $((b_{\text{max}} - 2R)^2 + (h_{\text{max}} - 2R)^2)/3 = 140733.333$

$b_{\text{max}} = 750.00$

$h_{\text{max}} = 750.00$

From EC8 A.4.4.3(6),  $p_f = 2t_f/b_w = 0.005$

$b_w = 400.00$

effective stress from (A.35),  $f_{f,e} = 765.1636$   
-----

$R = 40.00$

Effective FRP thickness,  $t_f = N L * t * \text{Cos}(b_1) = 1.00$

$f_{u,f} = 840.00$

$E_f = 82000.00$

$u_{,f} = 0.015$

$\alpha s_e$  ((5.4d), TBDY) =  $(\alpha s_e1 * A_{\text{ext}} + \alpha s_e2 * A_{\text{int}})/A_{\text{sec}} = 0.45746528$

$\alpha s_e1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}})/A_{\text{conf,max1}}) * (A_{\text{conf,min1}}/A_{\text{conf,max1}}), 0) = 0.45746528$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max1} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{conf,min1} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max1}$  by a length equal to half the clear spacing between external hoops.

$A_{noConf1} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $ase2 (>= ase1) = \text{Max}(((A_{conf,max2} - A_{noConf2})/A_{conf,max2}) * (A_{conf,min2}/A_{conf,max2}), 0) = 0.45746528$

The definitions of  $A_{noConf}$ ,  $A_{conf,min}$  and  $A_{conf,max}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988) "Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{conf,max2} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{conf,min2} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{conf,max2}$  by a length equal to half the clear spacing between internal hoops.

$A_{noConf2} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).  
 $psh_{min} * F_{ywe} = \text{Min}(psh_x * F_{ywe}, psh_y * F_{ywe}) = 3.0194$

Expression (5.4d) for  $psh_{min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without earthquake detailing (90° closed stirrups)

-----  
 $psh_x * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along Y) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  (5.4d) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along Y) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $psh_y * F_{ywe} = psh1 * F_{ywe1} + ps2 * F_{ywe2} = 3.0194$

$psh1$  ((5.4d), TBDY) =  $L_{stir1} * A_{stir1} / (A_{sec} * s1) = 0.00367709$

$L_{stir1}$  (Length of stirrups along X) = 2060.00

$A_{stir1}$  (stirrups area) = 78.53982

$psh2$  ((5.4d), TBDY) =  $L_{stir2} * A_{stir2} / (A_{sec} * s2) = 0.00067082$

$L_{stir2}$  (Length of stirrups along X) = 1468.00

$A_{stir2}$  (stirrups area) = 50.26548

-----  
 $A_{sec} = 440000.00$

$s1 = 100.00$

$s2 = 250.00$

$f_{ywe1} = 694.45$

$f_{ywe2} = 694.45$

$f_{ce} = 33.00$

From ((5.A5), TBDY), TBDY:  $cc = 0.00243499$

$c = \text{confinement factor} = 1.0435$

$y1 = 0.00140044$

$sh1 = 0.0044814$

$ft1 = 466.8167$

$fy1 = 389.0139$

$su1 = 0.00512$

using (30) in Biskinis/Fardis (2013) multiplied with  $shear\_factor$  and also multiplied by the  $shear\_factor$  according to 15.7.1.4, with  $Shear\_factor = 1.00$

$lo/lou_{min} = lb/ld = 0.30$

$su1 = 0.4 * esu1_{nominal}$  ((5.5), TBDY) = 0.032

From table 5A.1, TBDY:  $esu1_{nominal} = 0.08$ ,

For calculation of  $esu1_{nominal}$  and  $y1, sh1, ft1, fy1$ , it is considered characteristic value  $fsy1 = fs1/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

with  $fs1 = (f_{s,jacket} * A_{s1,ten,jacket} + f_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 389.0139$

with  $Es1 = (E_{s,jacket} * A_{s1,ten,jacket} + E_{s,core} * A_{s1,ten,core}) / A_{s1,ten} = 200000.00$

$y2 = 0.00140044$

$sh2 = 0.0044814$

$$ft2 = 466.8167$$

$$fy2 = 389.0139$$

$$su2 = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lo_{u,min} = lb/lb_{u,min} = 0.30$$

$$su2 = 0.4 * esu2_{nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esu2_{nominal} = 0.08$ ,

For calculation of  $esu2_{nominal}$  and  $y2$ ,  $sh2$ ,  $ft2$ ,  $fy2$ , it is considered  
characteristic value  $fsy2 = fs2/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1$ ,  $ft1$ ,  $fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fs2 = (fs_{jacket} * A_{sl,com,jacket} + fs_{core} * A_{sl,com,core}) / A_{sl,com} = 389.0139$$

$$\text{with } Es2 = (Es_{jacket} * A_{sl,com,jacket} + Es_{core} * A_{sl,com,core}) / A_{sl,com} = 200000.00$$

$$yv = 0.00140044$$

$$shv = 0.0044814$$

$$ftv = 466.8167$$

$$fyv = 389.0139$$

$$suv = 0.00512$$

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

$$lo/lo_{u,min} = lb/ld = 0.30$$

$$suv = 0.4 * esuv_{nominal} ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv_{nominal} = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv_{nominal}$  and  $yv$ ,  $shv$ ,  $ftv$ ,  $fyv$ , it is considered  
characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1$ ,  $sh1$ ,  $ft1$ ,  $fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs_{jacket} * A_{sl,mid,jacket} + fs_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 389.0139$$

$$\text{with } Esv = (Es_{jacket} * A_{sl,mid,jacket} + Es_{mid} * A_{sl,mid,core}) / A_{sl,mid} = 200000.00$$

$$1 = A_{sl,ten} / (b * d) * (fs1 / fc) = 0.02528302$$

$$2 = A_{sl,com} / (b * d) * (fs2 / fc) = 0.04909935$$

$$v = A_{sl,mid} / (b * d) * (fsv / fc) = 0.04462942$$

and confined core properties:

$$b = 690.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = A_{sl,ten} / (b * d) * (fs1 / fc) = 0.02869934$$

$$2 = A_{sl,com} / (b * d) * (fs2 / fc) = 0.05573338$$

$$v = A_{sl,mid} / (b * d) * (fsv / fc) = 0.05065988$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

---->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

---->

$$su (4.9) = 0.1476063$$

$$Mu = MRc (4.14) = 4.9689E+008$$

$$u = su (4.1) = 8.4959181E-006$$

-----  
Calculation of ratio  $lb/ld$

-----  
Inadequate Lap Length with  $lb/ld = 0.30$

-----  
Calculation of  $Mu2$ -

-----  
Calculation of ultimate curvature  $u$  according to 4.1, Biskinis/Fardis 2013:

$$u = 9.2452857E-006$$

$$Mu = 8.1540E+008$$

with full section properties:

$$b = 400.00$$

$$d = 707.00$$

$$d' = 43.00$$

$$v = 0.00174378$$

$$N = 16273.607$$

$$f_c = 33.00$$

$$\alpha (5A.5, \text{TBDY}) = 0.002$$

$$\text{Final value of } \alpha: \alpha^* = \text{shear\_factor} * \text{Max}(\alpha, \alpha_c) = 0.01241186$$

The Shear\_factor is considered equal to 1 (pure moment strength)

$$\text{From (5.4b), TBDY: } \alpha = 0.01241186$$

$$\omega_e ((5.4c), \text{TBDY}) = \alpha s_e * \text{sh}_{\min} * f_{ywe} / f_{ce} + \text{Min}(f_x, f_y) = 0.0496383$$

where  $f = \alpha^* p_f * f_{fe} / f_{ce}$  is accounting for FRP contribution like EC8-part3 A.4.4.3(6)

$$f_x = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$f_y = 0.03708128$$

Expression ((15B.6), TBDY) is modified as  $\alpha_f = 1 - (\text{Unconfined area}) / (\text{total area})$

$$\alpha_f = 0.31984848$$

$$\text{with Unconfined area} = ((b_{\max} - 2R)^2 + (h_{\max} - 2R)^2) / 3 = 140733.333$$

$$b_{\max} = 750.00$$

$$h_{\max} = 750.00$$

$$\text{From EC8 A.4.4.3(6), } p_f = 2t_f / b_w = 0.005$$

$$b_w = 400.00$$

$$\text{effective stress from (A.35), } f_{f,e} = 765.1636$$

$$R = 40.00$$

$$\text{Effective FRP thickness, } t_f = N L * t * \text{Cos}(b_1) = 1.00$$

$$f_u, f = 840.00$$

$$E_f = 82000.00$$

$$u, f = 0.015$$

$$\alpha_s_e ((5.4d), \text{TBDY}) = (\alpha_s e_1 * A_{\text{ext}} + \alpha_s e_2 * A_{\text{int}}) / A_{\text{sec}} = 0.45746528$$

$$\alpha_s e_1 = \text{Max}(((A_{\text{conf,max1}} - A_{\text{noConf1}}) / A_{\text{conf,max1}}) * (A_{\text{conf,min1}} / A_{\text{conf,max1}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max1}} = 353600.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the external perimeter hoops.

$A_{\text{conf,min1}} = 293525.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max1}}$  by a length equal to half the clear spacing between external hoops.

$A_{\text{noConf1}} = 158733.333$  is the unconfined external core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$\alpha_s e_2 (> \alpha_s e_1) = \text{Max}(((A_{\text{conf,max2}} - A_{\text{noConf2}}) / A_{\text{conf,max2}}) * (A_{\text{conf,min2}} / A_{\text{conf,max2}}), 0) = 0.45746528$$

The definitions of  $A_{\text{noConf}}$ ,  $A_{\text{conf,min}}$  and  $A_{\text{conf,max}}$  are derived from generalization of the rectangular sections confinement, which is expressed by (5.4d).

The generalization is done according to Mander, J., Priestley, M., and Park, R. (1988)

"Theoretical Stress-Strain Model for Confined Concrete."

J. Struct. Eng., 10.1061/(ASCE)0733-9445(1988)114:8(1804), 1804-1826.

$A_{\text{conf,max2}} = 171264.00$  is the confined core area at levels of member with hoops and is calculated as the area of core enclosed by the center lines of the internal perimeter hoops.

$A_{\text{conf,min2}} = 54741.00$  is the confined core area at midway between the levels of hoops and is calculated by reducing all the dimensions of the area  $A_{\text{conf,max2}}$  by a length equal to half the clear spacing between internal hoops.

$A_{\text{noConf2}} = 106242.667$  is the unconfined internal core area which is equal to  $b_i^2/6$  as defined at (A.2).

$$p_{sh,\min} * F_{ywe} = \text{Min}(p_{sh,x} * F_{ywe}, p_{sh,y} * F_{ywe}) = 3.0194$$

Expression (5.4d) for  $p_{sh,\min} * F_{ywe}$  has been multiplied by 0.3 according to 15.7.1.3 for members without

earthquake detailing (90° closed stirrups)

psh\_x\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along Y) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 (5.4d) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along Y) = 1468.00  
Astir2 (stirrups area) = 50.26548

psh\_y\*Fywe = psh1\*Fywe1+ps2\*Fywe2 = 3.0194  
psh1 ((5.4d), TBDY) = Lstir1\*Astir1/(Asec\*s1) = 0.00367709  
Lstir1 (Length of stirrups along X) = 2060.00  
Astir1 (stirrups area) = 78.53982  
psh2 ((5.4d), TBDY) = Lstir2\*Astir2/(Asec\*s2) = 0.00067082  
Lstir2 (Length of stirrups along X) = 1468.00  
Astir2 (stirrups area) = 50.26548

Asec = 440000.00

s1 = 100.00

s2 = 250.00

fywe1 = 694.45

fywe2 = 694.45

fce = 33.00

From ((5.A.5), TBDY), TBDY: cc = 0.00243499

c = confinement factor = 1.0435

y1 = 0.00140044

sh1 = 0.0044814

ft1 = 466.8167

fy1 = 389.0139

su1 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

su1 = 0.4\*esu1\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu1\_nominal = 0.08,

For calculation of esu1\_nominal and y1, sh1,ft1,fy1, it is considered  
characteristic value fsy1 = fs1/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs1 = (fs,jacket\*Asl,ten,jacket + fs,core\*Asl,ten,core)/Asl,ten = 389.0139

with Es1 = (Es,jacket\*Asl,ten,jacket + Es,core\*Asl,ten,core)/Asl,ten = 200000.00

y2 = 0.00140044

sh2 = 0.0044814

ft2 = 466.8167

fy2 = 389.0139

su2 = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/lb,min = 0.30

su2 = 0.4\*esu2\_nominal ((5.5), TBDY) = 0.032

From table 5A.1, TBDY: esu2\_nominal = 0.08,

For calculation of esu2\_nominal and y2, sh2,ft2,fy2, it is considered  
characteristic value fsy2 = fs2/1.2, from table 5.1, TBDY.

y1, sh1,ft1,fy1, are also multiplied by  $\text{Min}(1, 1.25 \cdot (\text{lb}/\text{d})^{2/3})$ , from 10.3.5, ASCE 41-17.

with fs2 = (fs,jacket\*Asl,com,jacket + fs,core\*Asl,com,core)/Asl,com = 389.0139

with Es2 = (Es,jacket\*Asl,com,jacket + Es,core\*Asl,com,core)/Asl,com = 200000.00

yv = 0.00140044

shv = 0.0044814

ftv = 466.8167

fyv = 389.0139

suv = 0.00512

using (30) in Biskinis/Fardis (2013) multiplied with shear\_factor  
and also multiplied by the shear\_factor according to 15.7.1.4, with  
Shear\_factor = 1.00

lo/lou,min = lb/d = 0.30

$$suv = 0.4 * esuv\_nominal ((5.5), TBDY) = 0.032$$

From table 5A.1, TBDY:  $esuv\_nominal = 0.08$ ,

considering characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY

For calculation of  $esuv\_nominal$  and  $yv$ ,  $shv, ftv, fyv$ , it is considered characteristic value  $fsyv = fsv/1.2$ , from table 5.1, TBDY.

$y1, sh1, ft1, fy1$ , are also multiplied by  $\text{Min}(1, 1.25 * (lb/ld)^{2/3})$ , from 10.3.5, ASCE 41-17.

$$\text{with } fsv = (fs\_jacket * Asl\_mid\_jacket + fs\_mid * Asl\_mid\_core) / Asl\_mid = 389.0139$$

$$\text{with } Esv = (Es\_jacket * Asl\_mid\_jacket + Es\_mid * Asl\_mid\_core) / Asl\_mid = 200000.00$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.09206128$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.04740567$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.08368017$$

and confined core properties:

$$b = 340.00$$

$$d = 677.00$$

$$d' = 13.00$$

$$fcc (5A.2, TBDY) = 34.43547$$

$$cc (5A.5, TBDY) = 0.00243499$$

$$c = \text{confinement factor} = 1.0435$$

$$1 = Asl\_ten / (b * d) * (fs1 / fc) = 0.11310683$$

$$2 = Asl\_com / (b * d) * (fs2 / fc) = 0.05824278$$

$$v = Asl\_mid / (b * d) * (fsv / fc) = 0.10280977$$

Case/Assumption: Unconfined full section - Steel rupture

' satisfies Eq. (4.3)

--->

$v < vs,y2$  - LHS eq.(4.5) is satisfied

--->

$$su (4.9) = 0.21669624$$

$$Mu = MRc (4.14) = 8.1540E+008$$

$$u = su (4.1) = 9.2452857E-006$$

Calculation of ratio  $lb/ld$

Inadequate Lap Length with  $lb/ld = 0.30$

Calculation of Shear Strength  $Vr = \text{Min}(Vr1, Vr2) = 1.0898E+006$

Calculation of Shear Strength at edge 1,  $Vr1 = 1.0898E+006$

$Vr1 = VCol ((10.3), ASCE 41-17) = knl * VCol0$

$$VCol0 = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $Vs = Av * fy * d / s$ ' is replaced by ' $Vs + f * Vf$ ' where  $Vf$  is the contribution of FRPs (11.3), ACI 440).

= 1 (normal-weight concrete)

Mean concrete strength:  $fc' = (fc'_jacket * Area\_jacket + fc'_core * Area\_core) / Area\_section = 33.00$ , but  $fc'^{0.5} <= 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$Mu = 1518.777$$

$$Vu = 0.0001715$$

$$d = 0.8 * h = 600.00$$

$$Nu = 16273.607$$

$$Ag = 300000.00$$

$$\text{From (11.5.4.8), ACI 318-14: } Vs = Vs\_jacket + Vs\_core = 901155.609$$

where:

$$Vs\_jacket = Vs\_j1 + Vs\_j2 = 802857.879$$

$Vs\_j1 = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$Av = 157079.633$$

$$fy = 555.56$$

$$s = 100.00$$

$Vs\_j1$  is multiplied by  $Col\_j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$V_f((11-3)-(11.4), ACI 440) = 463792.00$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a_i)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b_1 + 90^\circ = 90.00$

$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a_1)|)$ , with:

total thickness per orientation,  $t_{f1} = NL \cdot t / \text{NoDir} = 1.00$

$d_{fv} = d$  (figure 11.2, ACI 440) = 707.00

$f_{fe}((11-5), ACI 440) = 328.00$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

From (11-11), ACI 440:  $V_s + V_f \leq 915872.391$

$$b_w = 400.00$$

Calculation of Shear Strength at edge 2,  $V_{r2} = 1.0898E+006$

$V_{r2} = V_{Col}((10.3), ASCE 41-17) = knl \cdot V_{Col0}$

$$V_{Col0} = 1.0898E+006$$

$knl = 1$  (zero step-static loading)

NOTE: In expression (10-3) ' $V_s = A_v \cdot f_y \cdot d / s$ ' is replaced by ' $V_s + f \cdot V_f$ ' where  $V_f$  is the contribution of FRPs (11.3), ACI 440).

$\lambda = 1$  (normal-weight concrete)

Mean concrete strength:  $f_c' = (f_c'_{jacket} \cdot Area_{jacket} + f_c'_{core} \cdot Area_{core}) / Area_{section} = 33.00$ , but  $f_c'^{0.5} \leq 8.3$  MPa (22.5.3.1, ACI 318-14)

$$M/Vd = 4.00$$

$$\mu_u = 1518.776$$

$$V_u = 0.0001715$$

$$d = 0.8 \cdot h = 600.00$$

$$N_u = 16273.607$$

$$A_g = 300000.00$$

From (11.5.4.8), ACI 318-14:  $V_s = V_{s,jacket} + V_{s,core} = 901155.609$

where:

$$V_{s,jacket} = V_{s,j1} + V_{s,j2} = 802857.879$$

$V_{s,j1} = 279254.914$  is calculated for section web jacket, with:

$$d = 320.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j1}$  is multiplied by  $Col,j1 = 1.00$

$$s/d = 0.3125$$

$V_{s,j2} = 523602.964$  is calculated for section flange jacket, with:

$$d = 600.00$$

$$A_v = 157079.633$$

$$f_y = 555.56$$

$$s = 100.00$$

$V_{s,j2}$  is multiplied by  $Col,j2 = 1.00$

$$s/d = 0.16666667$$

$$V_{s,core} = V_{s,c1} + V_{s,c2} = 98297.73$$

$V_{s,c1} = 0.00$  is calculated for section web core, with:

$$d = 160.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c1}$  is multiplied by  $Col,c1 = 0.00$

$$s/d = 1.5625$$

$V_{s,c2} = 98297.73$  is calculated for section flange core, with:

$$d = 440.00$$

$$A_v = 100530.965$$

$$f_y = 555.56$$

$$s = 250.00$$

$V_{s,c2}$  is multiplied by  $Col,c2 = 1.00$

$$s/d = 0.56818182$$

$$V_f((11-3)-(11.4), ACI 440) = 463792.00$$

$f = 0.95$ , for fully-wrapped sections

$w_f/s_f = 1$  (FRP strips adjacent to one another).

In (11.3)  $\sin + \cos$  is replaced with  $(\cot + \cot a)\sin a$  which is more a generalised expression, where  $a$  is the angle of the crack direction (see KANEPE).

This later relation, considered as a function  $V_f(\theta, a)$ , is implemented for every different fiber orientation  $a_i$ , as well as for 2 crack directions,  $\theta = 45^\circ$  and  $\theta = -45^\circ$  to take into consideration the cyclic seismic loading.

orientation 1:  $\theta = b1 + 90^\circ = 90.00$

$$V_f = \text{Min}(|V_f(45, \theta)|, |V_f(-45, a1)|), \text{ with:}$$

total thickness per orientation,  $t_{f1} = NL * t / \text{NoDir} = 1.00$

$$d_{fv} = d \text{ (figure 11.2, ACI 440)} = 707.00$$

$$f_{fe} \text{ ((11-5), ACI 440)} = 328.00$$

$$E_f = 82000.00$$

$$f_e = 0.004, \text{ from (11.6a), ACI 440}$$

$$\text{with } f_u = 0.009$$

$$\text{From (11-11), ACI 440: } V_s + V_f \leq 915872.391$$

$$b_w = 400.00$$

-----  
End Of Calculation of Shear Capacity ratio for element: column JLC1 of floor 1

At local axis: 2  
-----

-----  
Start Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)

Section Type: rcjlc3

Constant Properties  
-----

Knowledge Factor,  $\gamma = 0.87$

Chord Rotation is generally considered as Deformation-Controlled Action according to Table C7-1, ASCE 41-17.

Mean strengths are used for Deformation-Controlled Actions according to 7.5.1.3, ASCE 41-17

Consequently:

Jacket

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$

Steel Elasticity,  $E_s = 200000.00$

Existing Column

New material of Primary Member: Concrete Strength,  $f_c = f_{cm} = 33.00$

New material of Primary Member: Steel Strength,  $f_s = f_{sm} = 555.56$

Concrete Elasticity,  $E_c = 26999.444$   
Steel Elasticity,  $E_s = 200000.00$   
Max Height,  $H_{max} = 750.00$   
Min Height,  $H_{min} = 400.00$   
Max Width,  $W_{max} = 750.00$   
Min Width,  $W_{min} = 400.00$   
Jacket Thickness,  $t_j = 100.00$   
Cover Thickness,  $c = 25.00$   
Element Length,  $L = 3000.00$   
Primary Member  
Ribbed Bars  
Ductile Steel  
Without Detailing for Earthquake Resistance (including stirrups not closed at 135°)  
Longitudinal Bars With Ends Lapped Starting at the End Sections  
Inadequate Lap Length with  $l_b/l_d = 0.30$   
FRP Wrapping Data  
Type: Carbon  
Dry properties (design values)  
Thickness,  $t = 1.00$   
Tensile Strength,  $f_{fu} = 840.00$   
Tensile Modulus,  $E_f = 82000.00$   
Elongation,  $e_{fu} = 0.009$   
Number of directions,  $N_{oDir} = 1$   
Fiber orientations,  $b_i = 0.00^\circ$   
Number of layers,  $N_L = 1$   
Radius of rounding corners,  $R = 40.00$

#### Stepwise Properties

Bending Moment,  $M = 793215.62$   
Shear Force,  $V_2 = 7630.77$   
Shear Force,  $V_3 = -206.4342$   
Axial Force,  $F = -19223.50$   
Longitudinal Reinforcement Area Distribution (in 2 divisions)  
-Tension:  $As_t = 0.00$   
-Compression:  $As_c = 5353.274$   
Longitudinal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten} = 1137.257$   
-Compression:  $As_{c,com} = 2208.54$   
-Middle:  $As_{c,mid} = 2007.478$   
Longitudinal External Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,jacket} = 829.3805$   
-Compression:  $As_{c,com,jacket} = 1746.726$   
-Middle:  $As_{c,mid,jacket} = 1545.664$   
Longitudinal Internal Reinforcement Area Distribution (in 3 divisions)  
-Tension:  $As_{t,ten,core} = 307.8761$   
-Compression:  $As_{c,com,core} = 461.8141$   
-Middle:  $As_{c,mid,core} = 461.8141$   
Mean Diameter of Tension Reinforcement,  $Db_L = 16.80$

New component: From table 7-7, ASCE 41\_17: Final chord rotation Capacity  $u_{,R} = 1.0^*$   $u = 0.03024022$   
 $u = y + p = 0.03024022$

- Calculation of  $y$  -

$y = (M_y * L_s / 3) / E_{eff} = 0.00024022$  ((4.29), Biskinis Phd))  
 $M_y = 3.6682E+008$   
 $L_s = M/V$  (with  $L_s > 0.1 * L$  and  $L_s < 2 * L$ ) = 300.00  
From table 10.5, ASCE 41\_17:  $E_{eff} = factor * E_c * I_g = 1.5270E+014$   
factor = 0.30  
 $A_g = 440000.00$   
Mean concrete strength:  $fc' = (fc'_{jacket} * Area_{jacket} + fc'_{core} * Area_{core}) / Area_{section} = 33.00$

$$N = 19223.50$$

$$E_c \cdot I_g = E_c \cdot I_{g\_jacket} + E_c \cdot I_{g\_core} = 5.0901E+014$$

Calculation of Yielding Moment  $M_y$

Calculation of  $y$  and  $M_y$  according to Annex 7 -

Assuming neutral axis within flange ( $y < t/d$ , compression zone rectangular) with:

flange width,  $b = 750.00$

web width,  $b_w = 400.00$

flange thickness,  $t = 400.00$

$$y = \text{Min}(y_{\text{ten}}, y_{\text{com}})$$

$$y_{\text{ten}} = 2.7307817E-006$$

$$\text{with } ((10.1), \text{ASCE 41-17}) f_y = \text{Min}(f_y, 1.25 \cdot f_y \cdot (l_b/d)^{2/3}) = 311.2112$$

$$d = 707.00$$

$$y = 0.19403023$$

$$A = 0.01021225$$

$$B = 0.00452265$$

$$\text{with } p_t = 0.00729988$$

$$p_c = 0.00416509$$

$$p_v = 0.00378591$$

$$N = 19223.50$$

$$b = 750.00$$

$$" = 0.06082037$$

$$y_{\text{comp}} = 1.6517162E-005$$

$$\text{with } f_c^* (12.3, \text{ACI 440}) = 33.60672$$

$$f_c = 33.00$$

$$f_l = 0.61848273$$

$$b = b_{\text{max}} = 750.00$$

$$h = h_{\text{max}} = 750.00$$

$$A_g = 0.44$$

$$g = p_t + p_c + p_v = 0.01009575$$

$$r_c = 40.00$$

$$A_e/A_c = 0.31291181$$

$$\text{Effective FRP thickness, } t_f = N_L \cdot t \cdot \text{Cos}(b_1) = 1.00$$

$$\text{effective strain from (12.5) and (12.12), } e_{fe} = 0.004$$

$$f_u = 0.009$$

$$E_f = 82000.00$$

$$E_c = 26999.444$$

$$y = 0.19186199$$

$$A = 0.01001485$$

$$B = 0.00440616$$

$$\text{with } E_s = 200000.00$$

CONFIRMATION:  $y = 0.19289193 < t/d$

Calculation of ratio  $l_b/d$

Inadequate Lap Length with  $l_b/d = 0.30$

- Calculation of  $p$  -

From table 10-8:  $p = 0.03$

with:

- Columns controlled by inadequate development or splicing along the clear height because  $l_b/d < 1$

$$\text{shear control ratio } V_y E / C o I O E = 0.49879178$$

$$d = d_{\text{external}} = 707.00$$

$$s = s_{\text{external}} = 0.00$$

$$- t = s_1 + s_2 + 2 \cdot t_f / b_w \cdot (f_{fe} / f_s) = 0.00729988$$

$$\text{jacket: } s_1 = A_{v1} \cdot L_{\text{stir1}} / (s_1 \cdot A_g) = 0.00367709$$

$A_{v1} = 78.53982$ , is the area of every stirrup parallel to loading (shear) direction

$L_{\text{stir1}} = 2060.00$ , is the total Length of all stirrups parallel to loading (shear) direction

$$s1 = 100.00$$

$$\text{core: } s2 = Av2 * Lstir2 / (s2 * Ag) = 0.00067082$$

Av2 = 50.26548, is the area of every stirrup parallel to loading (shear) direction

Lstir2 = 1468.00, is the total Length of all stirrups parallel to loading (shear) direction

$$s2 = 250.00$$

The term  $2 * tf / bw * (ffe / fs)$  is implemented to account for FRP contribution

where  $f = 2 * tf / bw$  is FRP ratio (EC8 - 3, A.4.4.3(6)) and  $ffe / fs$  normalises  $f$  to steel strength

All these variables have already been given in Shear control ratio calculation.

For the normalisation  $fs$  of jacket is used.

$$NUD = 19223.50$$

$$Ag = 440000.00$$

$$fcE = (fc\_jacket * Area\_jacket + fc\_core * Area\_core) / section\_area = 33.00$$

$$fyIE = (fy\_ext\_Long\_Reinf * Area\_ext\_Long\_Reinf + fy\_int\_Long\_Reinf * Area\_int\_Long\_Reinf) / Area\_Tot\_Long\_Rein = 555.56$$

$$fytE = (fy\_ext\_Trans\_Reinf * s1 + fy\_int\_Trans\_Reinf * s2) / (s1 + s2) = 555.56$$

$$pl = Area\_Tot\_Long\_Rein / (b * d) = 0.01009575$$

$$b = 750.00$$

$$d = 707.00$$

$$fcE = 33.00$$

-----  
End Of Calculation of Chord Rotation Capacity for element: column JLC1 of floor 1

At local axis: 3

Integration Section: (b)  
-----